



Designation: C1318 – 15

# Standard Test Method for Determination of Total Neutralizing Capability and Dissolved Calcium and Magnesium Oxide in Lime for Flue Gas Desulfurization (FGD)<sup>1</sup>

This standard is issued under the fixed designation C1318; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers analysis of magnesian, dolomitic and high-calcium limes for total neutralizing capability and dissolved major oxides. Dissolved calcium and magnesium are the major species that neutralize acid under the conditions of the test.

1.2 The test conditions are chosen to measure the acid-neutralizing capacity of both calcium hydroxide and magnesium hydroxide contained in slaked lime. By controlling the neutralization pH at 6, magnesium hydroxide and magnesium oxide are titrated in addition to calcium hydroxide fraction.

1.3 This test method also determines the fraction of Mg ions present in the lime that will dissolve under lime flue gas desulfurization (FGD) conditions. Because the  $Mg^{++}$  ion alters FGD performance, it is important to know its concentration.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

C25 Test Methods for Chemical Analysis of Limestone, Quicklime, and Hydrated Lime

C50 Practice for Sampling, Sample Preparation, Packaging, and Marking of Lime and Limestone Products

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C07 on Lime and Limestone and is the direct responsibility of Subcommittee C07.05 on Chemical Tests.

Current edition approved June 1, 2015. Published June 2015. Originally approved in 1995. Last previous edition approved in 2009 as C1318 – 95 (2009) <sup>$\epsilon$ 1</sup>. DOI: 10.1520/C1318-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C51 Terminology Relating to Lime and Limestone (as used by the Industry)

C110 Test Methods for Physical Testing of Quicklime, Hydrated Lime, and Limestone

C1301 Test Method for Major and Trace Elements in Limestone and Lime by Inductively Coupled Plasma-Atomic Emission Spectroscopy (ICP) and Atomic Absorption (AA)

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

## 3. Terminology

3.1 *Definitions*—Unless otherwise specified, for definitions of terms used in these test methods refer to Terminology C51.

## 4. Summary of Test Method

4.1 Lime is slaked by boiling and is reacted with acid at a pH and residence time similar to those found in full-scale FGD reaction tanks.

4.2 A sample of lime is titrated with 1N hydrochloric acid, maintaining a pH of 6 for 30 min. After 30 min, the acid consumption is recorded. The total neutralizing capacity is calculated from the acid consumption and reported as CaO. Dissolved magnesium is determined by spectrometry or by EDTA titration and reported as percent dissolved Magnesium Oxide (as MgO).

## 5. Significance and Use

5.1 There are existing lime-based flue gas desulfurization units in operation that require a method to measure the oxides available for sulfur dioxide absorption. Dissolved magnesium oxide varies among limes depending on the limestone sources and calcination conditions.

## 6. Interferences

6.1 Any substance reacting with acid under the conditions of the test will contribute to the total oxide and dissolved oxide values.

6.2 Magnesium in forms other than MgO, which dissolve under test conditions, may affect the dissolved MgO and total oxide value.