This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: C1511 - 04 (Reapproved 2009) C1511 - 15

Standard Test Method for Determining the Water Retention (Repellency) Characteristics of Fibrous Glass Insulation (Aircraft Type)¹

This standard is issued under the fixed designation C1511; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a laboratory procedure for evaluating the water absorption potential of blanket insulation for aircraft, thereby providing a measure of potential weight increase due to water retention in an aircraft.

1.2 The water repellency (or retention) characteristics of materials <u>maycan</u> be affected by conditions such as contamination or temperature of the water. Values obtained as a result of this test method <u>maydoes</u> not adequately describe the water repellency characteristics of materials subject to these conditions.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

C168 Terminology Relating to Thermal Insulation

C390 Practice for Sampling and Acceptance of Thermal Insulation Lots

C800 Specification for Fibrous Glass Blanket Insulation (Aircraft Type)

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Terminology

3.1 Definitions—Terminology C168 shall be considered as applying to the terms used in this specification.

https://standards.iteh.ai/catalog/standards/sist/c7e5253e-7f90-4be1-b9c2-8e991c607971/astm-c1511-15

4. Summary of Test Method

4.1 The insulation is weighed then submerged in de-ionized (or distilled) water for 15 min; it is drained for 60 s and reweighed. The amount of water retained is the difference in specimen weights and is expressed in grams.

5. Significance and Use

5.1 The water retention of the insulation can result in an increase in weight and a resultant potential degradation in the properties of the insulation.

6. Apparatus

6.1 The water repellency test apparatus is shown in Fig. 1.

6.2 Scale, accurate to 0.1 g.

¹ This test method is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.33 on Insulation Finishes and Moisture.

Current edition approved May 1, 2009March 1, 2015. Published August 2009June 2015. Originally approved in 2001. Last previous edition approved in 20042009 as C1511- 04.04(2009). DOI: 10.1520/C1511-04R09.10.1520/C1511-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.