



# **Standard Practice for Specimen Preparation and Mounting of Textile, Paper or Polymeric (Including Vinyl) and Wood Wall or Ceiling Coverings, Facings and Veneers, to Assess Surface Burning Characteristics<sup>1</sup>**

This standard is issued under the fixed designation E2404; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## **1. Scope**

1.1 This practice describes procedures for specimen preparation and mounting when testing textile, paper, vinyl, expanded vinyl or other polymeric wall or ceiling covering materials to assess flame spread and smoke development as surface burning characteristics using Test Method E84.

1.2 This practice applies also to facings or wood veneers intended to be applied on site over a wood substrate (see 8.7).

1.3 This practice applies also to water-resistive barriers that are used as a component of exterior wall systems, as part of the exterior envelope (see 3.2.10 and 8.9).

1.4 This practice does not apply to the following:

1.4.1 Laminated products factory produced with a wood substrate, which are covered by Practice E2579.

1.4.2 Water-resistive barriers comprised of foam plastic materials contained within the wall system (see 5.3.1).

1.4.3 Water vapor retarders used, in conjunction with thermal insulation, on the interior or exterior side of an exterior wall (see 3.2.11 and 5.3.1).

1.5 Testing is conducted with Test Method E84.

1.6 This practice does not provide pass/fail criteria that can be used as a regulatory tool.

1.7 Use the values stated in inch-pound units as the standard, in referee decisions. The values in the SI system of units are given in parentheses, for information only; see IEEE/ASTM SI-10 for further details.

1.8 This fire standard cannot be used to provide quantitative measures.

1.9 Fire testing of products and materials is inherently hazardous, and adequate safeguards for personnel and property

shall be employed in conducting these tests. Fire testing involves hazardous materials, operations, and equipment. This standard gives instructions on specimen preparation and mounting, but the fire-test-response method is given in Test Method E84. See also Section 10.

1.10 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.11 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes shall not be considered requirements of the standard.

## **2. Referenced Documents**

2.1 *ASTM Standards:*<sup>2</sup>

C1186 Specification for Flat Fiber-Cement Sheets

C1396/C1396M Specification for Gypsum Board

E84 Test Method for Surface Burning Characteristics of Building Materials

E176 Terminology of Fire Standards

E2573 Practice for Specimen Preparation and Mounting of Site-Fabricated Stretch Systems to Assess Surface Burning Characteristics

E2579 Practice for Specimen Preparation and Mounting of Wood Products to Assess Surface Burning Characteristics

IEEE/ASTM SI-10 International System of Units (SI): The Modern Metric System

2.2 *CSA Standard:*<sup>3</sup>

CSA O121 Douglas Fir Plywood

2.3 *NIST Standard:*<sup>4</sup>

Voluntary Product Standard PS 1-07 Structural Plywood

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee E05 on Fire Standards and is the direct responsibility of Subcommittee E05.22 on Surface Burning.

Current edition approved June 1, 2015. Published July 2015. Originally approved in 2005. Last previous edition approved in 2015 as E2404-15. DOI: 10.1520/E2404-15A.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from Canadian Standards Association (CSA), 178 Rexdale Blvd., Toronto, ON Canada M9W 1R3.

<sup>4</sup> Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Gaithersburg, MD 20899-3460.

### 3. Terminology

3.1 *Definitions*—For definitions of terms used in this practice refer to the terminology contained in Terminology E176.

#### 3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *expanded vinyl wall or ceiling covering, n*—a wall or ceiling covering consisting of a woven textile backing, an expanded vinyl base coat layer (which is a homogeneous vinyl layer that contains a blowing agent), and a nonexpanded vinyl skin coat.

3.2.2 *paper wall or ceiling covering, n*—a wall or ceiling covering with a top layer consisting of paper or an alternative cellulosic-based material, but not consisting of a wood product.

3.2.3 *polymeric wall or ceiling covering, n*—a wall or ceiling covering with a top layer consisting of polymeric-based material.

3.2.4 *self-supporting specimen, n*—a specimen that remains in place by its own structural characteristics both before and during the fire test.

3.2.5 *site-fabricated stretch system, n*—a system, fabricated on site and intended for acoustical, tackable or aesthetic purposes, that is comprised of three elements: (a) a frame (constructed of plastic, wood, metal, or other material) used to hold fabric in place, (b) a core material (infill, with the correct properties for the application), and (c) an outside layer, comprised of a textile, fabric or vinyl, that is stretched taut and held in place by tension or mechanical fasteners via the frame.

3.2.6 *textile, n*—originally a woven fabric, now generally applied to (1) staple fibers and filaments suitable for conversion to or use as yarns or for the preparation of nonwoven fabrics, (2) yarns made from natural or manufactured fibers, and (3) fabrics made from fibers as defined in (1) and (2) and from yarns.

3.2.7 *vinyl wall or ceiling covering, n*—a wall or ceiling covering produced by applying a poly(vinyl chloride) (PVC, vinyl) based coating, or laminating a preformed vinyl film, onto a woven or nonwoven fabric substrate or paper.

3.2.8 *wall or ceiling covering, n*—a textile-, paper- or polymeric (including vinyl) based product designed to be attached to a wall or ceiling surface for decorative or acoustical purposes.

3.2.8.1 *Discussion*—Wall or ceiling coverings with ink or topcoat layers added as part of the manufacturing process are included in this definition.

3.2.9 *wall or ceiling covering system, n*—an assembly of a textile wall or ceiling covering, a paper wall or ceiling covering or a polymeric (including vinyl) wall or ceiling covering, adhesive (if used), and substrate (if it is part of the assembly) used as a wall or ceiling treatment for decorative or acoustical purposes.

3.2.9.1 *Discussion*—The wall or ceiling covering material is usually intended to be directly attached to a substrate, via adhesives or mechanical fasteners. In some cases the wall or ceiling covering system will be supported by a frame system some distance away from the wall or ceiling covering material.

3.2.10 *water-resistive barrier, n*—a material behind an exterior wall covering that is intended to resist liquid water that has penetrated behind the exterior covering from further intruding into the exterior wall assembly.

3.2.10.1 *Discussion*—The definition above is the way that the International Code Council building code defines and uses the term.

3.2.11 *water vapor retarder, n*—a material or system that impedes the transmission of water vapor under specified conditions.

3.2.11.1 *Discussion*—The definition above is identical to the definitions of water vapor retarder contained in the terminology standards of ASTM Committees C16 (on Thermal Insulation) and E06 (on Buildings).

### 4. Summary of Practice

4.1 This practice describes procedures for specimen preparation and mounting when testing textile, paper, vinyl, expanded vinyl, or other polymeric wall or ceiling coverings to assess flame spread and smoke development as surface burning characteristics using Test Method E84.

4.2 This practice also describes procedures for specimen preparation and mounting for facings or wood veneers intended to be applied on site over a wood substrate and for water-resistive barriers.

### 5. Significance and Use

5.1 Textile, paper, vinyl, expanded vinyl or other polymeric wall or ceiling coverings and wall or ceiling covering systems used as interior finish are often evaluated with Test Method E84 to comply with building or life safety code requirements. This practice describes specimen preparation and mounting procedures for such materials and systems.

5.2 This practice also describes specimen preparation and mounting procedures for other systems that are evaluated with Test Method E84 to comply with building or life safety code requirements. Such systems are facings or wood veneers intended to be applied on site over a wood substrate and water-resistive barriers.

5.3 This practice is not applicable to the following materials:

5.3.1 Foam plastic materials used as water-resistive barriers.

5.3.2 Water vapor retarders installed over thermal insulation.

### 6. Conditioning

6.1 The test specimens shall be conditioned as described in the section on specimen conditioning in Test Method E84.

### 7. Test Specimens

7.1 The test specimen sizes shall comply with those described in the test specimen section of Test Method E84. The test specimens shall be butted against the vent end of the fire test chamber and shall consist of a continuous, unbroken length, or of sections joined end-to-end. The test specimens shall have a width of 20 to 24 in. (510 to 610 mm), a length of