
**Pulps — Preparation of laboratory sheets
for the measurement of diffuse blue
reflectance factor (ISO brightness)**

*Pâtes — Préparation des feuilles de laboratoire pour le mesurage du
facteur de réflectance dans le bleu (degré de blancheur ISO)*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 3688:1999

<https://standards.iteh.ai/catalog/standards/iso/ba5ec609-3142-4e63-a5db-ae61111c0daa/iso-3688-1999>



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3688 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test Methods and quality specifications for pulp*.

This second edition cancels and replaces the first edition (ISO 3688:1977), of which it constitutes a technical revision.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

ISO 3688:1999

<https://standards.iteh.ai/catalog/standards/iso/ba5ec609-3142-4e63-a5db-ae61111c0daa/iso-3688-1999>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Introduction

The reflectance factor depends on the manner of preparation of the laboratory sheets and also on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 3688:1999](https://standards.iteh.ai/catalog/standards/iso/ba5ec609-3142-4e63-a5db-ac61111c0daa/iso-3688-1999)

<https://standards.iteh.ai/catalog/standards/iso/ba5ec609-3142-4e63-a5db-ac61111c0daa/iso-3688-1999>

Pulps — Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness)

1 Scope

This International Standard specifies two procedures for the preparation of laboratory sheets prior to measuring the diffuse blue reflectance factor (ISO brightness). One is the traditional procedure based on preparation of sheets in a Büchner funnel using a filter paper or a wire screen. In the other procedure, the sheets are prepared in a standard sheet former (conventional or Rapid Köthen).

Details of the subsequent measurement procedure are given in ISO 2470.

It is applicable to all wood pulps and to most other types of pulp. Pulps with very long fibres, such as those made from unshortened cotton, flax and similar materials, shall be reduced to a suitable fibre length before testing by this method.

This International Standard shall be used in conjunction with ISO 2469 and ISO 2470.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 2469:1994, *Paper, board and pulps — Measurement of diffuse reflectance factor*.

ISO 2470:—¹⁾, *Paper and board — Measurement of diffuse blue reflectance factor (ISO brightness)*.

ISO 5263:1995, *Pulps — Laboratory wet disintegration*.

ISO 5269-1:1998, *Pulps — Preparation of laboratory sheets for physical testing — Part 1: Conventional sheet-former method*.

ISO 5269-2:1998, *Preparation of laboratory sheets for physical testing — Part 2: Rapid-Köthen method*.

3 Reagents

During the sheet preparation, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity, free from colouring matter and from iron and copper ions.

NOTE Distilled water is used to ensure that the brightness of the sample is not affected by the water.

1) To be published. (Revision of ISO 2470:1977)

3.1 Sodium hydroxide, (NaOH), approximately 0,1 mol/l solution, containing 4,0 g of sodium hydroxide per litre.

3.2 Sulfuric acid, (H₂SO₄), approximately 0,05 mol/l solution, containing 2,8 ml of sulfuric acid (ρ 1,84 g/ml) per litre, or **acetic acid**, w (CH₃COOH) = 10 % containing 95 ml of acetic acid (ρ 1,05 g/ml) per litre.

3.3 Retention aid to be used for recycled and non-wood pulps.

Recycled and non-wood pulps may contain very small particles or fibres, with a colour deviating from the colour of the long fibres. They may affect the brightness value, but they will not be retained by a wire screen. If the brightness value of a pulp including these particles or fibres is to be measured, a retention aid shall be added prior to sheet forming. For example, an addition of 0,4 % of polyacrylamide to the recycled pulp sample has proved effective. The use, kind and amount of retention aid shall be stated in the test report.

4 Apparatus and auxiliary materials

All equipment with which the pulp comes into contact shall be of non-corrosive material, for example glass, porcelain, plastics and chromium-plated or stainless steel. Iron, copper, brass and bronze particularly shall not be used, since iron and copper ions have a strong tendency to cause colour reversion in pulp.

Ordinary laboratory apparatus and the following.

4.1 Standard disintegrator, as specified in ISO 5263.

4.2 For sheet-making in a funnel

4.2.1 Büchner funnel or similar of non-corrodible material, the perforated bottom of which shall be flat, and having an internal diameter of 115 mm to 150 mm and a volume of 1 000 ml to 1 500 ml. The funnel is connected to a vacuum pump.

4.2.2 Filter paper, medium hard, fast filtering with a diameter of 110 mm to 150 mm to fit the funnel, and free from fluorescent materials and soluble impurities. Alternatively a **wire screen**, as specified in ISO 5269, can be used. The wire screen eliminates the difficulties in separating the sheet from a filter paper, a situation encountered when testing certain kinds of short-fibre pulp. However, there is a risk of losing some fine material, when using a wire screen. For most kinds of pulp, the brightness value is unchanged regardless of the filtering device, but for some kinds of mechanical or recycled pulp, the difference may be significant. Therefore, it is important that the apparatus and the filtering device used for the production of the sheets be reported.

NOTE When sheets are formed on a filter paper, fine material may stick to the filter paper and may lead to uneven brightness of the sheet. In this case, the wire screen may be preferable.

4.2.3 Blotters, suitable for interleaving and for absorbing water pressed from the test sheets, grammage approximately 250 g/m², and free from fluorescent materials and soluble impurities.

4.2.4 Pressing plates made from chromium-plated metal, stainless steel or rigid plastic [for example of poly(methyl methacrylate)] of the same size as the laboratory sheets.

4.2.5 Hydraulic disk-press.

4.3 For sheet making in sheet former

4.3.1 Sheet former and auxiliary material, for example, as described in the relevant part of ISO 5269. The material of the sheet former shall be such as not to influence the brightness of pulp.

4.3.2 Device for restricted drying of the laboratory sheets, either by clamping them between drying frames or by keeping them in place on a slightly convex plate by means of a cloth. A number of such frames or plates may be mounted in a cabinet.