



Designation: F 1001 – 99a

## Standard Guide for Selection of Chemicals to Evaluate Protective Clothing Materials<sup>1</sup>

This standard is issued under the fixed designation F 1001; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

Workers involved in the production, use, and transportation of chemicals can be exposed to numerous compounds capable of causing harm upon contact with the human body. The deleterious effects of these chemicals can range from acute trauma, such as dermatitis or burns, to chronic degenerative disease, such as cancer or pulmonary fibrosis. Because engineering controls may not eliminate all possible exposures, attention is often given to reducing the potential for direct skin contact through the use of protective clothing that resists degradation, penetration, and permeation.

Standard test methods are being established to measure degradation, penetration, and permeation chemical resistance of protective clothing materials. Chemical resistance information for a number of chemicals often accompanies many protective clothing articles. However, because there are so many possible protective clothing and chemical combinations, the number and type of chemicals appearing in chemical resistance tables vary extensively.

This guide establishes a standardized list of chemicals to be used in evaluating protective clothing materials. The list of chemicals includes a broad range of representative chemical classes and properties. This guide is intended to provide a minimum set of chemicals in generating test results for protective clothing users and to aid in screening new materials.

### 1. Scope

1.1 The purpose of this guide is to provide a recommended list of both liquid and gaseous chemicals for evaluating protective clothing materials in testing programs.

1.2 Results derived from testing programs using these lists of challenge chemicals are not intended for the definitive characterization of protective clothing materials.

1.3 This list of challenge chemicals is not inclusive of all chemical challenges; the chemicals were chosen to represent broad ranges of liquid and gaseous chemical classes and properties. Not all chemical classes are represented. Other chemicals, especially those of interest to the manufacturer or user, should be tested in addition to those recommended in this guide.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* A specific hazards statement is given in Section 7.

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee F-23 on Protective Clothing and is the direct responsibility of Subcommittee F23.30 on Chemicals.

Current edition approved June 10, 1999. Published August 1999. Originally published as F 1001 – 89. Last previous edition F 1001 – 99.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

F 739 Test Method for Resistance of Protective Clothing Materials to Permeation by Liquids or Gases Under Conditions of Continuous Contact<sup>2</sup>

F 903 Test Method for Resistance of Materials Used In Protective Clothing to Penetration by Liquids<sup>2</sup>

F 1494 Terminology Relating to Protective Clothing<sup>2</sup>

#### 2.2 OSHA Standards:<sup>3</sup>

CFR, Part 1910.1047, Ethylene Oxide

CFR 1910.1051

CFR 1910.1052

#### 2.3 Other Standards:

Compressed Gas Association Publication P-1, Safe Handling of Compressed Gases in Containers<sup>4</sup>

IARC-International Agency for Research on Cancer<sup>5</sup>

### 3. Terminology

#### 3.1 Definitions:

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 11.03.

<sup>3</sup> Available from Occupational Safety and Health Administration, U.S. Department of Labor, 200 Constitution Ave., NW, Washington, DC 20210.

<sup>4</sup> Available from Compressed Gas Assoc., Publications Dept., 1235 Jefferson Davis Hwy., Arlington, VA 22201.

<sup>5</sup> Available from International Agency for Research on Cancer.

3.1.1 *challenge chemical, n*—a chemical used to contact a protective clothing material sample to determine chemical/protective clothing material interactions or compatibility.

3.1.2 *degradation, n*—the deleterious change in one or more properties of a material.

3.1.3 *penetration, n*—in a protective clothing material or item, the process by which a solid, liquid, or gas moves through closures, seams, interstices, and pinholes or other imperfections on a non-molecular level.

3.1.4 *permeation, n*—the process by which a chemical moves through a protective clothing material on a molecular level.

3.1.4.1 *Discussion*—Permeation involves the following: (1) sorption of molecules of the chemical into the contacted (challenge side) surface of a material; (2) diffusion of the sorbed molecules in the material; and (3) desorption of the molecules from the opposite (collection side) surface of the material.

3.1.5 *protective clothing material, n*—any material or combination of materials used in an item of clothing for the purpose of isolating parts of the body from a potential hazard.

3.1.6 *totally encapsulating chemical protective suit, n*—a full body garment that is constructed of protective clothing materials; covers the wearer's torso, head, arms, and legs; may cover the wearer's hands and feet with tightly attached gloves and boots; completely encloses the wearer by itself or in combination with the wearer's respiratory equipment, gloves, and boots.

3.1.7 For definitions of protective clothing terms used in this guide, refer to Terminology F 1494.

#### 4. Summary of Guide

4.1 In this guide, two lists of challenge chemicals are recommended to be used in testing programs to evaluate chemical/protective clothing material interactions or compatibility. One list includes 15 liquid chemicals while the other list includes six gaseous chemicals. Users of this guide may evaluate protective clothing materials against either list or both lists in combination.

4.2 Types of testing programs are not specified. However, when a protective clothing material is tested in accordance with this guide and any appropriate test method, all results and documentation required by the test method should be reported for *each* chemical tested.

#### 5. Significance and Use

5.1 This guide establishes a recommended list of challenge chemicals to encourage those who evaluate chemical protective clothing to test a minimum number of chemicals in common. This list will simplify the comparison of data from different sources.

5.2 This guide may also serve material developers or evaluators in screening candidate protective clothing materials.

5.3 Test methods applicable to the use of this guide include, but are not limited to, Test Methods F 903 and F 739.

5.3.1 The battery of chemical gases shall not be used for testing material penetration resistance because Test Method F 903 has been designed for measuring liquid penetration only.

5.3.2 Evaluation of materials against the gaseous chemical battery is primarily intended for those materials used in the construction of totally-encapsulating protective suits or other clothing items that are designed to prevent exposure to chemical vapors or gases.

#### 6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.<sup>6</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *List of Recommended Liquid Test Chemicals*—Reagents are listed by common name, synonym, and Chemical Abstract Registry Service (CAS) number:

- 6.2.1 *Acetone* (2-propanone),<sup>7</sup> [67-64-1],
- 6.2.2 *Acetonitrile* (cyanomethane), [75-05-8],
- 6.2.3 *Carbon Disulfide*, [75-15-0],
- 6.2.4 *Dichloromethane* (methylene chloride), [75-09-2],
- 6.2.5 *Diethylamine*, [109-89-7],
- 6.2.6 *Dimethylformamide* (DMF), [68-12-2],
- 6.2.7 *Ethyl Acetate*, [141-78-6],
- 6.2.8 *n-Hexane*, [110-54-3],
- 6.2.9 *Methanol* (methyl alcohol, carbinol), [67-56-1],
- 6.2.10 *Nitrobenzene*, [98-95-3],
- 6.2.11 *Sodium Hydroxide* (50 % w/w), [1310-73-2],
- 6.2.12 *Sulfuric Acid* (93.1 % sp gr 1.84, 66° Be'), [7664-93-9],
- 6.2.13 *Tetrachloroethylene* (perchloroethylene), [127-18-4],
- 6.2.14 *Tetrahydrofuran* (THF, 1,4-epoxybutane), [109-99-9], and
- 6.2.15 *Toluene* (toluol), [108-88-3].

6.3 *List of Recommended Gaseous Test Chemicals*—Reagents are listed by common name, minimum purity, synonyms, and Chemical Abstracts Service (CAS) number.

- 6.3.1 *Ammonia*, anhydrous, (99.99 %), [7664-41-7]
- 6.3.2 *1,3-Butadiene*, inhibited, (99.0 %—(bivinyll, vinylethylene, biethylene), [106-99-0]
- 6.3.3 *Chlorine*, 99.5 %, [7782-50-5]
- 6.3.4 *Ethylene Oxide*, (99.7 %), (oxirane, 1,2-epoxyethane), [75-21-8]
- 6.3.5 *Hydrogen Chloride*, (99.0 %), (hydrochloric acid), [7647-01-0]
- 6.3.6 *Methyl Chloride*, (99.5 %), (chloromethane), [74-87-3]

<sup>6</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

<sup>7</sup> Chemical Abstracts Service, Division of American Chemical Society, 2540 Orlentangy River Road, Box 3012, Columbus, OH 43210.