



Designation: **C1685—08 C1685 – 15**

Standard Specification for Pneumatically Applied High-Temperature Fiber Thermal Insulation for Industrial Applications¹

This standard is issued under the fixed designation C1685; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the composition, thermal performance, sound absorption performance, and physical properties of high-temperature fiber thermal insulation for use at temperatures from ambient to 3000°F (1649°C).

1.2 The dry, loose high-temperature fibers shall be pneumatically conveyed to a nozzle chamber where they are mixed with a water-based chemical binder and then conveyed to a nozzle.

1.3 The pneumatically applied, high-temperature fiber insulation is intended for use in industrial applications on flat, or nearly flat, surfaces. It is not intended for use on pipes.

1.4 This specification addresses the use performance of this material in both thermal and acoustical applications.

1.5 This specification does not address the requirements for fire-resistive insulation, but it does not preclude this material's use in that capacity.

1.6 This is a material specification only and is not intended to cover methods of application that are provided by the manufacturer.

1.7 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C71 Terminology Relating to Refractories](#)

[C133 Test Methods for Cold Crushing Strength and Modulus of Rupture of Refractories](#)

[C165 Test Method for Measuring Compressive Properties of Thermal Insulations](#)

[C168 Terminology Relating to Thermal Insulation](#)

[C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus](#)

[C201 Test Method for Thermal Conductivity of Refractories](#)

[C356 Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat](#)

[C390 Practice for Sampling and Acceptance of Thermal Insulation Lots](#)

[C411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation](#)

[C423 Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method](#)

[C447 Practice for Estimating the Maximum Use Temperature of Thermal Insulations](#)

[C665 Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing](#)

[C795 Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel](#)

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved October 1, 2008; June 1, 2015. Published October 2008; July 2015. Last previous edition was approved in 2008 as C1685–08. DOI: 10.1520/C1685-08-10.1520/C1685-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C1045 Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions
- C1104/C1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation
- C1113 Test Method for Thermal Conductivity of Refractories by Hot Wire (Platinum Resistance Thermometer Technique)
- E84 Test Method for Surface Burning Characteristics of Building Materials
- E136 Test Method for Behavior of Materials in a Vertical Tube Furnace at 750°C
- E605 Test Methods for Thickness and Density of Sprayed Fire-Resistive Material (SFRM) Applied to Structural Members
- E2231 Practice for Specimen Preparation and Mounting of Pipe and Duct Insulation Materials to Assess Surface Burning Characteristics

2.2 *Other Standards:*

- ISO 8894 Thermal Conductivity by the Hot Wire Method; Part 1 Crossed Wire Method, Part 2 Parallel Wire Method³
- CAN/ULC-S102-07 Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies⁴

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, see Terminology C71 and C168.

3.2 *Definitions of Terms Specific to This Standard:*

3.3 *cured, n*—state or condition of the finished product after the liquid vehicle has been evaporated to a constant mass.

3.4 *pneumatically applied, v*—use of air to convey the fibrous insulation to a nozzle and then from a nozzle to the intended surface to be insulated.

4. Materials and Manufacture

4.1 *Composition*—The basic types of materials shall be loose inorganic fibers combined with a liquid, water-based binder. The fibers are made from mineral substances such as silica, alumina, calcium, and magnesium processed from the molten state into fibrous form. The liquid binder is made from inorganic materials: water, colloidal silica, and less than 2% of an organic foaming agent.

4.2 *Types*—The product is separated into types based on the chemistry and temperature use limit:

Type	Chemical Composition	Upper Use Temperature, °F (°C)
I	Calcium Magnesium Silicate	2012 (1100)
II	Magnesium Silicate	2300 (1260)
III	Aluminum Silicate	3000 (1649)

4.3 The liquid binder shall be added in sufficient quantity to provide the fibers with necessary adhesion to the applied surface, cohesion to one another, and the required physical properties of the installed, dry insulation.

4.4 There shall be two different grades of material, Grade A and Grade B, differentiated by different thermal conductivity, different sound absorption coefficients, and different noise reduction coefficients.

5. Physical Properties

5.1 For pneumatically applied, high-temperature thermal insulation, it is possible that the properties of density and apparent thermal conductivity will vary with the manufacturer. Minimum acceptable value of density and maximum acceptable values of thermal conductivity shall be stated by the manufacturer before sale and shall be tested in accordance with 9.1. (See Table 1.)

5.2 *Maximum Use Temperature*—When tested in accordance with 9.1, the high-temperature fiber insulation shall not warp, flame, or glow during hot surface exposure. No evidence of melting or fiber degradation shall be evident upon post-test inspection.

5.3 *Maximum Exothermic Temperature Rise*—When tested in accordance with 9.1, the internal temperature shall not at any time exceed the hot surface temperature by more than 200°F (111°C). The 200°F criterion applies during heat-up as well as steady-state conditions. Exceeding this limit constitutes noncompliance to this specification and rejection.

5.4 *Surface Burning Characteristics*—The cured insulation shall have a maximum flame spread index of 25 and a maximum smoke developed of 50 when tested in accordance with 9.4.

5.5 *Non-combustibility*—If required for the particular application, the installed, dry insulation shall meet the requirements of non-combustibility when tested in accordance with 9.5.

5.6 *Linear Shrinkage and Temperature of Use*—The pneumatically applied high-temperature insulation shall be demonstrated to be dimensionally stable with a maximum of 5% linear shrinkage when tested in accordance with Test Method C356 to its maximum use temperature.

³ Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, <http://www.iso.ch>.

⁴ Available from Ottawa Standards and Government Relations Office 440 Laurier Ave. West, Suite 200 Ottawa ON K1R 7X6, <http://www.ulc.ca>.