



Designation: **C363/C363M—09 C363/C363M – 09 (Reapproved 2015)**

Standard Test Method for Node Tensile Strength of Honeycomb Core Materials¹

This standard is issued under the fixed designation C363/C363M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the tensile-node bond strength of honeycomb core materials.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C274 Terminology of Structural Sandwich Constructions](#)

[D883 Terminology Relating to Plastics](#)

[D3878 Terminology for Composite Materials](#)

[D5229/D5229M Test Method for Moisture Absorption Properties and Equilibrium Conditioning of Polymer Matrix Composite Materials](#)

[E4 Practices for Force Verification of Testing Machines](#)

[E6 Terminology Relating to Methods of Mechanical Testing](#)

[E122 Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E456 Terminology Relating to Quality and Statistics](#)

[E1309 Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases](#)

[E1434 Guide for Recording Mechanical Test Data of Fiber-Reinforced Composite Materials in Databases](#)

[E1471 Guide for Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases](#)

3. Terminology

3.1 *Definitions*—Terminology [D3878](#) defines terms relating to high-modulus fibers and their composites. Terminology [C274](#) defines terms relating to structural sandwich constructions. Terminology [D883](#) defines terms relating to plastics. Terminology [E6](#) defines terms relating to mechanical testing. Terminology [E456](#) and Practice [E177](#) define terms relating to statistics. In the event of a conflict between terms, Terminology [D3878](#) shall have precedence over the other Terminologies.

3.2 *Symbols:*

3.2.1 σ —tensile node strength, MPa [psi].

3.2.2 P —ultimate tensile force, N [lb].

3.2.3 b —initial width of specimen, mm [in.].

3.2.4 t —thickness of specimen, mm [in.].

¹ This test method is under the jurisdiction of ASTM Committee [D30](#) on Composite Materials and is the direct responsibility of Subcommittee [D30.09](#) on Sandwich Construction.

Current edition approved April 1, 2009/July 1, 2015. Published May 2009/August 2015. Originally approved in 1955. Last previous edition approved in 2000/2009 as [C363—00-C363—09](#). DOI: [10.1520/C0363—C0363M-09](#); [10.1520/C0363_C0363M-09R15](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- 3.2.5 \bar{x} —sample mean (average).
- 3.2.6 $S_n - 1$ —sample standard deviation.
- 3.2.7 CV —sample coefficient of variation (in percent).
- 3.2.8 n —number of specimens.
- 3.2.9 x_i —measured or derived property.

4. Summary of Test Method

4.1 This test method consists of subjecting a honeycomb construction to a uniaxial tensile force parallel to the plane of the honeycomb. The force is transmitted to the honeycomb through pins, which are placed in cell rows on the top and bottom portions of one specimen.

4.2 The only acceptable failure mode for tensile-node bond strength is the tensile failure of the node-to-node honeycomb bond within the body of the honeycomb specimen. Failure of the honeycomb material at the loading pin location is not a valid failure mode.

5. Significance and Use

5.1 The honeycomb tensile-node bond strength is a fundamental property that can be used in determining whether honeycomb cores can be handled during cutting, machining and forming without the nodes breaking. The tensile-node bond strength is the tensile stress that causes failure of the honeycomb by rupture of the bond between the nodes. It is usually a peeling-type failure.

5.2 This test method provides a standard method of obtaining tensile-node bond strength data for quality control, acceptance specification testing, and research and development.

6. Interferences

6.1 *System Alignment*—Excessive bending will cause premature failure. Every effort should be made to eliminate excess bending from the test system. Bending may occur as a result of misaligned grips, poor specimen preparation, or poor alignment of the loading fixture.

6.2 *Geometry*—Specific geometric factors that affect the tensile-node bond strength include cell geometry, cell size, cell wall thickness and, specimen dimensions (length, width and thickness).

6.3 *Environment*—Results are affected by the environmental conditions under which the tests are conducted. Specimens tested in various environments can exhibit significant differences in both strength behavior and failure mode. Critical environments must be assessed independently.

7. Apparatus

7.1 *Testing Machine*—The testing machine shall be in accordance with Practices E4 and shall satisfy the following requirements:

7.1.1 *Testing Machine Configuration*—The testing machine shall have both an essentially stationary head and a movable head.

7.1.2 *Drive Mechanism*—The testing machine drive mechanism shall be capable of imparting to the movable head a controlled velocity with respect to the stationary head. The velocity of the movable head shall be capable of being regulated in accordance with 11.3.

7.1.3 *Force Indicator*—The testing machine load-sensing device shall be capable of indicating the total force being carried by the test specimen. This device shall be essentially free from inertia lag at the specified rate of testing and shall indicate the force with an accuracy over the force range(s) of interest of within $\pm 1\%$ of the indicated value.

7.2 *Grips*—Refer to Fig. 1 for an example grip configuration.

7.3 *Calipers*—The caliper(s) shall use a flat anvil interface to measure specimen length, width and thickness. The accuracy of the instruments shall be suitable for reading to within 1% of the sample width and thickness. For typical specimen geometries, an instrument with an accuracy of $\pm 25\ \mu\text{m}$ [$\pm 0.001\ \text{in.}$] is desirable for both thickness and width measurements.

8. Sampling and Test Specimens

8.1 *Sampling*—The number of test specimens and the method of their selection depend on the purpose of the particular test under consideration, and no general rule can be given to cover all cases. However, when specimens are to be used for acceptance tests, at least five specimens shall be tested, and these specimens shall be selected from that portion of the material which appears to have a maximum of distorted cells or misalignment of bond areas. For statistically significant data, consult the procedures outlined in Practice E122. Report the method of sampling.

8.2 *Geometry*—The test specimens shall be $130 \pm 5\ \text{mm}$ [$5 \pm 0.2\ \text{in.}$] wide. The test specimens shall have a minimum length of 260 [10 in.] with a minimum test section outside the grips of 200 mm [8 in.]. The standard thickness of the core slice shall be $12 \pm 1\ \text{mm}$ [$0.500 \pm 0.04\ \text{in.}$] for nonmetallic cores and $16 \pm 1\ \text{mm}$ [$0.625 \pm 0.04\ \text{in.}$] for metallic cores. Nonstandard thicknesses



FIG. 1 Honeycomb Core Tensile-Node Bond Strength Test Setup

are within the scope of this test method provided the actual thickness value is reported. Nonstandard thickness specimens shall have uniform thickness within ± 1 mm [± 0.04 in.].

NOTE 1—The standard thickness values listed above are based on historical values for metallic and nonmetallic core thicknesses used for qualification and allowable test programs.

8.3 *Specimen Preparation and Machining*—Specimens shall be cut such that the number of cells along the width is constant along the specimen length. The length being defined as the specimen dimension parallel to the application of the force, Fig. 1. The specimen width shall be parallel to the node bond areas.

8.4 *Labeling*—Label the test specimens so that they will be distinct from each other and traceable back to the panel of origin, and will neither influence the test nor be affected by it.

9. Calibration

9.1 The accuracy of all measuring equipment shall have certified calibrations that are current at the time of the use of the equipment.

10. Conditioning

10.1 The recommended pre-test condition is effective moisture equilibrium at a specific relative humidity as established by Test Method D5229/D5229M; however, if the test requestor does not explicitly specify a pre-test conditioning environment, no conditioning is required and the test specimens may be tested as prepared.

10.2 The pre-test specimen conditioning process, to include specified environmental exposure levels and resulting moisture content, shall be reported with the test data.

NOTE 2—The term “moisture,” as used in Test Method D5229/D5229M, includes not only the vapor of a liquid and its condensate, but the liquid itself in large quantities, as for immersion.

10.3 If no explicit conditioning process is performed, the specimen conditioning process shall be reported as “unconditioned” and the moisture content as “unknown.”