



Designation: **E759 – 92 (Reapproved 2011) E759/E759M – 92 (Reapproved 2015)^{ε1}**

Standard Test Method for Effect of Deflection on Sprayed Fire-Resistive Material Applied to Structural Members¹

This standard is issued under the fixed designation ~~E759~~E759/E759M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

^ε NOTE—Designation was changed to dual and units information was corrected editorially in August 2015.

1. Scope

1.1 This test method covers a procedure for determining the effect of deflection on sprayed fire-resistive material (SFRM) applied to steel deck. These materials include sprayed fibrous and cementitious materials applied directly in contact with the structural members. The test method is applicable only to laboratory procedures.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[E84 Test Method for Surface Burning Characteristics of Building Materials](#)

[E119 Test Methods for Fire Tests of Building Construction and Materials](#)

[E605/E605M Test Methods for Thickness and Density of Sprayed Fire-Resistive Material \(SFRM\) Applied to Structural Members](#)

[ASTM E759/E759M-92\(2015\)^{ε1}](#)

3. Summary of Test Method

3.1 In this test method, a cellular steel deck panel sprayed with fire-resistive material is subjected to bending by a vertical center load while supported horizontally at its ends.

4. Significance and Use

4.1 The intent of this test method is to determine properties of direct-applied SFRM that may be used to provide an indication of serviceability. Satisfactory performance of fire-resistive material applied to structural members and assemblies depends upon its ability while in place to withstand the various influences that may occur during the life of the structure, as well as upon its satisfactory performance under fire tests.

4.2 This test method measures the behavior of SFRM when subjected to deflection and evaluates such phenomena as spalling and delamination under bending stress. It is an indication of the ability of SFRM to remain in place and resist removal during anticipated service conditions.

¹ This test method is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.21 on Serviceability.

Current edition approved April 1, 2011-Aug. 1, 2015. Published May 2011-August 2015. Originally approved in 1980. Last previous edition approved in 2005/2011 as E759 – 92 (2005)/(2011). DOI: 10.1520/E0759-92R11-10.1520/E0759-92R15E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.