



Designation: **E937 – 93 (Reapproved 2011) E937/E937M – 93 (Reapproved 2015)<sup>ε1</sup>**

## Standard Test Method for Corrosion of Steel by Sprayed Fire-Resistive Material (SFRM) Applied to Structural Members<sup>1</sup>

This standard is issued under the fixed designation ~~E937~~E937/E937M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

---

<sup>ε1</sup> NOTE—Designation was changed to dual and units information was corrected editorially in August 2015.

---

### 1. Scope

- 1.1 This test method covers a procedure for measuring the corrosion to steel induced by sprayed fire-resistive material.
- 1.2 These SFRMs include sprayed fibrous and cementitious materials applied directly in contact with the structural members.
- 1.3 This test method is applicable only to laboratory procedures.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as the standard. ~~The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.~~

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[E119 Test Methods for Fire Tests of Building Construction and Materials](#)

[E605/E605M Test Methods for Thickness and Density of Sprayed Fire-Resistive Material \(SFRM\) Applied to Structural Members](#)

[E631 Terminology of Building Constructions](#)

### 3. Terminology

3.1 *Definitions*—Definitions in this test method are in accordance with Terminology [E631](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *corrosion*—chemical reaction between a metal and its environment that produces a deterioration of the metal and its properties.

3.2.2 *sprayed fire-resistive materials*—materials that are sprayed onto substrates to provide fire-resistive protection of the substrates.

### 4. Summary of Test Method

4.1 In this test method replicate panels of bare, shop-coated, and galvanized steel are sprayed with SFRM and subjected to room temperature and humidity conditions and to 240 h of conditioning in a temperature- and humidity-controlled chamber. Corrosion induced under these conditions is determined by weight loss<sup>3</sup> of the sheets as related to sheets not so conditioned.

---

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [E06](#) on Performance of Buildings and is the direct responsibility of Subcommittee [E06.21](#) on Serviceability.

Current edition approved April 1, 2011; August 1, 2015. Published May 2011; August 2015. Originally approved in 1983. Last previous edition approved in 2005/2011 as E937 – 93 (2005) (2011). DOI: 10.1520/E0937-93R11-10.1520/E0937\_E0937M-93R15E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Although “mass” is being determined, the term weight is used in this test method as an accepted substitute.

## 5. Significance and Use

5.1 It is the intent of this test method to determine relative corrosive properties of direct applied SFRM that provides an indication of serviceability. Satisfactory performance of SFRM applied to structural members and assemblies depends upon its ability to withstand the various influences that occur during the life of the structure, as well as upon its satisfactory performance under fire conditions.

5.2 This test method evaluates the relative corrosion of steel induced by SFRM and determines whether the presence of SFRM increases, decreases, or has no effect on the corrosion characteristics of steel.

## 6. Apparatus

6.1 *Standard Temperature Humidity Cabinet*, equipped to maintain the temperature at  $35 \pm 1.7^\circ\text{C}$  ( $95 \pm 3^\circ\text{F}$ ) [ $95 \pm 3^\circ\text{F}$ ] and a relative humidity of  $95 \pm 3\%$ . The cabinet and all accessories shall be of a material that does not affect the corrosiveness of the atmosphere in the cabinet. Additionally, all parts that come into contact with the test specimens shall be made of material that will not cause electrolytic corrosion. Adequate circulation of the atmosphere over the specimens shall be provided.

6.2 *Scale*, having a capacity of 5 kg and a sensitivity of  $\pm 0.1$  g.

6.3 *Wire Brush*, described as “cement mold brush” with brass wire bristles 25 mm ( $1\text{ in.}$ ) [ $1\text{ in.}$ ] long mounted in a handle. The bristle section shall be 127 mm ( $5\text{ in.}$ ) [ $5\text{ in.}$ ] long by 19 mm ( $3/4\text{ in.}$ ) [ $3/4\text{ in.}$ ] wide.

## 7. Materials

7.1 This test method requires the application of SFRM in accordance with manufacturer’s published instructions. The apparatus, materials, and procedures used to apply the SFRM shall be representative of application in the field.

7.2 The density of the prepared sample shall be the same as the density tested and reported during the Test Methods E119 fire exposures or as required by the sponsor of the test.

7.3 Determine the density and thickness of each laboratory-prepared specimen. Report in accordance with Test Methods E605/E605M.

7.4 Steel sheets shall be 200 mm by 200 mm ( $8\text{ in.}$  [ $8\text{ in.}$ ] by  $8\text{ in.}$  [ $8\text{ in.}$ ]) by minimum 12 gage and shall be: bare steel—A36 grade, galvanized steel—G60 grade, and shop-coated—A36 grade steel coated with iron oxide alkyd shop coat primer.

## 8. Laboratory Test Specimens

8.1 The three sets of specimens shall consist of four sheets each, in the following categories: bare, shop-coated, and galvanized steel.

8.2 The steel sheets shall be free of all surface rust. Wash the metal specimens with analytical grade trichlorethylene to remove any oil or grease. Dry at room temperature. For test purposes of this test method, the duplicate sets of steel sheets are referred to as follows:

Bare	I, II, III, IV
Shop-coated	I, II, III, IV
Galvanized	I, II, III, IV

## 9. Procedure

9.1 Weigh each sheet to the nearest 0.1 g and record the weighed samples as Ia, IIa, IIIa, and IVa for the bare, shop-coated, and galvanized sets, respectively. See Table 1.

**TABLE 1 Sample Weights**

	Bare	Shot-Coated	Galvanized
I = Specimens having SFRM, conditioned at room temperature (9.4).	Ia = g/mm <sup>2</sup> Ib = g/mm <sup>2</sup>	Ia = g/mm <sup>2</sup> Ib = g/mm <sup>2</sup>	Ia = g/mm <sup>2</sup> Ib = g/mm <sup>2</sup>
II = Specimens having SFRM, conditioned for 240 h at 35 ± 1.7°C (9.5).	IIa = g/mm <sup>2</sup> IIb = g/mm <sup>2</sup>	IIa = g/mm <sup>2</sup> IIb = g/mm <sup>2</sup>	IIa = g/mm <sup>2</sup> IIb = g/mm <sup>2</sup>
III = Specimens having SFRM, conditioned at room temperature (9.4).	IIIa = g/mm <sup>2</sup> IIIb = g/mm <sup>2</sup>	IIIa = g/mm <sup>2</sup> IIIb = g/mm <sup>2</sup>	IIIa = g/mm <sup>2</sup> IIIb = g/mm <sup>2</sup>
IV = Specimens having SFRM, conditioned for 240 h at 35 ± 1.7°C (9.5).	IVa = g/mm <sup>2</sup> IVb = g/mm <sup>2</sup>	IVa = g/mm <sup>2</sup> IVb = g/mm <sup>2</sup>	IVa = g/mm <sup>2</sup> IVb = g/mm <sup>2</sup>