



Designation: **D4800 – 94 (Reapproved 2011)** **D4800 – 94 (Reapproved 2015)**

Standard Guide for Classifying and Specifying Adhesives¹

This standard is issued under the fixed designation D4800; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide provides a classification system for tabulating the properties of adhesives suitable for holding parts or assemblies together. The use of this guide also provides information necessary for the development of standard specifications for adhesives.

NOTE 1—This classification system may serve many of the needs of industries using adhesives. This guide is subject to revision as the need requires; therefore, the latest revision should always be used.

1.2 *Limitations*—This classification system is intended to be a means of identifying adhesives. It is not intended for the selection of materials. Material selection should be made by those having expertise in the adhesives field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the attachment process to be employed, the inherent properties of the material not covered in this document, and the economic factors.

1.3 This classification system is based on the premise that adhesives can be arranged into broad generic families using basic properties to arrange the materials into groups, classes, and grades.

1.4 In all cases where the provisions of this classification system would conflict with the referenced ASTM specification for a particular material, the latter shall take precedence.

1.5 The values stated in SI units, as detailed in **IEEE/ASTM SI 10**, are to be regarded as the standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

D907 Terminology of Adhesives

D1084 Test Methods for Viscosity of Adhesives

D1298 Test Method for Density, Relative Density, or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method

D1310 Test Method for Flash Point and Fire Point of Liquids by Tag Open-Cup Apparatus

D2240 Test Method for Rubber Property—Durometer Hardness

D2583 Test Method for Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor

D2834 Test Method for Nonvolatile Matter (Total Solids) in Water-Emulsion Floor Polishes, Solvent-Based Floor Polishes, and Polymer-Emulsion Floor Polishes

D3278 Test Methods for Flash Point of Liquids by Small Scale Closed-Cup Apparatus

D4562 Test Method for Shear Strength of Adhesives Using Pin-and-Collar Specimen

D5363 Specification for Anaerobic Single-Component Adhesives (AN)

IEEE/ASTM SI 10 Standard for Use of the International System of Units (SI): The Modern Metric System

2.2 *Military Standards*:

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes³

MIL-A-46146 Adhesive, Silicone, RTV, Noncorrosive (for Use with Sensitive Metals and Equipment)³

3. Terminology

3.1 The terms used in this guide are in accordance with Terminology **D907**.

¹ This guide is under the jurisdiction of ASTM Committee **D14** on Adhesives and is the direct responsibility of Subcommittee **D14.60** on Adhesive Material Classification System.

Current edition approved Dec. 1, 2011; Sept. 1, 2015. Published December 2011; September 2015. Originally approved in 1987. Last previous edition approved in 2005 (2011). DOI: 10.1520/D4800-94R11.10.1520/D4800-94R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the [standard's](http://www.astm.org) Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

4. Significance and Use

4.1 The purpose of this classification system is to provide a method of identifying adhesives in order to give industry a system that can be used universally for materials. It further provides a means for specifying these materials by the use of the standards that are developed using this guide.

4.2 This classification system was developed to permit the addition of future adhesives.

5. Classification

5.1 **Fig. 1** summarizes the classification system as detailed in this guide.

5.2 Adhesives shall be classified on the basis of their broad generic family. The generic family is identified by letter designations as found in **Table 1**.

NOTE 2—For example: CA = Cyanoacrylate.

5.2.1 The generic family is based on the broad chemical makeup of the base materials. By its designation, certain inherent properties are specified.

5.3 The generic family is classified into groups according, in general, to the chemical composition. These groups are further subdivided into classes and grades, as shown in the basic property table that applies. The letter designation applicable is followed by a four-digit number indicating group, class, and grade.

5.3.1 The basic property tables have been developed to identify the commercially available adhesives into groups, classes, and grades. These tables are found in the standards listed in **Table 1**.

5.3.1.1 Where a standard does not exist for this classification system the letter designation for the generic family will be followed by four 0's and the use of the suffixes as needed (see **7.1**).

NOTE 3—Example: SI0000 indicates a Silicone (SI) from **Table 1**, with 0000 indicating no basic property table.


5.4 To facilitate the identification of new or special materials where basic property tables are not provided in a material specification, cell tables will be used. These tables shall appear in the material specifications. (See example of cell table in **Fig. 2**.)

5.4.1 Although the values listed in the cell tables include the range of properties available in existing materials, users should not infer that every possible combination of properties exists or can be obtained.

5.4.2 The requirements for special adhesives will use the classification system, as described, by the addition of a single letter that indicates the proper cell table in which the properties are listed. A specific value is designated by the cell number for each property in the order in which they are listed in the table. When a property is not to be specified, a zero is entered as the cell number. Likewise, when an acceptable value is not available in the cell table, the number 9 should be used and a suffix used indicating the specific value (see **7.1**). Thus, the letter designation “A” for cell table and 3400 for property values shall always be written A3400.

NOTE 4—An example of an anaerobic adhesive identified by this classification system is as follows. The designation AN0120A3400 indicates the following with the material requirements from Cell Table A of material specification.

AN0120	=	Anaerobic–Newtonian flow, thread locking
A	=	Table A for property requirements
3	=	Strength ASTM Test Method D4562 , 6 MPa min
4	=	Viscosity ASTM Test Methods D1084 , Method B, 900 MPa·s min
0	=	Unspecified
0	=	Unspecified



NOTE 1—

- 1 = Two or more letters identify the generic family based on abbreviations from **Table 1**.
- 2 = Four digits identify the specific type. The first two digits identify the group. The next digit identifies the class and the last digit identifies the grade. A basic property table will provide property values for the specific material (see **5.2**).
- 3 = One letter refers to a cell table listing of physical specifications and test methods.
- 4 = Four digits refer to the specific physical parameters listed in the cell table.
- 5 = Suffix codes indicate special requirements based on the application and identify special tests (two letters with three digits).

FIG. 1 Classification System