



Designation: ~~D2851–98~~ (Reapproved 2015) D2851 – 15

Standard Specification for Liquid Optical Adhesive¹

This standard is issued under the fixed designation D2851; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers liquid optical adhesive for use in bonding glass to glass or other transparent adherends.

1.2 The values stated in SI units are to be regarded as standard. The values given in parentheses are provided for information purposes only.

1.3 The following precautionary caveat pertains only to the test method portion, Section 6, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in 6.1.1.

2. Referenced Documents

2.1 *ASTM Standards*:²

[D542 Test Method for Index of Refraction of Transparent Organic Plastics](#)

[D897 Test Method for Tensile Properties of Adhesive Bonds](#)

[D904 Practice for Exposure of Adhesive Specimens to Artificial Light](#)

[D907 Terminology of Adhesives](#)

[D1084 Test Methods for Viscosity of Adhesives](#)

[E308 Practice for Computing the Colors of Objects by Using the CIE System](#)

[E1953 Practice for Description of Thermal Analysis and Rheology Apparatus](#)

3. Terminology

3.1 *Definitions*—Many terms in this specification are defined in Terminology [D907](#).

4. Significance and Use

4.1 The bond strength tests provide reasonably accurate information with regard to the bond strength of the adhesives. Bond strength data may be suitable for specification acceptance, service evaluation, manufacturing control, research, and development. Bond strength tests are not considered significant for applications differing widely from the test in rate and type of loading.

5. General Requirements

5.1 The adhesive shall be in liquid form and free of solvent in order to avoid bubble formation in the adhesive layer. Each component shall be completely reactive (without residual volatile products). The adhesive may be heat-, catalyst-, or radiation-cured.

5.1.1 *Volatility*—Volatile content of the adhesive shall not exceed 0.5 %, unless otherwise agreed upon between the manufacturer and the purchaser.

5.1.2 *Viscosity*—The viscosity of the adhesive shall be within a well-defined range as agreed upon between the manufacturer and the purchaser.

5.1.3 *Color*—The color of the adhesive shall not exceed the color of a platinum-cobalt standard solution No. 300.

¹ This specification is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.60 on Adhesive Material Classification System.

Current edition approved April 1, 2015/Sept. 1, 2015. Published April 2015/September 2015. Originally approved in 1970. Last previous edition approved in 2009/2015 as D2851 – 98 (2009) (2015). DOI: 10.1520/D2851-98R15-10.1520/D2851-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5.1.4 *Cleanliness*—The number and size of foreign particles found in 100 mL of the adhesive shall not exceed 5 particles in the size range from 10 to 100 μm (0.1 mm), and none larger than 100 μm . The number and size of foreign particles in the catalyst required to cure 100 mL of the adhesive shall not exceed 2 particles in the size range from 10 to 100 μm , and none larger than 100 μm .

5.1.5 *Refractive Index*—The refractive index of the cured adhesive shall be within a well-defined range as agreed upon between the manufacturer and the purchaser.

5.1.6 *Stability*—The liquid adhesive shall not change in viscosity by greater than 20 % of its original viscosity nor show any formation of solids, when tested as described in 6.6.

5.1.7 *Light Transmission*—Visible light transmission through a bonded glass doublet (two glass disks bonded as described in 6.8) shall not be less than 98.5 % of the total light transmitted through a single glass disk. There shall be no change in light transmission of a glass doublet after the environmental test (see 6.9).

5.1.8 *Environmental Test*—Separation within the adhesive layer or from either glass surface of the glass doublet shall not exceed 1.0 mm in depth nor extend beyond 180° of the periphery of the adhesive layer (see 6.9).

5.1.9 *Bond Strength*—The tensile strength of a bonded glass doublet after being subjected to the environmental test (see 6.9) shall be greater than 200 psi (1.38 MPa) or any value agreed upon between the manufacturer and the purchaser.

6. Test Methods

6.1 Volatility:

6.1.1 Thoroughly clean three petri dish bottoms, 95-mm outside diameter, by washing with detergent and a scrub brush. Rinse with warm running tap water. Place petri dishes in an air-circulating oven for 30 min at $65 \pm 2^\circ\text{C}$ ($150 \pm 4^\circ\text{F}$). Raise temperature to $110 \pm 2^\circ\text{C}$ ($230 \pm 4^\circ\text{F}$) for 1 h. Remove petri dishes from oven and place in a desiccator. After petri dishes have cooled to room temperature, approximately 2 h, weigh each dish to the nearest 0.1 mg. (**Warning**—In addition to other precautions, do not handle petri dishes with bare hands. Use tongs.)

6.1.2 Replace each petri dish in the oven at $110 \pm 2^\circ\text{C}$ ($230 \pm 4^\circ\text{F}$) for 1 h. Repeat cool-down procedure. Reweigh each petri dish to the nearest 0.1 mg. If weight agrees to within ± 0.2 mg of initial weight, proceed to 6.1.3. If weight exceeds this ± 0.2 -mg range, repeat process until a constant weight for each petri dish is obtained.

6.1.3 To each petri dish add approximately 10 g of adhesive, and mix with catalyst or any component part required for curing. Weigh each dish to the nearest 0.1 mg. Cure the adhesive by following the procedure described by the manufacturer. Then place each sample in an oven at $105 \pm 2^\circ\text{C}$ ($220 \pm 4^\circ\text{F}$) to a constant weight (same procedure as in 5.1.1 but at 105°C). Reweigh each sample to the nearest 0.1 mg and calculate the percent volatile matter as follows.

$$\text{Volatile matter, \%} = [(A - B)/A] \times 100 \quad (1)$$

where:

A = weight of original sample, and

B = weight of cured adhesive taken to constant weight.

6.2 *Viscosity*—Measure the viscosity of the adhesive in accordance with Test Methods **D1084**—(Brookfield, (Rotational Viscometer, Method B, or anysee Practice **E1953**other suitable viscometer may be used.))

6.3 *Color*—Determine the color of the adhesive by comparing it with platinum-cobalt (Pt-Co) standards. Place 100 mL of adhesive in a 100-mL Nessler tube. Make color observations by placing the adhesive-filled Nessler tube vertically over a sheet of white paper while looking down and through the filled tube. Compare the color observed with a standard Nessler tube, containing 100 mL of the Pt-Co standard held in the same manner.

6.3.1 Prepare the Pt-Co standard solutions by dissolving 1.246 g of potassium platonic chloride and 1000 g of cp crystalline cobaltous chloride hexahydrate in a solution of 300 mL of distilled water and 100 mL of concentrated hydrochloric acid. Dilute to 1000 mL in a volumetric flask using distilled water. This shall be the concentrated stock solution that has a Pt-Co number of 500. Dilute the concentrated stock solution with distilled water as shown below to obtain the desired Pt-Co standard.