



Designation: A1018/A1018M – 15

Standard Specification for Steel, Sheet and Strip, Heavy-Thickness Coils, Hot-Rolled, Carbon, Commercial, Drawing, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength¹

This standard is issued under the fixed designation A1018/A1018M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers hot-rolled, heavy-thickness coils beyond the size limits of Specification [A1011/A1011M](#).

1.2 The product is available in six designations: Commercial Steel, Drawing Steel, Structural Steel, High-Strength Low-Alloy Steel, High-Strength Low-Alloy Steel with Improved Formability, and Ultra-High Strength Steel.

1.3 This material is available only in coils described as follows:

Product	Size Limits, Coils Only	
	Width, in. [mm]	Thickness, in. [mm]
Strip	Over 8 to 12, incl [Over 200 to 300]	0.230 to 1.000, incl [From 6.0 through 25]
Sheet	Over 12 [Over 300]	0.230 to 1.000, incl [From 6.0 through 25]

NOTE 1—The changes in width limits with the publication of [A635/A635M](#) – 06a result in a change in tensile testing direction for material from 0.180 in. [4.5 mm] to 0.230 in. exclusive [6.0 mm exclusive] over 48 in. [1200 mm] wide as that material is now covered by Specification [A568/A568M](#) – 06a. The purchaser is advised to discuss this change with

the supplier.

1.4 Sheet and strip in coils of sizes noted in 1.3 are covered by this specification only with the following provisions:

1.4.1 The material is to be fed directly from coils into a blanking press, drawing or forming operation, tube mill, rolling mill, or sheared or slit into blanks for subsequent drawing or forming.

1.4.2 The material is not to be converted into steel plates for structural or pressure vessel use unless tested in complete accordance with the appropriate sections of Specifications [A6/A6M](#) (plates provided from coils) or [A20/A20M](#) (plates

produced from coils). Plate converted from coils is no longer governed by this sheet steel specification and since this material is now a plate, the requirements of the appropriate plate specification shall apply, except in cases where there is a conflict between the requirements of the plate specification and this specification. In these cases, the more restrictive limits of either specification shall apply.

1.4.3 The dimensional tolerances of Specification [A635/A635M](#) are applicable to material produced to this specification.

1.4.4 Not all strength levels are available in all thicknesses. The user should consult the producer for appropriate size limitations.

1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

- [A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling](#)
- [A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels](#)
- [A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)
- [A568/A568M Specification for Steel, Sheet, Carbon, Structural, and High-Strength, Low-Alloy, Hot-Rolled and Cold-Rolled, General Requirements for](#)
- [A572/A572M Specification for High-Strength Low-Alloy Columbium-Vanadium Structural Steel](#)

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.19](#) on Steel Sheet and Strip.

Current edition approved Sept. 1, 2015. Published September 2015. Originally approved in 2001. Last previous edition approved in 2010 as A1018/A1018M – 10. DOI: 10.1520/A1018_A1018M-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- [A635/A635M Specification for Steel, Sheet and Strip, Heavy-Thickness Coils, Hot-Rolled, Alloy, Carbon, Structural, High-Strength Low-Alloy, and High-Strength Low-Alloy with Improved Formability, General Requirements for](#)
- [A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)
- [A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys](#)
- [A1011/A1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength](#)
- [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)
- [G101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels](#)

resistance of these steels is equivalent to plain carbon steels. With copper specified, the atmospheric corrosion is somewhat enhanced.

5.1.5 *High-Strength Low-Alloy Steel with Improved Formability*—(HSLAS-F Grades 50[340], 60[410], 70[480], 80[550]).

5.1.5.1 This material has improved formability when compared with HSLAS. The steel is killed and made to a fine ferritic grain practice and includes microalloying elements such as columbium, titanium, vanadium, zirconium, and so forth. The steel shall be treated to achieve inclusion control. The material is intended for miscellaneous applications where higher strength, savings in weight, improved formability, and weldability are important. Atmospheric corrosion resistance of these steels is equivalent to plain carbon steels. With copper specified, the atmospheric corrosion resistance is somewhat enhanced.

NOTE 2—For methods of establishing the atmospheric corrosion resistance of low-alloy steels, see Guide [G101](#).

5.1.6 *Ultra-High Strength Steel*—(UHSS Grades 90 [620] and 100 [690], Types 1 and 2).

5.1.6.1 This material has increased strength compared with HSLAS-F. The steel is killed and made to a fine ferritic grain practice, and includes microalloying elements such as columbium (niobium), titanium, vanadium, molybdenum, and so forth. The steel shall be treated to achieve inclusion control. The material is intended for miscellaneous applications where higher strength, savings in weight, and weldability are important. Atmospheric corrosion resistance of these steels is equivalent to plain carbon steels. With copper specified, the atmospheric corrosion resistance is somewhat enhanced.

5.1.7 When required for HSLAS, HSLAS-F, and UHSS steels, limitations on the use of one or more of the microalloy elements shall be specified on the order.

5.2 The limits for copper, chromium, nickel, and molybdenum are available in two levels, Limits A and Limits B (see [Table 1](#)).

6. Ordering Information

6.1 Orders for material under this specification shall include the following information, as required, to describe adequately the desired material.

- 6.1.1 ASTM specification number and year of issue.
- 6.1.2 Name of material and designation (hot-rolled steel sheet or hot-rolled strip) (include grade and, as appropriate, type and class for CS, DS, SS, HSLAS, HSLAS-F, and UHSS) (see [5.1](#)).
 - 6.1.2.1 For CS and DS, when a type is not specified, Type B will be furnished.
 - 6.1.2.2 For SS Grade 36, when a type is not specified, Type 1 will be furnished (see [5.1](#)).
 - 6.1.2.3 For UHSS, when a type is not specified, Type 1 shall be furnished.
 - 6.1.2.4 For HSLAS, when a class is not specified, Class 1 will be furnished (see [5.1](#)).
- 6.1.3 Copper bearing, (if required),
- 6.1.4 For SS, HSLAS, and HSLAS-F and selected CS steels, specify the limits for chemical requirements listed in

3. Terminology

3.1 *Definitions*—For definitions of other terms used in this specification refer to Terminology [A941](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *inclusion control, n*—the process of reducing the volume fraction of inclusions or modifying the shape of inclusions to improve formability, weldability, and machinability.

3.2.1.1 *Discussion*—Inclusions, especially those elongated during the rolling process, create the conditions for initiating or propagating cracks, or both, when the material is stretched or bent during the manufacture of a part. The adverse effects of inclusions are minimized by reducing the content of inclusions in the steel, or by altering the shape of inclusions through the use of additions during the steelmaking process that change the elongated shape of the inclusions to less harmful small, well dispersed globular inclusions, or both.

4. General Requirements for Delivery

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification [A635/A635M](#), unless otherwise provided herein.

5. Classification

5.1 Heavy thickness coils are available in the following designations:

- 5.1.1 *Commercial Steel (CS Types A and B, and Standard Steel Designations)*
- 5.1.2 *Drawing Steel (DS Types A and B, and Standard Steel Designations)*
- 5.1.3 *Structural Steel*—(SS Grades 30[205], 33[230], 36[250] Types 1 and 2, 40[275] and 45[310]).
- 5.1.4 *High-Strength Low-Alloy Steel*—(HSLAS Grades 45[310], 50[340], 55[380], 60[410], 65[450], 70[480]) in Classes 1 and 2.

5.1.4.1 This material is intended for miscellaneous applications where greater strength and savings in weight are important. The material is available in two classes. They are similar in strength level, except that Class 2 offers improved weldability and more formability than Class 1. Atmospheric corrosion

TABLE 1 Chemical Requirements: Cu, Ni, Cr and Mo for Commercial Steels, Structural Steels, High-Strength Low-Alloy Steels, and High-Strength Low-Alloy Steels with Improved Formability

Designation	Limits	% Heat Analysis, Element Maximum Unless Otherwise Shown			
		Cu ^{A,B}	Ni ^B	Cr ^{B,C}	Mo ^{B,C}
CS:	A	0.20	0.20	0.15	0.06
Grades 1015, 1016, 1017, 1018, 1019, 1020, 1021, 1022, 1023, 1524	B	0.40	0.40	0.30	0.12
SS:	A	0.20	0.20	0.15	0.06
All grades	B	0.40	0.40	0.30	0.12
HSLAS:	A	0.20	0.20	0.15	0.06
All grades and classes except for Grade 70 [480]	B	0.40	0.40	0.30	0.12
Grade 70 [480] Class 1 and Class 2	A	0.20	0.20	0.15	0.16
	B	0.40	0.40	0.30	0.16
HSLAS-F:	A	0.20	0.20	0.15	0.06
Grades 50 [340] and 60 [410]	B	0.40	0.40	0.30	0.12
Grade 70 [480] and 80 [550]	A	0.20	0.20	0.15	0.16
	B	0.40	0.40	0.30	0.16

^A When copper bearing steel is specified, the minimum limit for copper is 0.20 %. When copper bearing steel is not specified, the maximum limit for copper is as shown in the table.

^B For Limits B steels, the sum of copper, nickel, chromium and molybdenum shall not exceed 1.00 % on heat analysis. When one or more of these elements are specified by the purchaser, the sum does not apply; in which case, only the individual limits on the remaining elements shall apply.

^C For Limits B steels, the sum of chromium and molybdenum shall not exceed 0.32 % on heat analysis. When one or more of these elements are specified, the sum does not apply; in which case, only the individual limits on the remaining elements shall apply.

(<https://standards.iteh.ai>)

Table 1 (elements Cu, Cr, Ni, and Mo). When Limits A or Limits B is not specified, Limits A shall be furnished.

6.1.5 *Condition*—Material in accordance with this specification is furnished in the hot rolled condition. Pickled (or blast cleaned) must be specified if required. Material ordered as pickled (or blast cleaned) will be oiled unless ordered dry,

6.1.6 Type of edge must be specified for hot rolled sheet coils and strip coils, either mill edge or cut edge (sheet), mill edge or slit edge (strip),

6.1.7 Dimensions (decimal thickness and width of material),

NOTE 3—Not all producers are capable of meeting all the limitations of the thickness tolerance tables in Specification **A635/A635M**. The purchaser should contact the producer regarding possible limitations prior to placing an order.

6.1.8 Coils size and weight requirements (must include inside diameter (ID), outside diameter (OD), and maximum weight),

6.1.9 Quantity (weight),

6.1.10 Application (part identification and description). Orders for conversion to plate shall include reference to the applicable ASTM plate specification.

6.1.11 A report is required of heat analysis and mechanical properties as determined by the tension test, and

6.1.12 Special requirements (if any).

6.1.12.1 When the purchaser requires a limit on “carbon equivalent” (see Supplementary Requirement S1), this requirement shall be specified in the purchase order or contract.

6.1.12.2 When the purchaser requires thickness tolerances for 3/8 in. [10 mm] minimum edge distance (see Supplementary

Requirement in Specification **A635/A635M**), this requirement shall be specified in the purchase order or contract.

NOTE 4—A typical ordering description is as follows: (inch pound units) ASTM A1018/A1018M: Grade 50, High-Strength, Low-Alloy Steel, Class 2, Limits B, hot rolled sheet coils, pickled and oiled, cut edge, 0.500 by 40 in. by coil; ID 24 in., OD 72 in., maximum; coil weight 40 000 lb., maximum; 200 000 lb. for roll forming shapes; (SI units) ASTM A1018/A1018M: Grade 340, High-Strength Low-Alloy Steel, Class 2, Limits B, hot-rolled sheet coils, pickled and oiled, cut edge; 10 by 900 mm by coil; ID 600 mm, OD 1800 mm, maximum; coil weight 18 000 kg maximum; 90 000 kg for roll forming shapes. For conversion to plate: (inch-pound units) ASTM A1018/A1018M: Grade 50, High-Strength Low-Alloy Steel, Class 1, Limits A, hot-rolled sheet coils, as rolled, mill edge, 0.500 by 50 in. by coil, ID 24 in., OD 72 in., maximum; coil weight 40 000 lb., maximum; 200 000 lb. for conversion to plate, Specification **A572/A572M** Grade 50; (SI units) ASTM A1018/A1018M: Grade 340, Structural Steel, hot-rolled sheet coils, as rolled, mill edge; 10 by 1000 mm by coil; ID 600 mm, OD 1800 mm, maximum; coil weight 18 000 kg maximum; 100 000 kg for conversion to plate, Specification **A572/A572M** Grade 340.

7. Chemical Composition

7.1 The heat analysis of commercial steel and drawing steel shall conform to the requirements of **Table 2**, and where appropriate, **Table 3**.

7.2 The heat analysis of structural steel, high-strength low-alloy steel, high-strength low-alloy steel with improved formability, and ultra-high strength steel shall conform to the requirements of **Tables 2 and 3**.

7.3 **Table 1** describes the heat analysis requirements for two sets of limits (A and B) for the elements copper, chromium,

**TABLE 2 Chemical Requirements^A
Commercial and Drawing Steels**

Designation	% Heat Analysis, Element Maximum Unless Otherwise Shown														
	C	Mn	P	S	Al	Si	Cu	Ni	Cr	Mo	V	Cb	Ti ^B	N	B
Commercial Steels (CS)															
CS Type A	0.10	0.60	0.030	0.035	0.20 ^C	0.20	0.15	0.06	0.008	0.008	0.025
CS Type B	0.02 to 0.15	0.60	0.030	0.035	0.20 ^C	0.20	0.15	0.06	0.008	0.008	0.025
1007	0.02 to 0.10	0.50	0.030	0.035	0.20 ^C	0.20	0.15	0.06	0.008	0.008	0.025
1008	0.10	0.50	0.030	0.035	0.20 ^C	0.20	0.15	0.06	0.008	0.008	0.025
1009	0.15	0.60	0.030	0.035	0.20 ^C	0.20	0.15	0.06	0.008	0.008	0.025
1010	0.08 to 0.13	0.30 to 0.60	0.030	0.035	0.20 ^C	0.20	0.15	0.06	0.008	0.008	0.025
1012	0.10 to 0.15	0.30 to 0.60	0.030	0.035	0.20 ^C	0.20	0.15	0.06	0.008	0.008	0.025
1015	0.13 to 0.18	0.30 to 0.60	0.030	0.035					0.008	0.008	0.025
1016	0.13 to 0.18	0.60 to 0.90	0.030	0.035					0.008	0.008	0.025
1017	0.15 to 0.20	0.30 to 0.60	0.030	0.035					0.008	0.008	0.025
1018	0.15 to 0.20	0.60 to 0.90	0.030	0.035					0.008	0.008	0.025
1019	0.15 to 0.20	0.70 to 1.00	0.030	0.035					0.008	0.008	0.025
1020	0.18 to 0.23	0.30 to 0.60	0.030	0.035					0.008	0.008	0.025
1021	0.18 to 0.23	0.60 to 0.90	0.030	0.035					0.008	0.008	0.025
1022	0.18 to 0.23	0.70 to 1.00	0.030	0.035					0.008	0.008	0.025
1023	0.20 to 0.25	0.30 to 0.60	0.030	0.035					0.008	0.008	0.025
1524	0.19 to 0.25	1.35 to 1.65	0.030	0.035					0.008	0.008	0.025
Drawing Steels (DS)															
DS Type A	0.08	0.50	0.020	0.030	0.01 min	...	0.20	0.20	0.15	0.06	0.008	0.008	0.025
DS Type B	0.02 to 0.08	0.50	0.020	0.030	0.01 min	...	0.20	0.20	0.15	0.06	0.008	0.008	0.025
1006	0.08	0.45	0.030	0.035	0.01 min	...	0.20	0.20	0.15	0.06	0.008	0.008	0.025
1006A	0.02 to 0.08	0.45	0.030	0.035	0.01 min	...	0.20	0.20	0.15	0.06	0.008	0.008	0.025

^A Where an ellipsis (. . .) appears in the table, there is no requirement, but the analysis shall be reported.

^B Titanium is permitted at the producer's option, to the lesser of 3.4N + 1.5S or 0.025 %.

^C When copper steel is specified, the copper limit is a minimum requirement. When copper steel is not specified, the copper limit is a maximum requirement.

nickel, and molybdenum. The required set of limits (A and B) for these elements shall be specified on the order.

7.4 Chemical analysis shall be conducted in accordance with Test Methods, Practices, and Terminology **A751**.