



## Designation: **A515/A515M – 10 A515/A515M – 10 (Reapproved 2015)**

# Standard Specification for Pressure Vessel Plates, Carbon Steel, for Intermediate- and Higher-Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A515/A515M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope<sup>2</sup>

1.1 This specification<sup>2</sup> covers carbon-silicon steel plates primarily for intermediate- and higher-temperature service in welded boilers and other pressure vessels.

1.2 Plates under this specification are available in three grades having different strength levels as follows:

colwidth="66,67\*"/COLSPEC

60 [415]  
65 [450]  
70 [485]

Tensile Strength, ksi [MPa]

60–80 [415–550]  
65–85 [450–585]  
70–90 [485–620]

1.3 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical property requirements; however, current practice normally limits the maximum thickness of plates furnished under this specification as follows:

colwidth="66,67\*"/COLSPEC

60 [415]  
65 [450]  
70 [485]

Maximum Thickness, in. [mm]

8 [200]  
8 [200]  
8 [200]

1.4 For plates produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification **A20/A20M** apply.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

**A20/A20M** Specification for General Requirements for Steel Plates for Pressure Vessels

**A435/A435M** Specification for Straight-Beam Ultrasonic Examination of Steel Plates

**A577/A577M** Specification for Ultrasonic Angle-Beam Examination of Steel Plates

**A578/A578M** Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications

## 3. General Requirements and Ordering Information

3.1 Plates supplied to this product specification shall conform to Specification **A20/A20M**. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions and mass, quality and repair of defects, marking, loading, and ordering information.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available where additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification **A20/A20M**.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.11** on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Oct. 1, 2010/Sept. 1, 2015. Published November 2010/September 2015. Originally approved in 1964. Last previous edition approved in 2007/2010 as **A515/A515M – 03 (2007)**; **A515/A515M – 10**. DOI: 10.1520/A0515\_A0515M-10-10.1520/A0515\_A0515M-10R15.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification **SA-515/SA-515M** in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

3.3 If the requirements of this specification are in conflict with the requirements of Specification **A20/A20M**, the requirements of this specification shall prevail.

3.4 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, three test results are reported for each qualifying coil. Additional requirements regarding plate produced from coil are described in Specification **A20/A20M**.

#### 4. Materials and Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and made to a coarse austenitic grain size practice.

#### 5. Heat Treatment

5.1 Plates 2 in. [50 mm] and under in thickness are normally supplied in the as-rolled condition. The plates may be ordered normalized or stress relieved, or both.

5.2 Plates over 2 in. [50 mm] in thickness shall be normalized.

#### 6. Chemical Composition

6.1 The steel shall conform to the chemical requirements given in **Table 1** unless otherwise modified in accordance with Supplementary Requirement S17, Vacuum Carbon-Deoxidized Steel, in Specification **A20/A20M**.

#### 7. Mechanical Properties

7.1 *Tension Test*—The plates, as represented by the tension test specimens, shall conform to the requirements given in **Table 2**.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ASTM A515/A515M-10\(2015\)](#)

<https://standards.iteh.ai/catalog/standards/sist/e7b4a15-18a6-49cd-b070-ecdd9a7d469f/astm-a515-a515m-102015>

**TABLE 1 Chemical Requirements**

Elements	Composition, %		
	Grade 60 [Grade 415]	Grade 65 [Grade 450]	Grade 70 [G
Carbon, max: <sup>A, B</sup>			
Carbon, max: <sup>A, B</sup>			
1 in. [25 mm] and under	0.24	0.28	0.31
Over 1 to 2 in. [25 to 50 mm], incl	0.27	0.31	0.33
Over 2 to 4 in. [50 to 100 mm], incl	0.29	0.33	0.35
Over 4 to 8 in. [100 to 200 mm], incl	0.31	0.33	0.35
Over 8 in. [200 mm]	0.31	0.33	0.35
Manganese <sup>B</sup> , max:			
Manganese, <sup>B</sup> max:			
Heat analysis	0.90	0.90	1.20
Product analysis	0.98	0.98	1.30
Phosphorus, max <sup>A</sup>	0.025	0.025	0.025
Sulfur, max <sup>A</sup>	0.025	0.025	0.025
Silicon:			
Heat analysis	0.15–0.40	0.15–0.40	0.15–0.40
Product analysis	0.13–0.45	0.13–0.45	0.13–0.45

<sup>A</sup> Applies to both heat and product analyses.

<sup>B</sup> For each reduction of 0.01 percentage point below the specified maximum for carbon, an increase of 0.06 percentage point above the specified maximum for manganese is permitted, up to a maximum of 1.50 % by heat analysis and 1.60 % by product analysis.