



Designation: B196/B196M – 07 (Reapproved 2013)<sup>ε1</sup>

## Standard Specification for Copper-Beryllium Alloy Rod and Bar<sup>1</sup>

This standard is issued under the fixed designation B196/B196M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

<sup>ε1</sup> NOTE—Corrections were made in Table 3 and 10.2.1 editorially in September 2015.

### 1. Scope\*

1.1 This specification establishes the requirements for copper-beryllium alloy rod and bar in straight lengths. The following three alloys are included:

Copper Alloy UNS No.	Previously Used Designations	Nominal Beryllium Content, %
C17000	Alloy 165	1.7
C17200	Alloy 25	1.9
C17300		1.9
		+0.4 lead

1.2 Unless otherwise required, Copper Alloy UNS No. C17200 shall be the alloy furnished whenever Specification B196/B196M is specified without any alloy designation.

1.3 The values stated in either inch-pounds or SI units are to be regarded separately as the standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 The following documents in the current issue of the Book of Standards form a part of this specification to the extent referenced herein:

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved April 1, 2013. Published April 2013. Originally approved in 1945 to replace portions of B120 – 41 T. Last previous edition approved in 2007 as B196/B196M-07. DOI: 10.1520/B0196\_B0196M-07R13E01.

### 2.2 ASTM Standards:<sup>2</sup>

[B194 Specification for Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar](#)

[B249/B249M Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings](#)

[B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast](#)

[B846 Terminology for Copper and Copper Alloys](#)

[E8 Test Methods for Tension Testing of Metallic Materials](#)

[E8M Test Methods for Tension Testing of Metallic Materials \[Metric\] \(Withdrawn 2008\)<sup>3</sup>](#)

### 3. General Requirements

3.1 The following sections of Specification [B249/B249M](#) constitute a part of this specification:

3.1.1 Terminology;

3.1.2 Dimensions and Permissible Variations;

3.1.3 Workmanship, Finish, and Appearance;

3.1.4 Sampling;

3.1.5 Number of Tests and Retests;

3.1.6 Specimen Preparation;

3.1.7 Test Methods;

3.1.8 Significance of Numerical Limits;

3.1.9 Inspection;

3.1.10 Rejection and Rehearing;

3.1.11 Certification;

3.1.12 Mill Test Report;

3.1.13 Packaging and Package Marking; and

3.1.14 Heat Identification

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard

3.2 In addition, when a section with a title identical to that referenced in 3.1 above appears in this specification, it contains additional requirements which supplement those appearing in Specification B249/B249M.

**4. Terminology**

4.1 For terms related to copper and copper alloys, refer to Terminology B846.

4.2 *Definitions of Terms Specific to This Standard:*

4.2.1 *Heat*—A heat shall be the result of castings poured simultaneously from the same source of molten metal.

4.2.2 *Lot*—The lot shall be a heat or fraction thereof.

**5. Ordering Information**

5.1 Orders for products should include the following information, as applicable:

- 5.1.1 ASTM specification designation and year of issue,
- 5.1.2 Quantity,
- 5.1.3 Copper Alloy UNS No. designation (Section 1),
- 5.1.4 Form of material (rod or bar and cross section, such as round, hexagonal, and so forth),
- 5.1.5 Temper (Section 8),
- 5.1.6 Dimensions (diameter or distance between parallel surfaces, and length),
- 5.1.7 How furnished (stock or specific lengths, with or without ends), and
- 5.1.8 When material is ordered for agencies of the U.S. government (See Section 11).

5.2 The following options are available and should be specified in the contract or purchase order when required:

- 5.2.1 Type of edge (square corners, rounded corners, rounded edge, full-rounded edge),
- 5.2.2 Mechanical properties (tension test and hardness) (Section 10),
- 5.2.3 Certification, and
- 5.2.4 Mill Test Report.

**6. Materials and Manufacture**

6.1 *Material:*

6.1.1 The material of manufacture shall be Copper Alloy UNS No. C17000, C17200, or C17300, cast and worked and of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 Heat traceability shall be maintained and reported on the Mill Test Report or Certification.

6.2 *Manufacture:*

**TABLE 1 Chemical Requirements**

Element	Composition, %		
	Copper Alloy UNS No.		
	C17000	C17200	C17300
Beryllium	1.60–1.85	1.80–2.00	1.80–2.00
Nickel + cobalt, min	0.20	0.20	0.20
Nickel + cobalt + iron, max	0.6	0.6	0.6
Aluminum, max	0.20	0.20	0.20
Silicon, max	0.20	0.20	0.20
Lead	...	...	0.20–0.6
Copper	remainder	remainder	remainder

6.2.1 The product shall be produced with a combination hot working, cold working, and thermal processing to produce a uniform wrought structure and the specified temper.

**7. Chemical Composition**

7.1 The material shall conform to the chemical composition requirements prescribed in Table 1 for Copper Alloy UNS No. designation specified in the ordering information.

7.2 These composition limits do not preclude the presence of other elements. Limits for unnamed elements may be established and analysis required by agreement between the manufacturer, or supplier, and purchaser.

7.3 Copper is customarily given as remainder, but may be taken as the difference between the sum of all elements analyzed and 100 %.

7.4 When all the elements in Table 1 are determined, the sum of results shall be 99.5 % min.

**8. Temper**

8.1 The standard temper designations available under this specification and as specified in Practice B601 are solution heat-treated TB00 (A), and cold-drawn hard TD04 (H), (see Table 2) to be precipitation heat treated by the user. Also available are products already precipitation heat treated by the manufacturer, tempers TF00 (AT) and TH04 (HT). These products meet property requirements in Table 3 and normally require no further heat treatment by the user.

**9. Precipitation Heat Treatment**

9.1 The precipitation heat treatment is performed on TB00 (A) and TD04 (H) tempers by the purchaser, after machining or forming.

**TABLE 2 Solution Heat-Treated and Solution Heat-Treated and Cold-Worked Mechanical Property Requirements**

Temper Designation		Diameter or Maximum Distance Between Parallel Surfaces		Tensile Strength, ksi	Tensile Strength, MPa	Yield Strength, min 0.2 % offset, ksi		Rockwell Hardness, B Scale	Elongation in 4 × D <sup>A</sup> , min, %
Standard	Former	in.	mm			ksi	MPa		
TB00	Solution heat treated (A)	all sizes	all sizes	60–85	410–590	20	140	45–85	20
TD04	Hard (H)	up to 3/8, incl.	up to 10	90–130	620–900	75	520	88–103	8
		over 3/8 to 1 incl.	over 10 to 25 incl.	90–125	620–860	75	520	88–102	8
		over 1 to 3, incl.	over 25 to 75	85–120	590–830	75	520	88–101	8

<sup>A</sup> 4 × D = 4 × diameter.