



Designation: F290 – 94 (Reapproved 2015)

Standard Specification for Round Wire for Winding Electron Tube Grid Laterals¹

This standard is issued under the fixed designation F290; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers round wire up to 0.006 in. (0.15 mm) in diameter for use as electron tube grid lateral winding wire.

1.2 Five classes of wire are covered based on their tensile properties (see 5.2 and 5.3).

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[E39 Methods for Chemical Analysis of Nickel](#) (Withdrawn 1995)³

[E107 Test Methods for Chemical Analysis of Electronic Nickel](#) (Withdrawn 2003)³

[E129 Test Method for Spectrographic Analysis of Thermionic Nickel Alloys by the Powder Techniques](#) (Withdrawn 1999)³

[F16 Test Methods for Measuring Diameter or Thickness of Wire and Ribbon for Electronic Devices and Lamps](#)

[F205 Test Method for Measuring Diameter of Fine Wire by Weighing](#)

[F288 Specification for Tungsten Wire for Electron Devices and Lamps](#)

[F289 Specification for Molybdenum Wire and Rod for Electronic Applications](#)

3. Terminology

3.1 *Description of Terms:*

3.1.1 The following description of terms shall apply to the requirements specified in [Table 1](#):

3.1.1.1 *breaking strength*—The stress at which the specimen breaks.

3.1.1.2 *elongation*—The maximum percent of stretch in a specimen of 10-in. (250-mm) gage length.

3.1.1.3 *tensile strength*—The ultimate strength of the material expressed either as grams per milligram per 200 mm length of wire or pounds per square inch.

3.1.1.4 *ultimate strength*—The maximum stress developed in a specimen.

3.1.1.5 *work load*—The difference between the yield load and the ultimate load.

3.1.1.6 *yield strength*—The stress developed at 1 percent elongation when testing a specimen of 10-in. (250-mm) gage length.

4. Chemical Composition

4.1 The wire shall conform to the requirements as to chemical composition as prescribed in [Table 2](#).

5. Tensile Properties

5.1 The wire shall conform to the requirements as to tensile strength, yield strength, working range, and elongation properties as prescribed in [Table 1](#) for the class of wire designated.

5.2 The class designations for the nickel-titanium-magnesium alloy UNS N03300; the nickel-manganese alloy UNS N02211; molybdenum wire, and the nickel-molybdenum-iron alloy UNS N10001; are based on their tensile properties as follows:

5.2.1 *Class I*—The wire shall conform to elongation properties as specified in ranges in [Table 1](#).

5.2.2 *Class II*—The wire shall conform to the following tensile properties:

5.2.2.1 Yield strength with a spread of approximately $\pm 15\%$, as shown in grams-force, minimum and maximum, in [Table 2](#),

5.2.2.2 Working range, as specified in [Table 1](#), and

¹ This specification is under the jurisdiction of ASTM Committee F01 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials, Wire Bonding, and Flip Chip.

Current edition approved July 1, 2015. Published October 2015. Originally approved in 1954 as B290 – 54 T; redesignated F290 in 1955. Last previous edition approved in 2010 as F290 – 94 (2010). DOI: 10.1520/F0290-94R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

TABLE 1 Tensile Properties for Nickel-Titanium-Magnesium Alloy (UNS N03300), Nickel-Manganese Alloy (UNS N02211), Molybdenum Wire, and Nickel-Molybdenum-Iron Alloy (UNS N10001) Wire
CLASS I

NOTE 1—Wire supplied as Class I shall conform to the following elongation values as specified by range:

Material	Range	Wire Diameter, in. (mm)	Elongation, %
Nickel-titanium-magnesium alloy (UNS N03300) and nickel-manganese alloy (UNS N02211)	1	All	8 to 16
	2	All	14 to 22
	3	0.003 (0.08) and under	20 and over
	4	Above 0.003 (0.08)	22 and over
Molybdenum	1	All	8 to 16
	2	All	14 to 22
Nickel-molybdenum-iron alloy (UNS N10001)	1	0.001 (0.025)	8 to 18
	2	0.0015 (0.038)	18 to 32
	3	0.002 (0.050) and above	25 and over

CLASS II

 NOTE 1—Wire supplied as Class II shall conform to the following requirements as to yield strength (± 15 percent), working range, and elongation:

Material	Wire Diameter		Yield Strength				Working Load, min, gf	Elongation, min, %	
	in.	(mm)	Approximate Center		Load				
			Stress psi	(Mpa)	min, gf	max, gf			
Nickel-titanium-magnesium alloy (UNS N03300)	0.0015	(0.038)	74 000	(510)	51	67	17	8	
	0.0016	(0.041)	74 000	(510)	56	76	17	8	
	0.0017	(0.043)	70 500	(486)	62	84	17	8	
	0.0018	(0.046)	70 500	(486)	69	93	20	8	
	0.0019	(0.048)	70 500	(486)	76	104	20	10	
	0.0020	(0.051)	70 000	(483)	85	115	35	10	
	0.0025	(0.064)	68 500	(472)	130	175	60	10	
	0.0027	(0.069)	64 500	(445)	145	190	75	10	
	0.0030	(0.076)	63 500	(438)	175	235	90	15	
	0.0033	(0.084)	63 000	(434)	210	280	115	15	
	0.0035	(0.089)	63 000	(434)	235	315	135	20	
	0.0040	(0.102)	61 500	(424)	300	400	190	20	
	0.0045	(0.114)	60 000	(414)	370	500	250	20	
	0.0050	(0.127)	60 000	(414)	450	610	330	20	
	0.0055	(0.140)	60 000	(414)	550	745	400	20	
	0.0060	(0.152)	60 000	(414)	655	885	475	20	
	Nickel-manganese alloy (UNS N02211)	0.0020	(0.051)	59 600	(411)	70	100	30	14
0.0025		(0.064)	58 400	(403)	110	150	50	14	
0.0027		(0.067)	56 800	(392)	125	170	60	14	
0.0030		(0.076)	56 600	(390)	150	210	80	18	
0.0033		(0.084)	50 400	(347)	175	245	105	18	
0.0035		(0.089)	50 400	(347)	200	270	120	18	
0.004		(0.102)	51 000	(352)	250	340	170	22	
0.0045		(0.114)	47 000	(324)	295	395	230	22	
0.005		(0.127)	46 000	(317)	350	470	305	22	
0.006		(0.152)	43 000	(296)	465	635	490	22	
Molybdenum		0.0008	(0.020)	120 000	(827)	24	34	1	8
		0.0010	(0.025)	120 000	(827)	35	50	4	8
		0.0012	(0.030)	118 500	(817)	50	70	6	8
		0.0013	(0.033)	118 500	(817)	60	80	8	8
		0.00133	(0.034)	118 500	(817)	65	85	8	8
		0.00150	(0.038)	113 500	(782)	77	105	10	12
		0.0017	(0.043)	113 500	(782)	95	135	15	12
	0.0020	(0.051)	105 000	(724)	127	173	25	12	
	0.0025	(0.064)	101 000	(696)	191	259	40	15	
	0.0030	(0.076)	96 000	(662)	262	354	65	17	
	0.0033	(0.084)	96 000	(662)	317	429	80	17	
	0.0035	(0.089)	96 000	(662)	356	482	90	17	
	0.0040	(0.102)	96 000	(662)	466	630	115	17	
	0.0045	(0.114)	96 000	(662)	589	797	145	17	
	0.0050	(0.127)	96 000	(662)	728	984	180	17	
	0.0055	(0.140)	96 000	(662)	880	1190	220	17	
	0.0060	(0.152)	96 000	(662)	1047	1417	260	17	
Nickel-molybdenum-iron alloy (UNS N10001)	0.0016	(0.041)	92 000	(634)	70	95	40	10	
	0.0020	(0.051)	85 000	(586)	102	138	65	10	
	0.0025	(0.064)	85 000	(586)	160	215	110	10	
	0.0030	(0.076)	80 000	(552)	219	297	165	15	
	0.0033	(0.084)	80 000	(552)	272	368	205	15	
	0.0035	(0.089)	80 000	(552)	287	389	240	15	



TABLE 1 Continued

CLASS II

NOTE 1—Wire supplied as Class II shall conform to the following requirements as to yield strength (± 15 percent), working range, and elongation:

Material	Wire Diameter		Yield Strength				Working Load, min, gf	Elongation, min, %
	in.	(mm)	Approximate Center		Load			
			Stress psi	(Mpa)	min, gf	max, gf		
	0.0040	(0.102)	80 000	(552)	371	503	320	20
	0.0050	(0.127)	80 000	(552)	606	820	485	20

Class III

NOTE 1—Wire supplied as Class III shall conform to the following requirements as to yield strength (± 10 %), working range, and elongation:

Material	Wire Diameter		Yield Strength				Working Load, min, gf	Elongation, min, %
	in.	(mm)	Approximate Center		Load			
			Stress psi	(Mpa)	min, gf	max, gf		
Nickel-titanium-magnesium alloy (UNS N03300)	0.0015	(0.038)	74 000	(510)	53	65	20	10
	0.0016	(0.041)	74 000	(510)	59	73	25	10
	0.0017	(0.043)	70 500	(486)	66	80	30	12
	0.0018	(0.046)	70 500	(486)	72	89	35	12
	0.0019	(0.048)	70 500	(486)	81	99	35	12
	0.0020	(0.051)	70 000	(483)	90	110	45	15
	0.0025	(0.064)	68 500	(472)	135	165	75	15
	0.0027	(0.069)	64 500	(445)	150	185	90	15

Class III

NOTE 1—Wire supplied as Class III shall conform to the following requirements as to yield strength (± 10 %), working range, and elongation:

Material	Wire Diameter		Yield Strength				Working Load, min, gf	Elongation, min, %	
	in.	(mm)	Approximate Center		Load				
			Stress psi	(Mpa)	min, gf	max, gf			
Nickel-titanium-magnesium alloy (UNS N03300)	0.0030	(0.076)	63 500	(438)	185	225	120	15	
	0.0033	(0.084)	63 000	(434)	220	270	145	15	
	0.0035	(0.089)	63 000	(434)	250	305	170	20	
	0.0040	(0.102)	61 500	(424)	315	385	230	20	
	0.0045	(0.114)	60 000	(414)	390	480	310	20	
	0.0050	(0.127)	60 000	(414)	475	585	400	20	
	0.0055	(0.140)	60 000	(414)	580	710	485	20	
	0.0060	(0.152)	60 000	(414)	690	850	575	20	
	Nickel-manganese alloy (UNS N02211)	0.0020	(0.051)	59 600	(411)	75	95	40	14
		0.0025	(0.064)	58 400	(403)	115	145	65	14
		0.0027	(0.069)	56 800	(392)	130	165	80	14
		0.0030	(0.076)	56 600	(390)	160	200	100	18
		0.0033	(0.084)	50 400	(347)	190	235	125	18
		0.0035	(0.090)	50 400	(347)	210	260	145	18
0.0040		(0.102)	51 500	(355)	265	325	200	22	
0.0045		(0.114)	47 500	(328)	310	380	265	22	
Molybdenum	0.0050	(0.127)	46 000	(317)	370	450	355	22	
	0.006	(0.152)	54 000	(372)	495	605	560	22	
	0.0008	(0.020)	120 000	(827)	25	33	1	8	
	0.0010	(0.025)	120 000	(827)	40	50	4	8	
	0.0012	(0.030)	118 500	(817)	55	65	6	8	
	0.0013	(0.033)	118 500	(817)	65	75	8	8	
	0.00133	(0.034)	118 500	(817)	70	80	8	8	
	0.0015	(0.038)	113 500	(782)	82	100	10	12	
	0.0017	(0.043)	113 500	(782)	105	129	15	12	
	0.0020	(0.051)	96 000	(662)	135	165	25	15	
	0.0025	(0.064)	96 000	(662)	202	248	40	15	
	0.0030	(0.076)	96 000	(662)	277	339	65	17	
	0.0033	(0.084)	96 000	(662)	336	410	80	17	
	0.0035	(0.089)	96 000	(662)	377	461	90	17	
	0.0040	(0.102)	96 000	(662)	493	603	115	17	
	0.0045	(0.114)	96 000	(662)	624	762	145	17	
	0.0050	(0.127)	96 000	(662)	770	942	180	17	
	0.0055	(0.140)	96 000	(662)	932	1139	220	17	
	0.0060	(0.152)	96 000	(662)	1109	1355	260	17	
	Nickel-molybdenum-iron alloy (UNS N10001)	0.0016	(0.041)	92 000	(634)	76	92	45	15
		0.0020	(0.051)	85 000	(586)	109	133	75	15
		0.0025	(0.064)	85 000	(586)	167	205	125	15
0.0030		(0.076)	80 000	(552)	232	284	185	20	
0.0033		(0.084)	80 000	(552)	289	353	230	20	
0.0035		(0.089)	80 000	(552)	305	373	270	20	