



Designation: C1670/C1670M – 15

Standard Specification for Adhered Manufactured Stone Masonry Veneer Units¹

This standard is issued under the fixed designation C1670/C1670M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The purpose of this standard is to establish the minimum product specifications for adhered manufactured stone masonry veneer units. These units are manufactured using a wet cast concrete mixture and finished to simulate stone, rocks found in nature, and other textures.

1. Scope*

1.1 This specification covers the minimum product requirements for adhered manufactured stone masonry veneer units applied as an adhered veneer to exterior and interior walls and structures suitable to receive units.

1.2 The property requirements of this specification apply at the time of delivery. This standard does not address the physical evaluation of installed units removed from service.

1.3 The units described by this specification are manufactured from a mixture of cement, normal or lightweight aggregates (or a combination of both), water, admixtures, other cementitious materials and other components which are wet-cast into shapes simulating the appearance of natural stone and other textures.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes shall not be considered as requirements of the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use of units.*

NOTE 1—When particular features are desired such as surface textures

¹ This test method is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.03 on Concrete Masonry Units and Related Units.

Current edition approved Sept. 1, 2015. Published September 2015. Originally approved in 2013. Last previous edition approved in 2014 as C1670/C1670M – 14. DOI: 10.1520/C1670_C1670M-15.

or color these features should be specified separately. Suppliers should be consulted as to the availability of units having the desired features.

2. Referenced Documents

2.1 ASTM Standards:

C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field

C33 Specification for Concrete Aggregates

C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

C140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units

C150 Specification for Portland Cement

C207 Specification for Hydrated Lime for Masonry Purposes

C260 Specification for Air-Entraining Admixtures for Concrete

C330 Specification for Lightweight Aggregates for Structural Concrete

C331 Specification for Lightweight Aggregates for Concrete Masonry Units

C426 Test Method for Linear Drying Shrinkage of Concrete Masonry Units

C482 Test Method for Bond Strength of Ceramic Tile to Portland Cement Paste

C494/C494M Specification for Chemical Admixtures for Concrete

C595 Specification for Blended Hydraulic Cements

C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

C666/C666M Test Method for Resistance of Concrete to Rapid Freezing and Thawing

C979 Specification for Pigments for Integrally Colored Concrete

C989 Specification for Slag Cement for Use in Concrete and Mortars

C1116/C1116M Specification for Fiber-Reinforced Concrete

C1157 Performance Specification for Hydraulic Cement

*A Summary of Changes section appears at the end of this standard

C1232 Terminology of Masonry

C1240 Specification for Silica Fume Used in Cementitious Mixtures

3. Terminology

3.1 Terminology defined in Terminology **C1232** shall apply for this specification.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *adhered manufactured stone masonry veneer unit, n*—a non-load bearing masonry unit that is produced by wet-cast blending of cementitious material, lightweight and other aggregates, pigments and admixtures, designed to be applied with a cementitious mortar to a backing surface.

3.2.2 *unit profile, n*—the combination of units that represent the range of shapes and sizes provided in the specified veneer.

3.2.3 *average thickness, n*—the mean of the depth measurement of the unit as measured from the back side to the face side.

3.2.4 *designated area, n*—the area of a completed wall section that is used to verify compliance.

3.2.5 *saturated density, n*—the water saturated weight of the cured specimen divided by the volume of the specimen.

3.2.6 *wet cast, adj*—manufactured from a measurable slump concrete.

4. Materials

4.1 Cementitious materials shall conform to the following applicable specifications:

4.1.1 *Portland Cement*—Specification **C150**.

4.1.2 *Blended Hydraulic Cements*—Specification **C595**.

4.1.3 *Pozzolans*—Specification **C618**.

4.1.4 *Slag Cement*—Specification **C989**.

4.1.5 *Hydraulic Cement*—Specification **C1157**.

4.1.6 *Silica Fume*—Specification **C1240**.

4.1.7 *Hydrated Lime*—Specification **C207**.

4.2 *Aggregates*—Aggregates shall conform to the following specifications:

4.2.1 *Normal Weight Aggregates*—Specification **C33**.

4.2.2 *Lightweight Aggregates*—Specification **C330** or **C331**.

4.3 *Air-Entraining Admixtures*—Specification **C260**.

4.4 *Concrete Admixtures*—Specification **C494/C494M**.

4.5 *Coloring Pigments*—Specification **C979**.

4.6 *Reinforcement Fibers*—Specification **C1116/C1116M**.

4.7 *Other Constituents:*

4.7.1 Other constituent materials shall be shown by test of experience or history of performance under equivalent conditions not to be detrimental to the durability of the adhered manufactured stone masonry veneer unit, or adhered manufactured stone masonry veneer construction, or both.

5. Compressive Strength

5.1 From each manufacturing location, obtain representative samples from standard production of each concrete mix used for units in accordance with **5.2**.

5.1.1 Sample and test the concrete mixes used for units no more than twelve months prior to production of units. More frequent testing shall be required if there is any change in the manufacturing process including changes in cementitious materials or their sources, aggregates or their sources, water-cementitious materials ratio, mix design, manufacturing process or curing. This does not include producing units of varying shapes, configurations or sizes of units.

NOTE 2—It is common practice to use the same mix design to produce a wide variety of adhered manufactured stone masonry veneer unit shapes, sizes, and configurations. This standard only requires the evaluation of the compressive strength of each mix design, not each unit configuration produced by a common mix design.

5.2 Sample the concrete mix at the manufacturing facility from standard production mix. Form compressive strength and absorption specimens in accordance with Practice **C31/C31M**; except that the time requirements for transportation do not apply when specimens are shipped to the testing laboratory.

5.2.1 For compressive strength testing, prepare five 4-in. diameter by 8 in. [100 mm by 200 mm] cylinders and test in accordance with **5.3**. Do not disturb the curing cylinders for a minimum of 48 hours after casting. De-mold them at an age of seven days.

5.3 Test specimens at an age of 28 days in accordance with Test Method **C39/C39M**.

5.4 The average compressive strength of five specimens shall be a minimum of 2100 psi [15 MPa] with no individual specimen having a measured compressive strength less than 1800 psi [12 MPa].

6. Freeze-Thaw Durability

6.1 From each manufacturing location, obtain representative samples from standard production of each concrete mix used for units in accordance with **6.2**.

6.1.1 Sample and test the concrete mixes used for units no more than twelve months prior to production of units. More frequent testing shall be required if there is any change in the manufacturing process including changes in cementitious materials or their sources, aggregates or their sources, water-cementitious materials ratio, mix design, manufacturing process or curing. This does not include producing units of varying shapes, configurations or sizes of units.

6.2 Sample the concrete mix at the manufacturing facility from standard production mix in accordance with Practice **C31/C31M** except that the time requirements for transportation do not apply when specimens are shipped to the testing laboratory.

6.2.1 For freeze/thaw durability testing, prepare five 3 in. by 3 in. by 11 in. [75 mm by 75 mm by 275 mm] beams. The molded beams shall be de-molded 24–32 hours after casting and shall be air cured for 28 days.

6.3 *Testing Requirements:*

6.3.1 No single specimen in a group of five specimens shall exhibit a mass loss greater than 1.5 % or show any fracture completely through the cross section when tested in accordance with Test Method **C666/C666M**, Procedure A, with the following modifications: