



Designation: C1232 – 15a

## Standard Terminology of Masonry<sup>1</sup>

This standard is issued under the fixed designation C1232; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This standard incorporates generic terms and generic definitions of terms specifically associated with manufactured masonry units and masonry constructed with manufactured masonry units. These generic terms and definitions are used within the standards developed by Committee C12 on Mortars and Grouts for Unit Masonry and Committee C15 on Manufactured Masonry Units.

1.2 This standard incorporates terms and definitions of terms associated with the standards specific to clay masonry units, in particular to Specifications C32, C34, C56, C62, C126, C212, C216, C279, C410, C530, C652, C902, C1088, C1167, C1261, C1272, and C1405, and to Test Methods C67.

1.3 This standard incorporates terms and definitions of terms associated with the standards specific to concrete masonry units in particular to Specifications C55, C73, C90, C129, C139, C744, C1319, C1372, C1491, C1623, and C1634 and to Test Methods C140, C426, and C1262.

1.4 This standard incorporates terms and definition of terms associated with the standards specific to autoclaved aerated concrete masonry units in particular to Practice C1692 and to Specifications C1386, C1691, and C1693.

1.5 This standard incorporates terms and definitions of terms associated with the standards specific to clay and concrete roofing tile units in particular to Specifications C1167 and C1492 and to Test Methods C1568, C1569, and C1570.

1.6 For terminology specific to mortar and grout, see Terminology C1180.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C32 Specification for Sewer and Manhole Brick (Made

From Clay or Shale)  
C34 Specification for Structural Clay Load-Bearing Wall Tile  
C55 Specification for Concrete Building Brick  
C56 Specification for Structural Clay Nonloadbearing Tile  
C62 Specification for Building Brick (Solid Masonry Units Made From Clay or Shale)  
C67 Test Methods for Sampling and Testing Brick and Structural Clay Tile  
C73 Specification for Calcium Silicate Brick (Sand-Lime Brick)  
C90 Specification for Loadbearing Concrete Masonry Units  
C126 Specification for Ceramic Glazed Structural Clay Facing Tile, Facing Brick, and Solid Masonry Units  
C129 Specification for Nonloadbearing Concrete Masonry Units  
C139 Specification for Concrete Masonry Units for Construction of Catch Basins and Manholes  
C140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units  
C212 Specification for Structural Clay Facing Tile  
C216 Specification for Facing Brick (Solid Masonry Units Made from Clay or Shale)  
C279 Specification for Chemical-Resistant Masonry Units  
C410 Specification for Industrial Floor Brick  
C426 Test Method for Linear Drying Shrinkage of Concrete Masonry Units  
C530 Specification for Structural Clay Nonloadbearing Screen Tile  
C652 Specification for Hollow Brick (Hollow Masonry Units Made From Clay or Shale)  
C744 Specification for Prefaced Concrete and Calcium Silicate Masonry Units  
C902 Specification for Pedestrian and Light Traffic Paving Brick  
C936 Specification for Solid Concrete Interlocking Paving Units  
C1088 Specification for Thin Veneer Brick Units Made From Clay or Shale  
C1167 Specification for Clay Roof Tiles  
C1180 Terminology of Mortar and Grout for Unit Masonry  
C1261 Specification for Firebox Brick for Residential Fireplaces

<sup>1</sup> This terminology is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.08 on Terminology.

Current edition approved Sept. 1, 2015. Published September 2015. Originally approved in 1993. Last previous edition approved in 2015 as C1232 – 15. DOI: 10.1520/C1232-15A.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

- C1262 Test Method for Evaluating the Freeze-Thaw Durability of Dry-Cast Segmental Retaining Wall Units and Related Concrete Units
- C1272 Specification for Heavy Vehicular Paving Brick
- C1319 Specification for Concrete Grid Paving Units
- C1372 Specification for Dry-Cast Segmental Retaining Wall Units
- C1386 Specification for Precast Autoclaved Aerated Concrete (AAC) Wall Construction Units (Withdrawn 2013)<sup>3</sup>
- C1405 Specification for Glazed Brick (Single Fired, Brick Units)
- C1491 Specification for Concrete Roof Pavers
- C1492 Specification for Concrete Roof Tile
- C1568 Test Method for Wind Resistance of Concrete and Clay Roof Tiles (Mechanical Uplift Resistance Method)
- C1569 Test Method for Wind Resistance of Concrete and Clay Roof Tiles (Wind Tunnel Method)
- C1570 Test Method for Wind Resistance of Concrete and Clay Roof Tiles (Air Permeability Method)
- C1623 Specification for Manufactured Concrete Masonry Lintels
- C1634 Specification for Concrete Facing Brick
- C1691 Specification for Unreinforced Autoclaved Aerated Concrete (AAC) Masonry Units
- C1692 Practice for Construction and Testing of Autoclaved Aerated Concrete (AAC) Masonry
- C1693 Specification for Autoclaved Aerated Concrete (AAC)

### 3. Terminology

3.1 *Generic Definitions*—The definitions apply to manufactured masonry units and masonry constructed with manufactured masonry units. They are generic as used by ASTM Committees C12 and C15.

**bed surface**, *n*—(1) the nonvertical surfaces of a manufactured masonry unit intended by the manufacturer to be joined by mortar or other methods. (2) the in situ nonvertical surfaces of a manufactured masonry unit joined by mortar or other methods.

**cryptofluorescence**, *n*—crystalline deposit of water-soluble compounds in the pores of masonry.

**efflorescence**, *n*—crystalline deposit, usually white, of water-soluble compounds on the surface of masonry.

**face, exposed**, *n*—the in situ exposed surface(s) of a manufactured masonry unit.

**face, finished**, *n*—any surface(s) of a manufactured masonry unit intended by the manufacturer to be exposed to view.

**freeze thaw resistance**, *n*—the ability of masonry to maintain integrity under the forces caused by cyclic action of freezing and thawing in the presence of moisture.

**frog**, *n*—an indentation in a bed surface of a masonry unit. Indentations not exceeding  $\frac{3}{8}$  in. (9.5 mm) are termed a frog,

sometimes called a panel or panel frog. Indentations exceeding  $\frac{3}{8}$  in. (9.5 mm) are termed a deep frog.

**groove**, *n*—a channel formed on surfaces other than finished faces of manufactured masonry units for production or construction purposes.

**height**, *n*—vertical dimension of the face of a unit when the unit is positioned as a stretcher.

**length**, *n*—horizontal dimension of the face of a unit when the unit is positioned as a stretcher.

**masonry**, *n*—the type of construction made up of manufactured masonry units laid with mortar, grout, or other methods of joining.

**nominal dimension**, *n*—dimension that is greater than the specified dimension by the thickness of a mortar joint. It is usually expressed as a whole number.

**permeable unit pavement system**, *n*—pavement with a wearing surface consisting of clay or concrete paving units that allows for the flow of water through the wearing surface to a bed, base, subbase, or combinations thereof.

DISCUSSION—Permeable unit pavement systems are utilized to reduce stormwater runoff. The system can also be designed for water storage or harvesting. Permeable unit pavements have wearing surfaces that allow water flow through open spaces or joints to drain water. The base and subbase are typically constructed with open-graded aggregates, but can be designed with other materials that allow sufficient drainage or storage that can accommodate a design storm (for example, 1 year, 24 hour event).

With unit pavers the open spaces can be achieved with exposed coring, a specially-shaped perimeter configuration, wider joints, or combinations thereof. Permeable pavement systems can also be made with standard units and a laying pattern or joint width that permits sufficient water entry.

**score**, *n*—a channel formed for appearance purposes on the finished faces of a manufactured masonry unit.

**shell**, *n*—the outer walls of a hollow masonry unit. Shell can either be an end shell or a face shell.

**specified dimensions**, *n*—dimensions to which masonry units or constructions are required to conform. Actual (measured) dimensions may differ from the specified dimensions by permissible variations.

**surface feature**, *n*—a quality or condition of the face of a manufactured masonry unit.

DISCUSSION—Surface features include coatings, colors, textures, relief, or combinations of these. A masonry unit may have different surface features on individual faces.

**thickness**, *n*—that dimension designed to lie at right angles to the face of the wall, floor, or other assembly.

**unit, facing**, *n*—manufactured masonry unit designed for use where one or more faces will be exposed and for which the specification includes requirements on color, finish, and other properties affecting appearance.

**unit, hollow masonry**, *n*—unit whose net cross-sectional area in any plane parallel to the surface containing cores, cells, or

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

deep frogs is less than 75 % of its gross cross-sectional area measured in the same plane.

**unit, manufactured masonry, *n***—a manmade noncombustible building product intended to be laid by hand and joined by mortar, grout, or other methods of joining.

**unit, permeable paving, *n***—a manufactured masonry unit for pavement applications configured to achieve a minimum percentage of open area in the wearing surface of the pavement by coring, a specially-shaped perimeter, or larger spacer lugs, or combinations thereof.

DISCUSSION—Permeable paving units may be specified under C902 for Pedestrian and Light Traffic Paving Brick, C936 for Solid Concrete Interlocking Paving Units, C1272 for Heavy Vehicular Paving Brick, or C1319 for Concrete Grid Paving Units. Permeable pavement systems can also be made with standard units and a laying pattern that permits sufficient water entry.

**unit, solid masonry, *n***—unit whose net cross-sectional area in any plane parallel to the surface containing cores, cells, or deep frogs is 75 % or more of its gross cross-sectional area measured in the same plane.

**units placed in usage, *n***—manufactured masonry units that have been installed in masonry.

### 3.2 Definitions Specific to Clay Masonry Units:

**absorption, *n***—weight of water picked up by a clay masonry unit during immersion at prescribed conditions expressed in relation to the dry weight of the unit.

DISCUSSION—Two conditions of immersion are designated in standards relating to brick: 24 h in room temperature (60 to 86°F (15.5 to 30°C)) water or 5 h in boiling water. (Different time intervals are specified for structural tile and other products.) The resulting absorptions are termed *cold water absorption* and *boiling water absorption*.

Absorption values are used in brick and tile standards as one factor in classifying these products into durability grades. Absorptions are indicators of the extent of firing during manufacture as well as being indicators of durability.

**absorption, initial rate of, *n***—a measure of the suction of water upward into a dry brick from a bed face during one minute of exposure.

DISCUSSION—Initial rate of absorption (IRA) is a distinct property that offers different information from absorption. It is expressed as grams of water picked up in one minute by a net area of 30 in.<sup>2</sup> (194 cm<sup>2</sup>).

Initial rate of absorption is one factor influencing the quality of bond between brick and mortar. It is used in brick standards to recommend construction practices for enhancing mortar to brick bonding.

**brick, *n***—a solid or hollow masonry unit of clay or shale, usually formed into a rectangular prism, then burned or fired in a kiln; brick is a ceramic product.

**brick, building, *n***—brick for load-resisting or other purposes where appearance properties such as texture or color are not important (formerly called common brick); see Specification C62 and Specification C652.

**brick, chemical-resistant, *n***—brick suitable for use in chemical environments where resistance to thermal shock may be

a consideration, usually used in conjunction with chemical-resistant mortars; see Specification C279.

**brick, facing, *n***—brick for general purposes where appearance properties such as color, texture, and chippage are important; see Specification C216 and Specification C652.

DISCUSSION—Facing brick are produced from selected clays and are available in typical face sizes, various colors, and in various textures.

**brick, firebox, *n***—brick intended for use as the lining in the fireboxes of residential fireplaces; see Specification C1261.

**brick, floor, *n***—brick with physical properties related to resistance to chemicals, thermal and mechanical shock, or absorption, or combinations of these, used as finished floor surfaces in industrial applications; see Specification C410.

DISCUSSION—Other brick are used as flooring in non-industrial applications; see Specification C902. Floor brick manufactured to meet the requirements in Specification C410 are typically smooth and dense.

**brick, paving, *n***—brick made to provide the wearing surface of highways, streets, driveways, walkways, patios, and similar applications; see Specifications C902 and C1272.

**brick, sewer, *n***—low absorption, abrasive-resistant brick intended for use in drainage structures; see Specification C32.

**brick, specially-shaped, *n***—a brick manufactured to a basic shape of other than a rectangular prism.

**cells/core holes, *n***—continuous openings or perforations within extruded clay products.

DISCUSSION—The extent of permissible openings is specified for each product as the percentage of gross area in the normal bedding surface plane that must be net (solid) area. Core hole is generally used for brick while cell is used for structural tile. Cells are distinguished from core holes by being larger in size. As an illustration, cells must be larger than 1 in.<sup>2</sup> (645 mm<sup>2</sup>) under Specification C34, and 1½ in.<sup>2</sup> (968 mm<sup>2</sup>) under Specification C652.

**ceramic, *adj***—pertaining to products containing hydrous silicates of alumina that are treated to develop fired bond.

DISCUSSION—Ceramic materials used for brick and clay tile typically consist of clay or other similar earthy materials that have been fired in a kiln to temperatures above 1500°F (655°C). The exposure to high temperature begins the transformation of the constituent materials from their natural state to that of a glassy state (incipient fusion).

**clay, *n***—an earthy or stony mineral aggregate consisting essentially of hydrous silicates of alumina, plastic when sufficiently pulverized and wetted, rigid when dry, and vitreous when fired to a sufficiently high temperature.

**color, body, *n***—the range of color obtained when materials used to form the brick react to the effects of firing temperature and atmosphere.

DISCUSSION—There may be additives in the body to produce a desired color. When no materials are added to the surface of the brick and the unit is not flashed when fired, the body color is also the through-body color, a surface feature.

**color, through-body, *n***—the range of surface color obtained when units without materials added to the surfaces for appearance purposes are fired without flashing.

DISCUSSION—Through-body color results from the materials used to form the brick reacting to the effects of firing temperature. There may be additives in the body to produce a desired color.