



Designation: **C563 – 13 C563 – 15**

# Standard Test Method for Approximation of Optimum SO<sub>3</sub> in Hydraulic Cement Using Compressive Strength<sup>1</sup>

This standard is issued under the fixed designation C563; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*Scope

1.1 This test method describes the determination of approximate optimum SO<sub>3</sub> for maximum compressive strength at 24 h, 3 days, or 7 days by measuring the change in strength produced in hydraulic cement mortar as a result of substituting calcium sulfate for a portion of the cement.

1.2 This test method refers to the sulfur trioxide (SO<sub>3</sub>) content of the cement only. Slag cements and occasionally other hydraulic cements can contain sulfide or other forms of sulfur. The determination of SO<sub>3</sub> content by rapid methods may include these other forms, and may therefore produce a significant error. If a significant error occurs, analyze the cement for SO<sub>3</sub> content using the reference test method of Test Methods **C114** for sulfur trioxide.

1.3 Values stated as SI units are to be regarded as standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**C109/C109M** Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

**C114** Test Methods for Chemical Analysis of Hydraulic Cement

**C150** Specification for Portland Cement

**C204** Test Methods for Fineness of Hydraulic Cement by Air-Permeability Apparatus

**C305** Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

**C471M** Test Methods for Chemical Analysis of Gypsum and Gypsum Products (Metric)

**C511** Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes

**C595** Specification for Blended Hydraulic Cements

**C778** Specification for Sand

**C1157** Performance Specification for Hydraulic Cement

**C1437** Test Method for Flow of Hydraulic Cement Mortar

## 3. Significance and Use

3.1 The purpose of this test method is to estimate the SO<sub>3</sub> content for a hydraulic cement that gives maximum compressive strength in mortar made and cured at ~~23°C~~ 23°C. The value obtained is one way to establish an appropriate level of sulfate in the manufacture of cements specified in Specifications **C150**, **C595** and **C1157**.

3.2 The SO<sub>3</sub> content of a cement giving maximum compressive strength is different at different ages of mortar; typically this SO<sub>3</sub> content is higher at 3 days than the 24-h, and often higher for 7 days than that for 3 days. A manufacturer can choose the age of 24-h, 3 days or 7 days for specimens at which to determine optimum SO<sub>3</sub> content.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **C01** on Cement and is the direct responsibility of Subcommittee **C01.28** on Sulfate Content. Current edition approved ~~Jan. 1, 2013~~ Sept. 1, 2015. Published ~~February 2013~~ October 2015. Originally approved in 1965. Last previous edition approved in ~~2007~~ 2013 as **C563C563 – 13-07**. DOI: ~~10.1520/C0563-13~~ 10.1520/C0563-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

3.3 This test method indicates optimum SO<sub>3</sub> content for cement in mortar made and cured at a standard temperature of 23.0 ± 2.0 °C (73.5 ± 3.5 °F)–3.5 °F). The optimum SO<sub>3</sub> increases with increasing temperature and may increase when water-reducing admixtures are used.

3.4 It should not be assumed that the optimum SO<sub>3</sub> estimated in this test method is the same SO<sub>3</sub> content for optimum performance of a concrete prepared from the cement.

3.5 The test method is applicable to cements specified in Specifications **C150**, **C595**, and **C1157**.

#### 4. Apparatus

4.1 Use the apparatus as specified in Test Method **C109/C109M**.

#### 5. Materials

5.1 *Calcium Sulfate*—Use calcium sulfate for addition to the cement that is either a high-grade natural gypsum having an SO<sub>3</sub> content of at least 46 %, or the calcium sulfate from the source used for the intended plant production. Grind the calcium sulfate to 100 % passing the 75-µm (No. 200) sieve, and at least 800 m<sup>2</sup>/kg Blaine fineness (Test Method **C204**). If the SO<sub>3</sub> content of the calcium sulfate is unknown, analyze it in accordance with Test Methods **C471M**.

5.2 *Blended/Graded Standard Sand*—Use graded sand conforming to Specification **C778**.

#### 6. Test Specimens

6.1 Make six specimens from each batch of mortar. Make two rounds of three mixtures of mortar as described in 6.3. Make both rounds during the same day if possible. Make only complete rounds on any given day.

6.2 *Preparing Specimen Molds*—Prepare molds in accordance with the section on Preparation of Specimen Molds of Test Method **C109/C109M**.

6.3 *Proportioning, Consistency, and Mixing of Mortar*—Proportion the dry material for the standard mortar as one part of cement to 2.75 parts graded sand by mass. Mix the following quantities of dry materials at one time for a 6-cube batch:

Mixture No. 1—	500 g cement
Mixture No. 1	500 g cement
	1375.0 g graded sand
	1375.0 g graded sand
Mixture No. 2—	494.6 g cement
Mixture No. 2	494.6 g cement
	5.3 g calcium sulfate
	1375.0 g graded sand
	1375.0 g graded sand
Mixture No. 3—	489.2 g cement
Mixture No. 3	489.2 g cement
	10.6 g calcium sulfate
	10.6 g calcium sulfate
	1375.0 g graded sand
	1375.0 g graded sand

6.3.1 Use an amount of mixing water to produce a flow of 110 ± 5 using 25 drops of the table as determined in the section on Procedures in Test Method **C1437** for all types of cement.

6.3.2 Mix mechanically in accordance with the section on Procedure for Mixing Mortars of Practice **C305**, except as follows:

6.3.2.1 Add the calcium sulfate to the water; then start the mixer and mix at slow speed (140 ± 5 rpm) for 15 s; then stop the mixer and add the cement to the water; then start the mixer and mix at slow speed (140 ± 5 rpm) for 30 s.

6.4 *Molding of Test Specimens*—Mold specimens in accordance with the Procedure Section of Test Method **C109/C109M**.

6.5 *Storage of Test Specimens*—Immediately upon completion of molding, place the test specimens in the moist closet or moist room. Keep all test specimens, immediately after molding, in the molds on the base plates in the moist closet or moist room for 20 to 24 h with their upper surfaces exposed to the moist air but protected from dripping water. If the specimens are removed from the molds before 24 h, keep them on the shelves of the moist closet or moist room until they are 24-h old and then immerse the specimens, except those for the 24-h test, in saturated lime water in storage tanks constructed of noncorroding materials until the age chosen for the test. Keep the storage water clean by changing as required.

#### 7. Temperature and Humidity

7.1 The temperature and humidity of the moist cabinet or moist room shall be as specified in Specification **C511**.

7.2 The temperature and humidity of the mixing room shall be as specified in Test Method **C109/C109M**.