This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



**Designation:** B747 - 11 B747 - 15

# Standard Specification for Copper-Zirconium Alloy Sheet and Strip <sup>1</sup>

This standard is issued under the fixed designation B747; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

#### 1. Scope\*

- 1.1 This specification establishes the requirements for sheet and strip of Copper Alloy UNS C15100.C15100 sheet and strip.
- 1.2 *Units*—Values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are provided for information only and are not considered standard.

#### 2. Referenced Documents

- 2.1 ASTM Standards:<sup>2</sup>
- B193 Test Method for Resistivity of Electrical Conductor Materials
- B248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar
- B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast
- B846 Terminology for Copper and Copper Alloys
- E3 Guide for Preparation of Metallographic Specimens
- E8/E8M Test Methods for Tension Testing of Metallic Materials
- E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry
- E112 Test Methods for Determining Average Grain Size
- E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition
- E478 Test Methods for Chemical Analysis of Copper Alloys

#### 3. General Requirements

- 3.1 The following sections of Specification B248 constitute a part of this specification:
- 3.1.1 Terminology,
- 3.1.2 Workmanship, Finish, and Appearance,
- 3.1.3 Sampling,
- 3.1.4 Number of Tests and Retests, o/standards/sist/04fl ce3e-ab0f-4ea1-ba23-1cd0b76d4006/astm-b747-15
- 3.1.5 Specimen Preparation,
- 3.1.6 Significance of Numerical Limits,
- 3.1.7 Inspection,
- 3.1.8 Rejection and Rehearing,
- 3.1.9 Certification,
- 3.1.10 Test Reports, Report,
- 3.1.11 Packaging and Package Marking, and
- 3.1.12 Supplementary Requirements.

#### 4. Terminology

4.1 For definition of terms related to copper and copper alloys, refer to Terminology B846.

#### 5. Ordering Information

- 5.1 Include the following specified choices when placing orders for product under this specification, as applicable:
- 5.1.1 ASTM designation number and year of issue,

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved Oct. 1, 2011Oct. 1, 2015. Published November 2011October 2015. Originally approved in 1985. Last previous edition approved in 20072011 as B747-07:B747-11. DOI: 10.1520/B0747-11.10.1520/B0747-15.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- 5.1.2 Quantity (of each size),
- 5.1.2 Copper Alloy [Alloy] UNS No. designation (see designation, 1.1),
- 5.1.3 Form of material (sheet or strip), Temper,
- 5.1.5 Temper (see 8.1),
- 5.1.4 Dimensions (thickness, width, length, if applicable),
- 5.1.5 How furnished (rolls, specific lengths with or without ends, stock lengths with or without ends),
- 5.1.6 Quantity-total weight or total length or number of pieces of each size,
- 5.1.7 Type of edge, if required (slit, sheared, sawed, square corners, rounded corners, rounded edges, or full-rounded edges),
- 5.1.8 Type of width and straightness tolerances, if required (slit metal tolerances, square sheared metal tolerances, sawed metal tolerances, straightened or edge-rolled metal tolerances), and
  - 5.1.9 Intended application.
- 5.2 In addition, when material is purchased for the U.S. Government, it shall conform to the Supplemental requirements as defined in Specification The following options are available but may not be included unless specified at the time of placing of the order B248 when specified in the contract or purchase order required:
  - 5.2.1 Heat identification or traceability details,
  - 5.2.2 Certification,
  - 5.2.3 Test Report,
  - 5.2.4 If product specification number must be shown on package marking, and
- 5.2.5 If product is purchased for agencies of the U.S. Government (See Supplemental Requirements section of Specification B248 for additional requirements).

## 6. Material Materials and Manufacture

- 6.1 *Material: Materials:*
- 6.1.1 The material of manufacture shall be a <u>east-form (cast bar, slab, cake, billet, etc.slab, etcetera)</u> of Copper Alloy UNS No. C15100 of such purity and soundness as to be suitable for processing in to-into the products prescribed herein.
- 6.1.2 When specified in the contract or purchase order, that heat identification or traceability is required, the purchaser shall specify the details desired.

Note 1—Due to the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.

- 6.2 Manufacture:
- 6.2.1 The product shall be manufactured by such hotworking, hot-working, cold-working, and annealing processes as to produce a uniform wrought structure in the finished product.
- 6.2.2 The product shall be hot- or cold-worked to the finished size, and subsequently annealed, annealed when required, to meet the temper properties specified. <a href="mailto:catalog/standards/sist/04flce3e-ab0f-4ea1-ba23-1cd0b76d4006/astm-b747-15">catalog/standards/sist/04flce3e-ab0f-4ea1-ba23-1cd0b76d4006/astm-b747-15</a>
  - 6.3 Edges:
  - 6.3.1 Slit edges shall be furnished unless otherwise specified in the contract or purchase order.

#### 7. Chemical Composition

- 7.1 The material shall conform to the chemical composition prescribed requirements in Table 1.
- 7.2 These composition limits do not preclude the presence of other elements. By agreement between <u>the</u> manufacturer and purchaser, limits may be established and analysis required for unnamed elements.
  - 7.3 When all elements <del>listed in Table 1</del> are <del>analyzed determined</del>, the sum of the results shall be 99.9 % minimum min.

#### 8. Temper

- 8.1 The standard tempers for products described in this specification are given in Table 2.
- 8.1.1 Cold rolled tempers H01 to H08.
- 8.1.2 Annealed temper OS015.

**TABLE 1 Chemical Requirements** 

	Composition, %	
Element	Copper Alloy	
	UNS No. C15100	
Copper (including Ag)	99.80 % min	
Zirconium	0.05-0.15	
Cu + sum of named elements	99.9 % min	

**TABLE 2 Tensile Strength and Grain Size Requirements** 

Temper De	esignation <sup>A</sup>	Tensile Strength, ksi <sup>B</sup> (MPa) <sup>C</sup>		Grain Size,
<u>StandardCode</u>	FormerName	Min	Max	$mm^D$
OS015	annealed			0.030 max
H01	quarter hard	40 (275)	45 (310)	
H02	half hard	43 (295)	51 (350)	
H03	three-quarter hard	47 (325)	56 (385)	•••
H04	hard	53 (365)	62 (425)	
H06	extra hard	59 (405)	65 (450)	
H08	spring	64 (440)	71 (490)	

<sup>&</sup>lt;sup>A</sup> Standard designations defined in PracticeClassification B601.

# 9. Grain Size for Annealed Temper

- 9.1 Grain size shall be the standard requirement for all product in the annealed tempers.
- 9.2 Acceptance or rejection based upon grain size shall depend only on the average grain size of a test specimen taken from each of two sample portions, and each specimen shall be within the limits prescribed in Table 2 when determined in accordance with Test MethodMethods E112.

### 10. Physical Property Requirements

10.1 Electrical Resistivity Requirements: Requirement:

10.1.1 The product furnished shall conform to the electrical mass Resistivity requirements resistivity requirement prescribed in Table 3 by temper—when tested in accordance with Test Method B193.

# 11. Mechanical Property Requirements

- 11.1 Tensile Strength Requirements: Requirements:
- 11.1.1 Product furnished under this specification shall conform to the tensile requirements prescribed in Table 2, when tested in accordance with Test MethodMethods E8/E8M.
  - 11.1.2 Acceptance and or rejection based upon mechanical properties shall depend only on tensile strength.

#### 12. Dimensions, Mass, and Permissible Variations Variation

- 12.1 The following titled sections and tables dimensions and tolerances for product described by this specification shall be as specified in Specification B248 are a part of this specification: with particular reference to the following tables and related paragraphs as noted to Specification B747 in the table title:
  - 12.1.1 Thickness.
  - 12.1.2 Width—Slit metal and slit metal with rolled edges.
  - 12.1.2 Square Sheared Metal; Sawed Metal. Width:

- 12.1.2.1 Slit Metal and Slit Metal with Rolled Edges.
- 12.1.2.2 Square Sheared Metal.
- 12.1.2.3 Sawed Metal.
- 12.1.3 Length:
- 12.1.3.1 Length Tolerances for Specific and Stock Lengths With and Without Ends. Tolerance for Straight Lengths.

**TABLE 3 Electrical Resistivity** 

colwidth="0.93in"/0	COLSPEC Electrical Resistivity at 20°C (68°F), max, Ω-g/m²	Equivalent Conductivity at 20°C (68°F), % IACS, min
Annealed (OS015)	0.16136	95
Rolled (H01, H02, —H03, H04, H06, H08)	<del>0.17031</del>	90
Rolled (H01, H02, H03, H04, H06, H08)	<u>0.17031</u>	<u>90</u>

 $<sup>^{</sup>B}$  ksi = 1000 psi.

<sup>&</sup>lt;sup>C</sup> See Appendix X1

 $<sup>^{\</sup>it D}$  Although no minimum grain size is required, this material must be fully recrystallized.