



Designation: C1417 – 15

# Standard Specification for Manufacture of Reinforced Concrete Sewer, Storm Drain, and Culvert Pipe for Direct Design<sup>1</sup>

This standard is issued under the fixed designation C1417; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the manufacture and acceptance of precast concrete pipe designed to conform to the owner's design requirements and to ASCE 15 or an equivalent design specification.

1.2 This specification is the companion to SI Specification C1417M; therefore, no SI equivalents are presented in this specification.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement

A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement

A1064/A1064M Specification for Carbon-Steel Wire and Welded Wire Reinforcement, Plain and Deformed, for Concrete

C33/C33M Specification for Concrete Aggregates

C76 Specification for Reinforced Concrete Culvert, Storm Drain, and Sewer Pipe

C150/C150M Specification for Portland Cement

C260/C260M Specification for Air-Entraining Admixtures for Concrete

C494/C494M Specification for Chemical Admixtures for Concrete

C497 Test Methods for Concrete Pipe, Manhole Sections, or Tile

C595/C595M Specification for Blended Hydraulic Cements

C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

C655 Specification for Reinforced Concrete D-Load

Culvert, Storm Drain, and Sewer Pipe  
C822 Terminology Relating to Concrete Pipe and Related Products

C989/C989M Specification for Slag Cement for Use in Concrete and Mortars

C1017/C1017M Specification for Chemical Admixtures for Use in Producing Flowing Concrete

C1116/C1116M Specification for Fiber-Reinforced Concrete

C1602/C1602M Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete

### 2.2 Other Standards:

ASCE 15 Standard Practice for the Direct Design of Buried Precast Reinforced Concrete Pipe Using Standard Installations (SIDD)<sup>3</sup>

ACI 318 Building Code Requirements for Reinforced Concrete<sup>4</sup>

## 3. Terminology

### 3.1 Definitions:

3.1.1 For definitions of terms relating to concrete pipe, see Terminology C822.

3.1.2 *group of pipe sections, n*—each day's production run of pipe sections of a single concrete strength for a specific project.

3.1.3 *lot of pipe sections, n*—total of the number of groups of pipe sections of a single concrete strength produced for a specific project.

3.1.4 *running average, n*—average concrete compressive strength of all groups of pipe sections of a single concrete strength produced for a specific project, generally determined as each group is tested.

## 4. Basis of Acceptance of Design

4.1 *Manufacturing Design Data*—The manufacturer shall submit the following manufacturing design data for the concrete pipe to the owner for approval.

4.1.1 Pipe wall thickness.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.05 on Special Projects.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1998. Last previous edition approved in 2014 as C1417 – 14<sup>e1</sup>. DOI: 10.1520/C1417-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American Society of Civil Engineers (ASCE), 1801 Alexander Bell Dr., Reston, VA 20191, <http://www.asce.org>.

<sup>4</sup> Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.aci-int.org>.

#### 4.1.2 Concrete strength.

#### 4.1.3 Reinforcement:

##### 4.1.3.1 Specification,

##### 4.1.3.2 Reinforcement Type 1, 2, or 3, where:

- Type 1: Smooth wire or plain bars
- Type 2: Welded smooth wire reinforcement, 8 in. maximum spacing of longitudinals
- Type 3: Welded deformed wire reinforcement, deformed wire, deformed bars, or any reinforcement with stirrups, anchored thereto

##### 4.1.3.3 Design yield strength,

##### 4.1.3.4 Placement and design concrete cover,

##### 4.1.3.5 Cross-sectional diameters,

##### 4.1.3.6 Spacing,

##### 4.1.3.7 Cross-sectional area,

##### 4.1.3.8 Description of longitudinal members, and

4.1.3.9 If stirrups are used, developable stirrup design stress, stirrup shape, placement, and anchorage details.

##### 4.1.4 Design factors and the assumed orientation angle.

##### 4.1.5 Pipe laying length and joint information.

4.2 Approval of the manufacturing design data shall be based on its conformance to the owner's design requirements and to ASCE 15 or to an equivalent design specification.

## 5. Basis of Acceptance of Concrete Pipe

5.1 Acceptance of pipe shall be on the basis of concrete compression tests, materials tests, conformance to the manufacturing design data, conformance to this specification, and inspection of manufactured pipe for defects.

5.2 When mutually agreed in writing by the owner and the manufacturer, a certification may be made the basis of acceptance of the concrete pipe. This certification shall consist of a statement by the manufacturer that the concrete pipe conforms to the manufacturing design data and to this specification, and that the concrete and materials have been sampled and tested and conform to this specification.

5.3 *Age for Acceptance*—Pipe shall be considered ready for acceptance when they conform to the requirements of this specification.

## 6. Material

6.1 *Reinforced Concrete*—The reinforced concrete shall consist of cementitious materials; mineral aggregates; admixtures, if used; and water in which steel has been embedded in such a manner that the steel and concrete act together.

#### 6.2 Cementitious Material:

6.2.1 *Cement*—Cement shall conform to the requirements for portland cement of Specification **C150/C150M** or shall be portland blast-furnace slag cement, portland-limestone cement, or portland-pozzolan cement conforming to the requirements of Specification **C595/C595M**, except that the pozzolan constituent in the Type IP portland-pozzolan cement shall be fly ash.

6.2.2 *Slag Cement*—Slag cement shall conform to the requirements of Grade 100 or 120 of Specification **C989/C989M**.

6.2.3 *Fly Ash*—Fly ash shall conform to the requirements of Specification **C618**, Class F or Class C.

6.2.4 *Allowable Combinations of Cementitious Materials*—The combination of cementitious materials used in the concrete shall be one of the following:

6.2.4.1 Portland cement only.

6.2.4.2 Portland blast-furnace slag cement only.

6.2.4.3 Portland-pozzolan cement only.

6.2.4.4 Portland-limestone cement only,

6.2.4.5 A combination of portland cement or portland-limestone cement and slag cement.

6.2.4.6 A combination of portland cement or portland-limestone cement and fly ash, or

6.2.4.7 A combination of portland cement or portland-limestone cement, slag cement, and fly ash, or

6.2.4.8 A combination of portland-pozzolan cement and fly ash.

6.3 *Aggregates*—Aggregates shall conform to the requirements of Specification **C33/C33M**, except that the requirement for gradation shall not apply.

6.4 *Admixtures*—The following admixtures and blends are allowable:

6.4.1 Air-entraining admixture conforming to Specification **C260/C260M**;

6.4.2 Chemical admixture conforming to Specification **C494/C494M**;

6.4.3 Chemical admixture for use in producing flowing concrete conforming to Specification **C1017/C1017M**; and

6.4.4 Chemical admixture or blend approved by the owner.

6.5 *Steel Reinforcement*—Reinforcement shall consist of wire and welded wire conforming to Specification **A1064/A1064M**; or of bars conforming to Specifications **A615/A615M**, Grade 40 or 60, or **A706/A706M**, Grade 60. For helically wound cages only, weld shear tests are not required.

6.6 *Water*—Water used in the production of concrete shall be potable or non-potable water that meets the requirements of Specification **C1602/C1602M**.

6.7 *Fibers*—Synthetic fibers and nonsynthetic fibers shall be allowed to be used, at the manufacturer's option, in concrete pipe as a nonstructural manufacturing material. Synthetic fibers (Type II and Type III) and nonsynthetic fiber (Type I) designed and manufactured specifically for use in concrete and conforming to the requirements of Specification **C1116/C1116M** shall be accepted.

## 7. Joints

7.1 The joints shall be designed and the ends of the concrete pipe sections shall be formed so that the sections can be laid together to make a continuous line of pipe, compatible with the permissible variations given in Section 15.

## 8. Manufacture

8.1 *Mixture*—The aggregates shall be sized, graded, proportioned, and mixed with such proportions of cementitious material, water, and admixtures, if any, to produce a thoroughly mixed concrete of such quality that the pipe will conform to the test and design requirements of this specification. All concrete shall have a water-cementitious materials ratio not exceeding 0.53 by weight. Minimum concrete strength shall be 4000 psi.

8.2 *Finish*—Pipe shall be substantially free of fractures, large or deep cracks, and surface roughness. The ends of the pipe shall be normal to walls and center line of the pipe, within the limits of variations given in Section 15.

## 9. Circumferential Reinforcement

9.1 A line of circumferential reinforcement for any given total area may be composed of up to two layers for pipe with wall thicknesses of less than 7 in. or three layers for pipe with wall thickness of 7 in. or greater. The layers shall not be separated by more than the thickness of one longitudinal plus ¼ in. The multiple layers shall be fastened together to form a single cage. If the multiple layers of a cage contain circumferential splices, the individual layers shall be rotated so that the splices are staggered. All other specification requirements, such as laps, welds, tolerances of placement in the wall of the pipe, and so forth, shall apply to this method of fabricating a line of reinforcement. The design shall be based on the centroid of the layers.

9.2 Reinforcement placement and concrete cover shall conform to the approved manufacturing data. The nominal concrete cover over the circumferential reinforcement shall not be less than 1 in. in pipe having a wall thickness of 2½ in. or greater, and shall not be less than ¾ in. in pipe having a wall thickness of less than 2½ in. The location of the reinforcement shall be subject to the permissible variations in dimensions given in Section 15. Requirements for placement and protective covering of the concrete from the inner or outer surface of the pipe do not apply to that portion of a cage that is flared so as to extend into the bell or reduced in diameter so as to extend into the spigot.

9.3 Where the wall reinforcement does not extend into the joint area, the maximum longitudinal distance to the last circumferential from the inside shoulder of the bell or the shoulder of the spigot shall be 3 in., except that if this distance exceeds one half of the wall thickness, the pipe wall shall contain at least a total reinforcement area of the minimum specified area per linear foot times the laying length of the pipe section. The minimum cover on the last circumferential near the spigot shoulder shall be ½ in.

9.4 Where reinforcement is in the bell or spigot, the minimum end-cover on the last circumferential shall be ½ in. in the bell or ¼ in. in the spigot.

9.5 The continuity of the circumferential reinforcing steel shall be maintained during the manufacture of the pipe, except when, as agreed upon by the owner, lift eyes or holes are provided in each pipe or the pipe is converted into a manhole tee.

## 10. Welds, Splices, and Development of Circumferential Reinforcement

### 10.1 General:

10.1.1 When pipe are not marked to show a specific orientation in the ground, any weld to, or splice of, a circumferential shall be considered to be at the point of the maximum flexural stress.

10.1.2 When pipe are marked to show a specific orientation in the ground, any weld to, or splice of, a circumferential shall be considered to be at a distance determined by the orientation angle closer to the point of maximum flexural stress than the marking indicates.

10.1.3 Splices of smooth and deformed wire shall be welded and shall meet the requirements of 10.3 and 10.4.

### 10.2 Notation:

$A_{wa}$	= actual steel area of the individual circumferential wire, in. <sup>2</sup>
$A_{wr}$	= steel area required for the individual circumferential wire for flexure, in. <sup>2</sup> , either at the splice, for splices, or at the point of maximum moment, for quadrant mat reinforcement.
$d_b$	= diameter of reinforcing wire or bar, in.
$f'_c$	= design compressive strength of concrete, lb/in. <sup>2</sup> .
$f_y$	= design yield strength of reinforcement, lb/in. <sup>2</sup> .
$L_d$	= development length of reinforcing wire or bar, in.
$s$	= spacing of wire to be developed or spliced, in.

### 10.3 Welds:

10.3.1 When splices are welded there shall be a minimum lap of 2 in. and a weld of sufficient length such that pull test of representative specimens shall develop at least 50 % of the minimum specified tensile strength of the steel. For butt-welded splices in bars or wire, permitted only with helically wound cages, pull tests of representative specimens shall develop at least 75 % of the minimum specified tensile strength of the steel.

### 10.4 Lapped Splices of Circumferential Reinforcement:

10.4.1 If lapped splices of circumferentials consisting of deformed bars #6 or less are not welded, they shall be lapped not less than  $L_d$ , where:

$$L_d = \frac{d_b f_y A_{wr}}{33 \sqrt{f'_c} A_{wa}} \quad (1)$$

or not less than:

$$\frac{d_b f_y}{66 \sqrt{f'_c}} \quad (2)$$

whichever is greater. Splices of larger than #6 bars shall meet the requirements of ACI 318.

10.4.2 If lapped splices of circumferentials consisting of welded smooth wire reinforcement or welded deformed wire reinforcement are not welded, the overlap measured between the outermost longitudinals on each side of the splice shall be no less than the spacing of the longitudinals plus 1 in. or  $L_d$ , where:

$$L_d = 0.27 \frac{A_{wr} f_y}{s \sqrt{f'_c}} \quad (3)$$

whichever is greater.

10.4.3 At the option of the manufacturer, a more detailed analysis may be made and the following exception to the requirements of 10.4.2 may be applied. If the area of circumferential reinforcement is at least twice that required for flexure, the first requirement of 10.4.2 shall not apply. The overlap measured between the outermost longitudinals on each