



Designation: D6754/D6754M – 15

Standard Specification for Ketone Ethylene Ester Based Sheet Roofing¹

This standard is issued under the fixed designation D6754/D6754M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers flexible sheet made from ketone ethylene ester (KEE) as the primary polymer intended for use in single ply roofing membrane exposed to the weather. The sheet shall be reinforced with fabric.

1.2 In-place roof system design criteria, such as fire resistance, field-seaming strength, material compatibility, uplift resistance, in-situ shrinkage, among others, are factors that must be considered, but are beyond the scope of this specification.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 The following precautionary caveat pertains to the test methods portion only, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- D471 Test Method for Rubber Property—Effect of Liquids
- D751 Test Methods for Coated Fabrics
- D1079 Terminology Relating to Roofing and Waterproofing
- D1204 Test Method for Linear Dimensional Changes of Nonrigid Thermoplastic Sheet or Film at Elevated Temperature
- D2136 Test Method for Coated Fabrics—Low-Temperature Bend Test

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.18 on Nonbituminous Organic Roof Coverings.

Current edition approved Nov. 1, 2015. Published November 2015. Originally approved in 2002. Last previous edition approved in 2010 as D6754/D6754M – 10. DOI: 10.1520/D6754_D6754M-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D3045 Practice for Heat Aging of Plastics Without Load
- D3389 Test Method for Coated Fabrics Abrasion Resistance (Rotary Platform Abrader)
- D5602 Test Method for Static Puncture Resistance of Roofing Membrane Specimens
- D5635 Test Method for Dynamic Puncture Resistance of Roofing Membrane Specimens
- D7635/D7635M Test Method for Measurement of Thickness of Coatings Over Fabric Reinforcement
- G21 Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi
- G151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources
- G154 Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials
- G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials

3. Terminology

3.1 *Definitions*—Terminology D1079 shall apply to this specification.

3.2 *ketone ethylene ester (KEE), n*—a high molecular weight thermoplastic copolymer of ethylene, containing carbon monoxide and either vinyl acetate or acrylate monomer which are incorporated to provide softness and polarity.

3.2.1 *Discussion*—Ester groups of the vinyl acetate or acrylate are pendant from the ethylene backbone and reduce crystallinity, which provides flexibility. Carbon monoxide groups within the polymer backbone provide polarity. The KEE polymer is therefore a flexible polymer, which is miscible with other polymers of similar polarity.

3.3 *polymer content, n*—in this specification, polymer content shall be defined as polymeric materials which are in the solid state at room temperature, and are high (greater than 50 000 Mw) in molecular weight. Other ingredients, known to the art of polymer compounding, such as certain waxes, stabilizers, and other additives, while polymeric in nature are not considered to be part of the base polymer system.

4. Materials and Manufacture

4.1 The sheet shall be formulated from the appropriate polymers and other compounding ingredients. The KEE polymer shall be a minimum of 50 % by weight of the polymer content of the sheet.