



Designation: F 1105 – 95 (Reapproved 1999)^{ε1}

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Preparing Aircraft Cleaning Compounds, Liquid-Type, Temperature-Sensitive, or Solvent-Based, for Storage Stability Testing¹

This standard is issued under the fixed designation F 1105; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Keywords were added editorially in May 1999.

1. Scope

1.1 This test method covers the determination of the stability in storage of liquid enzyme-based, terpene-based, and solvent-based chemical cleaning compounds used to clean the exterior surfaces of aircraft.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *U.S. Government Document:*
Federal Specification PPP-P704²

3. Summary of Test Method

3.1 Storage stability is determined by evaluation of the effect of time, temperature, and environmental conditions on the cleaning compound. Samples used for testing are filled containers taken from the manufacturer's controlled production formulation, packaged, and delivered to the purchaser for normal use.

3.2 The sample container shall be subjected to the specified storage environment for a period of 12 months. The test shall be completed prior to 24 months from date of packaging.

4. Significance and Use

4.1 This test method determines the procedure to be used to ensure the long-term storage stability of aircraft cleaning and maintenance products in order to ensure their ability to meet the shelf-life requirements called up in specifications or contract documents. The subsequent testing requirements are detailed in the specification or contract.

¹ This test method is under the jurisdiction of ASTM Committee F-7 on Aerospace and Aircraft and is the direct responsibility of Subcommittee F07.07 on Qualification Testing of Aircraft Cleaning Materials.

Current edition approved Oct. 10, 1995. Published December 1995. Originally published as F 1105 – 87. Last previous edition F 1105 – 90 (1991)^{ε1}.

² Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094 Attn: NPQDS.

5. Sampling

5.1 The sample for storage stability testing shall be taken from a controlled production formula, packaged lot, or batch delivered in a sealed, filled container to the purchaser for use. This sample is normally a 1-gal can conforming to Federal Specification PPP-P-704. This material shall have previously been tested and passed all other specification requirements for qualification or acceptance. The sample container selected for the test shall be kept sealed and unopened for the duration of the test. The sample container shall be durably and legibly marked with the following minimum information:

Storage Stability Test Sample

Supplier _____
Formula number _____
Date of packaging _____
Cold test period _____
Hot test period _____
Batch/Lot No. _____
Test began _____
Test ends _____

6. Procedure

6.1 *Storage Environment*—Place the sample container in a storage area where a temperature of 50 to 80°F (10 to 27°C) is maintained at least 80 % of the total storage test time. Do not subject the storage test sample to temperature over 90°F (32°C) or under 10°F (–12°C) during the entire test. Maintain the sample container in a static condition not subject to vibration, rolling, inversion, or other movement. Movement to the necessary temperature controlled area for cold- and hot-temperature testing is excepted, but accomplish such transfer with minimum (or no) disturbance of container contents.

6.1.1 *Cold-Temperature Storage Environment*—Subject the sample container to a 15-day time interval at 17 ± 3°F (–8 ± 2°C). Conduct this cold test interval during the period 90 to 120 days after start of the storage stability test time.

6.1.2 *Hot-Temperature Storage Environment*—Subject the sample container to a 15-day time interval at 90 ± 5°F (32 ± 2°C). Conduct this hot test interval after 270 days of elapsed test time but 60 days before the termination of the storage test.

6.1.3 *Completion of Test*—After 12 months storage test