

Designation: C625 - 95 (Reapproved 2010) C625 - 15

An American National Standard

# Standard Practice for Reporting Irradiation Results on Graphite<sup>1</sup>

This standard is issued under the fixed designation C625; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope-Scope\*

1.1 This practice covers information recommended for inclusion in reports giving graphite irradiation results.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

E261 Practice for Determining Neutron Fluence, Fluence Rate, and Spectra by Radioactivation Techniques E525 Practice for Reporting Dosimetry Results on Nuclear Graphite (Discontinued 2001) (Withdrawn 2001)<sup>3</sup>

# 3. Terminology

3.1 Definitions:

3.1.1 grade, n—designation given a material by a manufacturer such that it is always reproduced to the same specifications established by the manufacturer.

## 4. Significance and Use

- 4.1 The purpose of this practice is to identify sample and test parameters that may influence graphite irradiation test results. This practice should not be construed as a requirement or recommendation that proprietary information be disclosed.
- 4.2 Irradiation results on graphite include dimensional changes and changes in properties that are used in reactor design. The irradiation data are reported in government documents, open literature publications, and are assembled into data manuals for use by reactor designers.

#### 5. Sample Description

- 5.1 Source,
- 5.2 Grade or identifying sample number,
- 5.3 Raw materials including filler, binder, additives, impregnants and their pretreatment, if not proprietary information,
- 5.4 Forming process including the size and shape of parent stock, if not proprietary information,
- 5.5 Heat treatment including graphitizing temperature, rate of heating and soak time, if not proprietary information.
- 5.6 Purification, if not proprietary information,
- 5.7 Sampling plan including location in parent stock, grain orientation, size, and shape of samples, and
- 5.8 Pre-irradiation sample treatment including prestressing, annealing, or previous irradiation.

# 6. Property Measurements

- 6.1 *Method*—Indicate the method and accuracy of measurement and, if applicable, differences between pre- and post-irradiation measurements. Where applicable, give reference to standards or guides that prescribe (or describe) the method used.
  - 6.2 Results—Specify the number of samples represented or the number of measurements per sample if mean values are given.

<sup>&</sup>lt;sup>1</sup> This practice is under the jurisdiction of ASTM Committee D02 on Petroleum Products Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.F0 on Manufactured Carbon and Graphite Products.

Current edition approved May 1, 2010 Oct. 1, 2015. Published May 2010 November 2015. Originally approved in 1968. Last previous edition approved in  $\frac{2005}{2010}$  as  $\frac{2005}{2010}$ . DOI:  $\frac{2005}{2010}$ . DOI:  $\frac{2005}{2010}$ . DOI:  $\frac{2005}{2010}$ .

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.