



Designation: A159 – 83 (Reapproved 2015)

Standard Specification for Automotive Gray Iron Castings¹

This standard is issued under the fixed designation A159; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.
This specification replaces Federal specification AA-I-653A.*

1. Scope

1.1 This specification applies to gray iron castings, cast in sand molds, used in the products of the automobile, truck, tractor, and allied industries.

1.2 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

2. Referenced Documents

2.1 The following documents of the issue in effect on the date of material procurement form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:²

[A247 Test Method for Evaluating the Microstructure of Graphite in Iron Castings](#)

[E10 Test Method for Brinell Hardness of Metallic Materials](#)

2.3 *Military Standard*:

[MIL-STD-129 Marking for Shipment and Storage](#)³

2.4 *Federal Standard*:

[Fed. Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)³

3. Grades

3.1 The specified grades, hardness ranges, and metallurgical description are shown in [Table 1](#) and [Table 2](#) and in Section 9.

4. Ordering Information

4.1 Orders for materials under this specification shall include the following information:

4.1.1 ASTM designation,

- 4.1.2 Grade designation of gray iron required ([3.1](#)),
- 4.1.3 If special heat treatment is required (see [Section 6](#)),
- 4.1.4 If special microstructure requirements are needed (see [Section 7](#)),
- 4.1.5 Surface where hardness test is to be performed (see [9.4](#)),
- 4.1.6 Depth and surface hardness of case required (see [9.6](#)),
- 4.1.7 Inspection lot and sampling plan required (see [Section 10](#)),
- 4.1.8 If additional requirements are needed (see [11.3](#)), and
- 4.1.9 Whether special packaging and marking is required (see [Section 12](#)).

5. Hardness

5.1 The foundry shall exercise the necessary controls and inspection techniques to ensure compliance with the specified hardness range, Brinell hardness shall be determined in accordance with [Test Method E10](#), after sufficient material has been removed from the casting surface to ensure representative hardness readings. The 10-mm ball and 3000-kg load shall be used unless otherwise agreed upon. The area or areas on the casting where hardness is to be checked shall be established by agreement between supplier and purchaser and shall be shown on the drawing.

6. Heat Treatment

6.1 Unless otherwise specified, castings of Grades G1800 and G2500 may be annealed in order to meet the desired hardness range.

6.2 Appropriate heat treatment for removal of residual stresses, or to improve machinability or wear resistance may be specified by agreement between supplier and purchaser.

7. Microstructure

7.1 The microstructure shall consist of flake graphite in a matrix of ferrite or pearlite or mixtures thereof.

7.2 As graphite size and shape somewhat affect hardness-strength ratio and other properties, the type size and distribution of the graphite flakes at a designated location on the casting may be specified by agreement between supplier and purchaser in accordance with [Method A247](#).

¹ This specification is under the jurisdiction of ASTM Committee A04 on Iron Castings and is the direct responsibility of Subcommittee A04.01 on Grey and White Iron Castings.

Current edition approved Nov. 1, 2015. Published November 2015. Originally approved in 1935. Last previous edition approved in 2011 as A159 – 83 (2011). DOI: 10.1520/A0159-83R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.



TABLE 1 Grades of Gray Iron

Grade	Casting Hardness Range	Description
G1800	HB 187 max 4.4 BID min or as agreed ^A	ferritic-pearlitic
G2500	HB 170-229 4.6–4.0 BID or as agreed ^A	pearlitic-ferritic
G3000	HB 187-241 4.4–3.9 BID or as agreed ^A	pearlitic
G3500	HB 207-255 4.2–3.8 BID or as agreed ^A	pearlitic
G4000	HB 217-269 4.1–3.7 BID or as agreed ^A	pearlitic

^ABrinell impression diameter (BID) is the diameter in millimetres of the impression of a 10 mm ball at 3000-kg load.

7.3 Unless otherwise specified, the matrix microstructure of castings covered by this specification shall be substantially free of primary cementite. Castings in Grades G1800 and G2500 may have a matrix of ferrite or pearlite or both. Grades G3000, G3500, and G4000 shall be substantially pearlite in matrix structure.

8. Heavy-Duty Brake Drums and Clutch Plates

8.1 These castings are considered as special cases and are covered in Table 2.

9. Alloy Gray Iron Automotive Camshafts

9.1 These castings are considered as special cases.

9.2 *Grade Designation*—G4000d.

9.3 *Chemistry*—Alloy gray iron camshafts shall contain alloys within the following range or as agreed upon between supplier and purchaser.

Chromium	0.85–1.25 %
Molybdenum	0.40–0.60 %
Nickel	as agreed

9.4 *Casting Hardness*—HB 241-321 determined on a bearing surface as agreed by supplier and purchaser.

9.5 *Microstructure*—Extending 45° on both sides of the centerline of the cam nose and to a minimum depth of 1/8 in. (3.2 mm), the surface shall consist of primary carbides (of acicular or cellular form or a mixture thereof) and graphite in a fine pearlitic matrix. The graphite shall be Type VII A and E distribution, 4 to 7 flake size in accordance with Method A247. The amount of primary carbides and location at which the

structure is checked shall be a matter of agreement between the supplier and the purchaser.

9.6 *Selective Hardening*—The cam areas of camshaft casting are usually selectively hardened by flame or induction hardening by the supplier. The depth and surface hardness of the hardened case shall be as agreed upon between supplier and purchaser.

10. Quality Assurance Provisions

10.1 *Responsibility for Inspection*—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and tests requirements specified in this specification. Except as otherwise specified in the contract or purchase order, the producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspection and tests set for in this specification where such inspections are deemed necessary to assure that material conform to prescribed requirements.

10.2 *Lot*—For the purpose of inspection, lot and sampling plans shall be agreed upon between the purchaser and the producer.

11. General

11.1 Castings furnished to this specification shall be representative of good foundry practice and shall conform to dimensions and tolerances specified on the casting drawing.

11.2 Minor imperfections usually not associated with the structural function may occur in castings. These are often repairable but repairs shall be made only where allowed by the purchaser and only by approved methods.

11.3 Additional casting requirements may be agreed upon by purchaser and supplier. These should appear as product specifications on the casting or part drawing.

12. Preparation for Delivery

12.1 Unless otherwise specified in the contract or purchase order, castings shall be cleaned, preserved, and packaged in accordance with supplier's standard commercial practice.

12.2 *Government Procurement*—When specified for Government procurement, castings shall be marked for shipment in accordance with MIL-STD-129 for military procurement and Fed. Std. No. 123 for civil agency procurement.