



Designation: ~~A323 – 05 (Reapproved 2010)~~ A323 – 05 (Reapproved 2015)

Standard Specification for Ferroboron¹

This standard is issued under the fixed designation A323; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers several grades of ferroboron.

1.2 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards*:²

[A1025 Specification for Ferroalloys and Other Alloying Materials, General Requirements](#)

[E371 Test Method for The Determination of Boron in Ferroboron \(Withdrawn 2006\)](#)³

3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification [A1025](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A1025](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A1025](#), this specification shall prevail.

4. Chemical Composition

4.1 The various grades shall conform to the requirements as to chemical composition specified in [Table 1](#). The manufacturer shall furnish an analysis of each lot showing the percentage of each element specified.

5. Sizing

5.1 Ferroboron is available in various sizes such as: 2 in. (50.8 mm) by down, 1 in. (25.4 mm) by down, ¼ in. (6.35 mm) by down, and 20 mesh (0.841 mm) by down. The size shall be as specified in the order.

6. Chemical Analysis

6.1 The chemical analysis of the material shall be made in accordance with Test Method [E371](#). Where a method is not given in Test Method [E371](#) for the analysis for a particular element, the analysis shall be made in accordance with a procedure agreed upon by the manufacturer and purchaser.

7. Keywords

7.1 ferroboron

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.18](#) on Castings.

Current edition approved ~~April 1, 2010~~ Nov. 1, 2015. Published ~~May 2010~~ November 2015. Originally approved in 1949. Last previous edition approved in ~~2005~~ 2010 as [A323 – 05](#). [A323 – 05 \(2010\)](#). DOI: [10.1520/A0323-05R10](#); [10.1520/A0323-05R15](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on [www.astm.org](#).