



Designation: ~~D3209 – 93 (Reapproved 2008)~~ D3209 – 93 (Reapproved 2015)

Standard Test Method for Freeze/Thaw Resistance of Polymer Floor Polishes¹

This standard is issued under the fixed designation D3209; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the stability of polymer emulsion floor polishes when these are exposed to repeated cycles of freezing and thawing. Possible degradation of the emulsion is observed and possible reduction of initial gloss is measured.

1.2 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1455 Test Method for 60° Specular Gloss of Emulsion Floor Polish

3. Significance and Use

3.1 This test method is used to determine the effect of freezing on floor polishes. It may be used to predict the stability of a floor polish when exposed to freezing.

4. Apparatus

4.1 *Freezer*, adjusted to -7.8 to -6.7°C (18 to 20°F).

4.2 *Flint Glass Bottles*, three, 4 oz (125 mL) capacity.³

4.3 *Black Glass*,⁴ standard, polished as described in Test Method **D1455**.

4.4 *60° Gloss Meter*.

4.5 *Polishes* to be tested.

5. Procedure

5.1 Determine the turbidity of each polish, visually or by any other suitable method.

5.2 Pour one coat of each polish to be tested on the black glass. Allow to dry in a vertical position at room temperature. Determine the initial gloss in accordance with Test Method **D1455**.

5.3 Place 100 mL of polish in each of three 125-mL (4-oz) flint glass bottles. Place the filled bottles side by side, horizontally, in the freezer on a rack, providing a minimum of 25 mm (1 in.) between the bottles and the freezer walls with the contact area between the bottles and the rack no greater than that required to support the bottles.

5.4 Allow the samples to remain in the freezer for 16 h, or a minimum of 8 h after becoming solid.

¹ This test method is under the jurisdiction of ASTM Committee **D21** on Polishes and is the direct responsibility of Subcommittee **D21.03** on Chemical and Physical Testing.

Current edition approved March 1, 2008; Nov. 1, 2015. Published April 2008; November 2015. Originally approved in 1973. Last previous edition approved in 2004; 2008 as D3209 – 93 (2004); (2008). DOI: 10.1520/D3209-93R08; 10.1520/D3209-93R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The sole source of supply of the apparatus known to the committee at this time is Fisher Scientific, Catalog No. 02-883 BA. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁴ The sole source of supply of the apparatus known to the committee at this time is Peril Stein Glass, 2543 Kensington Ave., Phila. PA 19125. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.