



Designation: C518 – 15

Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus¹

This standard is issued under the fixed designation C518; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the measurement of steady state thermal transmission through flat slab specimens using a heat flow meter apparatus.

1.2 The heat flow meter apparatus is used widely because it is relatively simple in concept, rapid, and applicable to a wide range of test specimens. The precision and bias of the heat flow meter apparatus can be excellent provided calibration is carried out within the range of heat flows expected. This means calibration shall be carried out with similar types of materials, of similar thermal conductances, at similar thicknesses, mean temperatures, and temperature gradients, as expected for the test specimens.

1.3 This a comparative, or secondary, method of measurement since specimens of known thermal transmission properties shall be used to calibrate the apparatus. Properties of the calibration specimens must be traceable to an absolute measurement method. The calibration specimens should be obtained from a recognized national standards laboratory.

1.4 The heat flow meter apparatus establishes steady state one-dimensional heat flux through a test specimen between two parallel plates at constant but different temperatures. By appropriate calibration of the heat flux transducer(s) with calibration standards and by measurement of the plate temperatures and plate separation. Fourier's law of heat conduction is used to calculate thermal conductivity, and thermal resistivity or thermal resistance and thermal conductance.

1.5 This test method shall be used in conjunction with Practice C1045. Many advances have been made in thermal technology, both in measurement techniques and in improved understanding of the principles of heat flow through materials. These advances have prompted revisions in the conceptual

approaches to the measurement of the thermal transmission properties **(1-4)**.² All users of this test method should be aware of these concepts.

1.6 This test method is applicable to the measurement of thermal transmission through a wide range of specimen properties and environmental conditions. The method has been used at ambient conditions of 10 to 40°C with thicknesses up to approximately 250 mm, and with plate temperatures from -195°C to 540°C at 25-mm thickness **(5, 6)**.

1.7 This test method may be used to characterize material properties, which may or may not be representative of actual conditions of use. Other test methods, such as Test Methods C236 or C976 should be used if needed.

1.8 To meet the requirements of this test method the thermal resistance of the test specimen shall be greater than 0.10 m²·K/W in the direction of the heat flow and edge heat losses shall be controlled, using edge insulation, or a guard heater, or both.

1.9 It is not practical in a test method of this type to try to establish details of construction and procedures to cover all contingencies that might offer difficulties to a person without pertinent technical knowledge. Thus users of this test method shall have sufficient knowledge to satisfactorily fulfill their needs. For example, knowledge of heat transfer principles, low level electrical measurements, and general test procedures is required.

1.10 The user of this method must be familiar with and understand the Annex. The Annex is critically important in addressing equipment design and error analysis.

1.11 Standardization of this test method is not intended to restrict in any way the future development of improved or new methods or procedures by research workers.

1.12 Since the design of a heat flow meter apparatus is not a simple matter, a procedure for proving the performance of an apparatus is given in **Appendix X3**.

¹ This test method is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.30 on Thermal Measurement.

Current edition approved Sept. 1, 2015. Published December 2015. Originally approved in 1963. Last previous edition approved in 2010 as C518-10. DOI: 10.1520/C0518-15.

² The boldface numbers in parentheses refer to the list of references at the end of this test method.

1.13 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.14 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

C167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations

C168 Terminology Relating to Thermal Insulation

C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

C236 Test Method for Steady-State Thermal Performance of Building Assemblies by Means of a Guarded Hot Box (Withdrawn 2001)⁴

C687 Practice for Determination of Thermal Resistance of Loose-Fill Building Insulation

C976 Test Method for Thermal Performance of Building Assemblies by Means of a Calibrated Hot Box (Withdrawn 2002)⁴

C1045 Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions

C1046 Practice for In-Situ Measurement of Heat Flux and Temperature on Building Envelope Components

C1058 Practice for Selecting Temperatures for Evaluating and Reporting Thermal Properties of Thermal Insulation

C1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus

E230/E230M Specification and Temperature-Electromotive Force (emf) Tables for Standardized Thermocouples

E178 Practice for Dealing With Outlying Observations

E456 Terminology Relating to Quality and Statistics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

2.2 ISO Standard:

ISO 8301:1991 Thermal Insulation—Determination of Steady-State Thermal Resistance and Related Properties—Heat Flow Meter Apparatus⁵

3. Terminology

3.1 *Definitions*—For definitions of terms and symbols used in this test method, refer to Terminology C168 and to the following subsections.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *calibration, n*—the process of establishing the calibration factor for a particular apparatus using calibration specimens having known thermal transmission properties.

3.2.2 *calibration transfer specimen, n*—(CTS) a thermal calibration specimen that has been measured by a national standards laboratory (7).

3.2.3 *cold surface assembly, n*—the plate that provides an isothermal boundary at the cold surface of the test specimen(s).

3.2.4 *controlled environment, n*—an environment sometimes employed in the apparatus to limit lateral heat flows.

3.2.5 *edge insulation, n*—auxiliary insulation used to limit lateral heat flows, these are sometimes permanently mounted in the apparatus.

3.2.6 *guard, n*—promotes one-dimensional heat flow. Primary guards are planar, additional coplanar guards can be used and secondary or edge guards are axial.

3.2.7 *heat flow meter apparatus, n*—the complete assemblage of the instrument, including hot and cold isothermal surfaces, the heat flux transducer(s), and the controlled environment if used, and instrumentation to indicate hot and cold surface temperatures, specimen thickness, and heat flux.

3.2.8 *hot surface assembly, n*—the plate that provides an isothermal boundary at the hot surface of the test specimen(s).

3.2.9 *heat flux transducer, n*—a device containing a thermopile, or an equivalent, that produces an output which is a function of the heat flux passing through it. The metering area usually consists of a number of differently connected temperature sensors placed on each face of a core and surface sheets to protect the assembly. A properly designed transducer will have a sensitivity that is essentially independent of the thermal properties of the specimen.

3.2.10 *metering area, n*—the area of the specimen(s) in contact with the sensor area of the heat flux transducer.

3.2.11 *secondary transfer standard, n*—a specimen, which has been measured in a heat flow meter apparatus, which has been calibrated with primary standards, used to calibrate additional apparatuses.

3.2.12 *sensitivity, n*—the ratio of the heat flux passing through the transducer to the electrical output of the heat flux transducer.

3.2.13 *standard reference material (SRM), n*—a lot of material that has been characterized by a national standards laboratory (7).

3.2.14 *thermal transmission properties, n*—those properties of a material or system that define the ability of the material or system to transfer heat. Properties, such as thermal resistance, thermal conductance, thermal conductivity, and thermal resistivity would be included, as defined in Terminology C168.

3.3 *Symbols and Units*—The symbols used in this test method have the following significance:

3.3.1 λ —thermal conductivity, $W/(m \cdot K)$.

3.3.2 C —thermal conductance, $W/(m^2 \cdot K)$.

3.3.3 R —thermal resistance, $(m^2 \cdot K)/W$.

3.3.4 q —heat flux (heat flow rate, Q , through area A), W/m^2 .

3.3.5 Q —heat flow rate in the metered area, W .

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

3.3.6 A —metering area, m^2 .

3.3.7 L —separation between the hot and cold plate assemblies during testing, m .

3.3.8 T_m —mean temperature, $(T_h + T_c)/2$, K .

3.3.9 ΔT —temperature difference across the specimen, K .

3.3.10 ρ —(bulk) density of the material tested, kg/m^3 .

3.3.11 S —calibration factor of the heat flux transducer, $(W/m^2)/V$.

3.3.12 E —heat flux transducer output, V .

3.3.13 T_h —temperature of the hot plate surface, K .

3.3.14 T_c —temperature of the cold plate surface, K .

3.4 *Subscripts:*

3.4.1 h —hot.

3.4.2 c —cold

3.4.3 a , b —first and second specimen.

3.4.4 m —mean.

3.4.5 α —statistical term used to define significance level.

4. Significance and Use

4.1 This test method provides a rapid means of determining the steady-state thermal transmission properties of thermal insulations and other materials with a high level of accuracy when the apparatus has been calibrated appropriately.

4.2 Proper calibration of the heat flow meter apparatus requires that it be calibrated using specimen(s) having thermal transmission properties determined previously by Test Methods C177, or C1114.

NOTE 1—Calibration of the apparatus typically requires specimens that are similar to the types of materials, thermal conductances, thicknesses, mean temperatures, and temperature gradients as expected for the test specimens.

4.3 The thermal transmission properties of specimens of a given material or product may vary due to variability of the composition of the material; be affected by moisture or other conditions; change with time; change with mean temperature and temperature difference; and depend upon the prior thermal history. It must be recognized, therefore, that the selection of typical values of thermal transmission properties representative of a material in a particular application should be based on a consideration of these factors and will not apply necessarily without modification to all service conditions.

4.3.1 As an example, this test method provides that the thermal properties shall be obtained on specimens that do not contain any free moisture although in service such conditions may not be realized. Even more basic is the dependence of the thermal properties on variables, such as mean temperature and temperature difference. These dependencies should be measured or the test made at conditions typical of use.

4.4 Special care shall be taken in the measurement procedure for specimens exhibiting appreciable inhomogeneities, anisotropies, rigidity, or especially high or low resistance to heat flow (see Practice C1045). The use of a heat flow meter apparatus when there are thermal bridges present in the specimen may yield very unreliable results. If the thermal bridge is present and parallel to the heat flow the results obtained may well have no meaning. Special considerations also are necessary when the measurements are conducted at

either high or low temperatures, in ambient pressures above or below atmospheric pressure, or in special ambient gases that are inert or hazardous.

4.5 The determination of the accuracy of the method for any given test is a function of the apparatus design, of the related instrumentation, and of the type of specimens under test (see Section 10), but this test method is capable of determining thermal transmission properties within $\pm 2\%$ of those determined by Test Method C177 when the ambient temperature is near the mean temperature of the test ($T(\text{ambient}) = T(\text{mean}) \pm 1^\circ\text{C}$), and in the range of 10 to 40°C . In all cases the accuracy of the heat flow meter apparatus can never be better than the accuracy of the primary standards used to calibrate the apparatus.

4.5.1 When this test method is to be used for certification testing of products, the apparatus shall have the capabilities required in A1.7 and one of the following procedures shall be followed:

4.5.1.1 The apparatus shall have its calibration checked within 24 h before or after a certification test using either secondary transfer standards traceable to, or calibration standards whose values have been established by, a recognized national standards laboratory not more than five years prior to the certification date. The average of two calibrations shall be used as the calibration factor and the specimen(s) certified with this average value. When the change in calibration factor is greater than 1 %, the standard specimen shall be retested and a new average calculated. If the change in calibration factor is still greater than 1 % the apparatus shall be calibrated using the procedure in Section 6.

4.5.1.2 Where both the short and long term stability of the apparatus have been proven to be better than 1 % of the reading (see Section 10), the apparatus may be calibrated at less frequent intervals, not exceeding 30 days. The specimens so tested cannot be certified until after the calibration test following the test and then only if the change in calibration factor from the previous calibration test is less than 1 %. When the change in calibration is greater than 1 %, test results from this interval shall be considered void and the tests repeated in accordance with 4.5.1.1.

4.5.2 The precision (repeatability) of measurements made by the heat flow meter apparatus calibrated as in Section 6.6 normally are much better than $\pm 1\%$ of the mean value. This precision is required to identify changes in calibration and is desirable in quality control applications.

5. Apparatus

5.1 The construction guidelines given in this section should be understood by the user of this test method. While it is mandatory that these details be followed carefully when constructing an apparatus, it behooves the user to verify that the equipment is built as specified. Serious errors of measurement may result from this oversight.

5.2 *General:*

5.2.1 The general features of a heat flow meter apparatus with the specimen or the specimens installed are described in Section 6 and shown in Figs. 1-3. A heat flow meter apparatus consists of two isothermal plate assemblies, one or more heat




FIG. 1 Apparatus with One Heat Flux Transducer and One Specimen




FIG. 2 Apparatus with One Heat Flux Transducer and Two Specimens




FIG. 3 Apparatus with Two Heat Flux Transducers and One Specimen

flux transducers and equipment to control the environmental conditions when needed. Each configuration will yield equivalent results if used within the limitations stated in this test method. There are distinct advantages for each configuration in practice and these are discussed in [Appendix X2](#).

NOTE 2—Further information can be found in ISO 8301:1991, which is the equivalent ISO standard for the Heat Flow Meter Apparatus.

5.2.2 Further design considerations such as plate surface treatment, flatness and parallelism, temperature requirements and measuring system requirements can be found in [Annex A1](#).

6. Calibration

6.1 The calibration of a heat flow meter apparatus is a very critical operation. Since lateral heat losses or gains of heat are not controlled or eliminated automatically, but only lessened by increasing the size of the guard area and edge insulation, there is no guarantee that the heat losses or gains are negligible under all testing conditions. To ensure that the equipment is performing properly with specimens of different thermal resistances, the apparatus shall be calibrated with materials

having similar thermal characteristics and thicknesses as the materials to be evaluated. The apparatus shall be calibrated with the specimen in the same orientation and the heat flux in the same direction under which the primary, CTS or SRM, or secondary transfer standards were characterized, if known. The material selected for the calibration standard shall have properties that are not affected by convection over the range of calibration parameters (temperature difference, thickness, density, and so forth) of interest. The apparatus shall be calibrated as a unit, with the heat flux transducer(s) installed in the apparatus.

6.2 This procedure applies to the calibration of a heat flow meter apparatus over a wide range of heat flow rates and temperatures, which permits the testing of a wide variety of insulation materials over an extended temperature range.

6.3 The following calibration procedure is used to compute the calibration factor, S for a heat flow meter apparatus, and must be used by anyone who desires to produce meaningful heat flux measurements from a heat flow apparatus.

6.4 Calibration Standards:

6.4.1 Calibration standards may be good for many years if handled carefully but shall be checked periodically to confirm lack of change.

6.4.2 It is recommended that the primary standards obtained from a national standards laboratory should not be used on a daily basis, but secondary or working standards should be produced. Create a record on the secondary standards with the following information.

6.4.2.1 Name of national laboratory to which it is traceable.

6.4.2.2 Date the secondary standard is produced.

6.4.2.3 Date the secondary standard is last tested.

6.4.2.4 Direction of heat flux during calibration.

6.4.2.5 Thermal value of the secondary standard.

6.4.2.6 Range of parameters for which it is valid.

6.4.2.7 Estimate of bias of the primary and secondary standards.

6.5 Calibration Procedure:

6.5.1 Calibrate the heat flow meter apparatus under the same conditions of plate temperatures, temperature gradient, specimen thickness, heat flow direction, and apparatus orientation as those for which data are available for the standard.

6.5.2 *Single Temperature Point*—If the calibration standard is tested at a single mean temperature, conduct the calibration and subsequent tests near the same mean temperature. Use engineering judgment or an error analysis to determine how closely the mean temperature must be maintained. As assessment of the sensitivity of the calibration standard to test conditions should be determined by the user of the transfer standard to determine its limitations of use.

6.5.3 *Multiple Temperature Points*—If the calibration standard is tested at three or more mean temperatures, calibrate the heat flow meter apparatus at the same temperatures using the same temperature gradients (8). A smooth curve can be fitted to the points such that a calibration factor can be interpolated for any given mean temperature. It is not permissible to extrapolate above or below the mean temperature range of the

calibration standard measurements. Changing the plate temperature of a heat flow meter apparatus has the potential of changing apparatus calibration. When changing plate temperatures, take steps to determine if the heat flux transducer calibration factor has changed.

6.5.4 Single Thickness Point—If the original calibration standard is tested at only one thickness, the heat flow meter apparatus can be calibrated for that thickness without an exhaustive thickness study. If tests are to be conducted at thicknesses other than the calibrated thickness, make a thorough study of the error of the heat flow meter apparatus at other thicknesses. Several references on this subject are listed at the end of this test method (4, 7, 8-12, 13, 14).

6.5.5 Multiple Thickness Points—If the original standard is tested at three or more thicknesses, the heat flow meter apparatus can be calibrated over the same thickness range. A smooth curve can be fitted to the points such that a calibration factor can be interpolated for any given thickness. If tests are to be conducted at thicknesses above or below the calibrated thicknesses, make a thorough study of the error of the heat flow meter apparatus at these thicknesses.

6.6 Calibration of Various Designs:

6.6.1 There are several configurations of heat flow meter apparatuses that use one or two heat flux transducers and one or two specimens in the apparatus. While it is not practical to list all of the possible combinations of apparatus and specimen configurations, this section contains the equations for calculating the calibration factor of three common apparatuses. The calibration and testing configuration should be identical. The calibration factor of a heat flow meter apparatus is determined by running the same standard specimens a number of times, not consecutively, but over a period of time with the standard removed each time.

6.6.2 One Calibration Standard—Apparatus with one heat flux transducer and one standard (see Fig. 1).

$$S = C \cdot (T_h - T_c) / E \quad (1)$$

6.6.3 Two Calibration Standards—Apparatus with one heat flux transducer and one specimen configuration (same as that for 6.6.2).

6.6.3.1 The two calibration standards need to be the same thickness and of similar material but need not be identical. With the following equation, it is not necessary to know the thermal conductance of each calibration standard, but it is necessary to know the average thermal conductance of the two standards:

$$S = \frac{C_a + C_b}{\left(\frac{E_a}{(T_{ha} - T_{ca})} + \frac{E_b}{(T_{hb} - T_{cb})} \right)} \quad (2)$$

6.6.3.2 Two Calibration Standards—Apparatus with one heat flux transducer and two specimens (see Fig. 2).

6.6.3.3 Again, the standards need to be the same thickness and of similar material but not necessarily identical.

$$S = \frac{C_a + C_b}{E \cdot \left(\frac{1}{(T_{ha} - T_{ca})} + \frac{1}{(T_{hb} - T_{cb})} \right)} \quad (3)$$

6.6.4 One Calibration Standard—Apparatus with two heat flux transducers and one specimen (see Fig. 3).

6.6.4.1 Assuming the two transducers physically are identical and have similar outputs, one can sum the outputs of the two transducers and then calibrate as a single transducer apparatus. In this case, it is very important to keep the mean temperature and the plate temperatures equal to those used in testing the standard. It is essential that each of the transducers be at steady state.

$$S = \frac{C \cdot (T_h - T_c)}{(E_1 + E_2)} \quad (4)$$

6.6.4.2 In the case where multiple transducers are used, a similar calculation can be utilized to calculate the calibration factor.

6.6.4.3 As an alternative, each heat flux transducer can be calibrated as an independent apparatus as in 6.6.1.

7. Test Procedures

7.1 Foreword on Testing Procedures—The relative simplicity of this test method may lead one to overlook very important factors, which may affect the results. To ensure accurate measurement, the operator shall be instructed fully in the operation of the equipment. Furthermore, the equipment shall be calibrated properly with reference materials having similar heat transfer characteristics. Also it is necessary that the specimen be prepared properly for evaluation.

7.2 Sampling and Preparation of Specimens:

7.2.1 Test Specimens—One- or two-piece specimens may be used, depending on the configuration selected for the test. Where two pieces are used, they shall be selected from the same material to be essentially identical in construction, thickness, and density. For loose fill materials, the method specified in the material specification or in Practice C687 shall be used to produce a specimen or specimens of the desired density.

7.2.2 Selection of Specimens—The specimen or specimens shall be of such size as to cover the plate assembly surfaces and shall either be of the actual thickness to be applied in use or of sufficient thickness to give a true average representation of the material to be tested. If sufficient material is not available, the specimen shall at least cover the metering area, and the rest of the plate surfaces must be covered with a mask with a thermal conductivity as close to that of the specimen as possible.

7.3 Specimen Conditioning—Details of the specimen selection and conditioning preferably are given in the material specification. Where such specifications are not given, the specimen preparation shall be conducted in accordance with the requirement that materials shall not be exposed to temperatures that will change the specimens in an irreversible manner. Typically, the material specifications call for specimen conditioning at 22°C and 50 % R.H. for a period of time until less than a 1 % mass change is observed over a 24-h period. For some materials, such as cellulose, considerably longer times may be required for both conditioning and testing.

7.4 Specimen Preparation:

7.4.1 Use the following guidelines when the material specification is unavailable. In general, the surfaces of the specimen

should be prepared to ensure that they are parallel with and have uniform thermal contact with the hot and cold plates.

7.4.2 Compressible Specimens—The surfaces of the uncompressed specimens may be comparatively uneven so long as surface undulations are removed under test compression. It may be necessary to smooth the specimen surfaces to achieve better plate-to-specimen contact. If the apparent thermal conductivity of the contact void is greater than that of the specimen, compressible or otherwise, the measured heat flux will be greater than the heat flux that would be obtained if the voids were absent. This may often be the case at higher temperatures where radiant heat transfer predominates in the void. For the measurement of compressible specimens, the temperature sensors are often mounted directly in the plate surfaces. Also, plate spacers may be required for the measurement of compressible specimens.

7.4.3 Rigid and High Conductance Specimens—The measurement of rigid specimens or high conductance specimens requires careful surface preparation. First, the surfaces should be made flat and parallel to the same degree as the heat-flowmeter. If the specimen has a thermal resistance that is sufficiently high compared to the specimen-to-plate interface resistance, temperature sensors mounted in the plates may be adequate.

7.5 Measurements on Specimens:

7.5.1 Blanket and Batt-Type Materials—When specified, the test thickness of blankets and batt-type materials shall be determined before testing in accordance with Test Methods **C167**, provided that good contact is maintained between the specimen and the isothermal plates. Also, it is recommended highly that the thickness during the actual test be measured. At the conclusion of the test, the density in the metering area should be determined.

7.5.2 Loose-fill Materials—These materials generally are tested in open test frames as spelled out in Practice **C687**. The requirement to measure the density in the metering area is again critical.

7.6 Limitations on Specimen Thickness:

7.6.1 General—The combined thickness of the specimen or specimens, the heat flux transducer and any damping material, which in total equals the distance between the cold and hot plates, must be restricted in order to limit the effect of edge losses on the measurements. In addition edge losses are affected by the edge insulation and the ambient temperature, so the requirements on both of these parameters must be met.

7.6.2 Maximum Spacing Between Hot and Cold Plates—The maximum allowable distance between the hot and cold plates during a test, is related to the dimensions of the heat flux transducer, the metering area, the size of the plate assembly, the construction of the heat meter apparatus, and the properties of the specimen. No suitable theoretical analysis is available to predict the maximum allowable thickness of specimens. It is possible to use the results of an analysis for a similarly sized guarded hot plate as a guide (**15, 16-17**).

7.7 Procedure of Measurement:

7.7.1 Temperature Difference—For any test, make the temperature difference across the specimen not less than 10 K. For

specimens that are expected to have a large thermal resistance, a larger temperature difference in the specimen is recommended (see Practice **C1058** for the selection of the plate temperatures). The actual temperature difference or gradient is best specified in the material specifications or by agreement of the parties concerned.

7.7.2 Edge Insulation—Enclose the edges of the specimens with thermal insulation to reduce edge heat losses to an acceptable level if this edge insulation is not built into the apparatus (see **A1.6**).

7.7.3 Settling Time and Measurement Interval—Verify the existence of thermal equilibrium by observing and recording, the emf output of the heat flux transducer, the mean temperature of the specimens, the temperature drop across the specimen, and a calculated λ value. Make observations at time intervals of at least 10 min until five successive observations yield values of thermal conductivity, which fall within ½ % of the mean value for these five readings. If the five readings show a monotonically increasing or decreasing trend, equilibrium has not been attained. In this case, additional sets of readings shall be taken. If experience has shown that a shorter time interval may be used, follow the same criteria for stability. For high density specimens ($\rho > 40 \text{ kg/m}^3$) or for low conductance specimens ($C < 0.05 \text{ W/K}\cdot\text{m}^2$) the time between readings may have to be increased to 30 min or longer (**18**).

8. Calculation

8.1 Density and Change in Mass—When required, calculate the density of the dry specimen as tested, ρ , the mass change due to conditioning of the material, and the mass change of the specimen during test.

8.1.1 Density of Batt and Blanket Specimens—It has been found that it is important to measure the mass of the specimens in contact with the metering area. The area of the specimen directly measured shall be cut out and its mass determined after testing, unless the specimen must be retained for further testing.

8.2 Thermal Properties for One Specimen—When only one specimen is used, calculate the thermal conductance of the specimen as follows:

$$C = S \cdot E / \Delta T \quad (5)$$

and where applicable, calculate the thermal conductivity, as follows:

$$\lambda = S \cdot E \cdot (L / \Delta T) \quad (6)$$

8.3 Thermal Properties for Two Specimens—When two specimens are used, calculate the total thermal conductance, C , as follows:

$$C = S \cdot E / (\Delta T_a + \Delta T_b) \quad (7)$$

The λ factor, that is, the average thermal conductivity of the specimen is calculated as follows:

$$\lambda_{ave} = (S \cdot E / 2) \cdot (L_a + L_b) / (\Delta T_a + \Delta T_b) \quad (8)$$

where the subscripts refer to the two specimens.

8.4 Other derived thermal properties may be calculated but only under the provisions given in Practice **C1045**.