

SLOVENSKI STANDARD

SIST EN ISO 15463:2004

01-maj-2004

Xi gkf]U'nUdfYXYUj c'bUZY]b'nYa Y'g_Y[Ud]bU!HYfYbg]dfY['YX'bcj]\nUy]jb] \ zdfc]nj cXb] \ fKj jyb] \ L]b'j fHJb] \ YYa Ybhcj fGc'%' (* .8\$\$' L

Petroleum and natural gas industries - Field inspection of new casing, tubing and plain-end drill pipe (ISO 15463:2003)

Erdöl- und Erdgasindustrie - Feld-Abnahme von neuen Futterrohren, Steigrohren und glattendigen Bohrrohren (ISO 15463:2003)

STANDARD PREVIEW

(standards.iteh.ai)

Industries du pétrole et du gaz naturel - Contrôle sur parc ou sur chantier des tubes de cuvelage, des tubes de production et des tiges de forage a extrémités lisses (ISO 15463:2003)

<https://standards.iteh.ai/catalog/standards/sist/ab17dfd9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

Ta slovenski standard je istoveten z: EN ISO 15463:2003

ICS:

75.180.10	Oprema za raziskovanje in odkopavanje	Exploratory and extraction equipment
-----------	---------------------------------------	--------------------------------------

SIST EN ISO 15463:2004

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 15463:2004
<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 15463

December 2003

ICS 75.180.10

English version

**Petroleum and natural gas industries - Field inspection of new
casing, tubing and plain-end drill pipe (ISO 15463:2003)**

Industries du pétrole et du gaz naturel - Contrôle sur parc
ou sur chantier des tubes de cuvelage, des tubes de
production et des tiges de forage à extrémités lisses (ISO
15463:2003)

This European Standard was approved by CEN on 2 December 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 15463:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4fle-a0f1-f10b548b08c3/sist-en-iso-15463-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN ISO 15463:2003 (E)

Foreword

This document (EN ISO 15463:2003) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum and natural gas industries", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by June 2004.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

NOTE FROM CMC The foreword is susceptible to be amended on reception of the German language version. The confirmed or amended foreword, and when appropriate, the normative annex ZA for the references to international publications with their relevant European publications will be circulated with the German version.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 15463:2003 has been approved by CEN as EN ISO 15463:2003 without any modifications.

SIST EN ISO 15463:2004

<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

INTERNATIONAL STANDARD

ISO
15463

First edition
2003-12-15

Petroleum and natural gas industries — Field inspection of new casing, tubing and plain-end drill pipe

*Industries du pétrole et du gaz naturel — Contrôle sur parc ou sur
chantier des tubes de cuvelage, des tubes de production et des tiges
de forage à extrémités lisses*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 15463:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>



Reference number
ISO 15463:2003(E)

© ISO 2003

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 15463:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/ab17dfd9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	vi
Introduction	vii
1 Scope	1
2 Conformance	1
2.1 Normative references	1
2.2 Units of measurement	1
2.3 Tables and figures	2
3 Normative references	2
4 Terms, definitions, symbols and abbreviated terms	2
4.1 Terms and definitions	2
4.2 Symbols and abbreviated terms	13
5 Application	15
5.1 Basis for inspection	15
5.2 Applicability of inspections	15
5.3 Repeatability of results	15
5.4 Consequences of variability	15
6 Ordering information	16
7 Quality assurance	16
8 Qualification of inspection personnel <small>SIST EN ISO 15463:2004</small>	17
8.1 General	17
8.2 Written procedure	17
8.3 Qualification of inspection personnel	17
8.4 Training programs	18
8.5 Examinations	18
8.6 Experience	18
8.7 Requalification	18
8.8 Documentation	18
8.9 NDT personnel certification	19
9 General inspection procedures	19
9.1 General	19
9.2 Documents at job site	19
9.3 Pre-inspection procedures	19
9.4 Records and notification	19
9.5 Post-inspection procedures	20
9.6 Job site checklist	21
9.7 Documentation	21
10 Acceptance criteria, disposition and responsibility	21
10.1 General	21
10.2 Basis for acceptance	21
10.3 Responsibility for Rejections	21
11 Visual and dimensional inspection	22
11.1 General	22
11.2 Application	22
11.3 Drift mandrels	22
11.4 Precision callipers (micrometer, vernier calliper or dial calliper)	22
11.5 Length and diameter-measuring devices (steel rules, steel length or diameter-measuring tapes, and other non-adjustable measuring devices)	22

11.6	Depth gauges	22
11.7	External surface illumination	23
11.8	Internal surface illumination	23
11.9	Full-length visual inspection (FLVI) of new OCTG	24
11.10	Outside diameter verification	24
11.11	Straightness	24
11.12	Drift testing	25
11.13	Visual thread inspection (VTI)	26
12	Hardness testing	29
12.1	General	29
12.2	Application	29
12.3	Equipment	30
12.4	Calibration	30
12.5	Standardization	30
12.6	Procedures	31
13	Magnetic particle inspection (MPI)	31
13.1	General	31
13.2	Application	32
13.3	Equipment and materials	32
13.3.1	Internal conductors	32
13.4	Magnetic particles	33
13.5	Illumination equipment and optical aids	33
13.6	General procedures	34
13.7	Calibration	34
13.8	Standardization	35
13.9	Periodic checks	35
13.10	End area inspection (SEA)	36
13.11	Inspection of unattached couplings (UCMPI)	37
13.12	Full-length magnetic particle inspection (FLMPI)	38
14	Electromagnetic inspection (EMI)	38
14.1	General	38
14.2	Equipment	39
14.3	Application	39
14.4	Calibration	39
14.5	Standardization	40
14.6	Equipment requirements and periodic checks	42
14.7	Inspection procedure	42
15	Residual magnetism and demagnetization	42
15.1	General	42
15.2	Application	43
15.3	Services	43
16	Gamma-ray wall thickness inspection	44
16.1	General	44
16.2	Application	44
16.3	Equipment	44
16.4	Calibration and standardization	44
16.5	Inspection procedure	45
17	Electromagnetic grade comparison	45
17.1	General	45
17.2	Application	45
17.3	Equipment	45
17.4	Calibration and Standardization	45
17.5	Inspection procedure	46
18	Ultrasonic inspection	46
18.1	General	46
18.2	Application	47

18.3	General procedures for calibration, standardization, and inspection	47
18.4	Inspection for longitudinal, transverse, and oblique imperfections	48
18.5	Standardization	49
18.6	Procedure for the detection of longitudinal, transverse, and oblique imperfections	49
18.7	Inspection of the body wall for wall thinning	49
18.8	Ultrasonic inspection of longitudinal welds	50
18.9	Manual ultrasonic thickness gauging	52
18.10	Manual ultrasonic shear-wave inspection	54
19	Evaluation of imperfections and deviations	55
19.1	General	55
19.2	Application	55
19.3	Equipment	55
19.4	Calibration and standardization procedures	56
19.5	Procedure for evaluating outside-surface-breaking pipe body imperfections	56
19.6	Procedure for evaluating inside-surface-breaking pipe body imperfections	58
19.7	Procedure for evaluating welds	58
19.8	Procedure for evaluating grinds	59
19.9	Procedure for evaluating large-area wall reduction	59
19.10	Procedure for evaluating imperfections in upsets	60
19.11	Procedure for evaluation of outside surface imperfections on couplings	61
19.12	Procedure for evaluation of visually-located thread imperfections	61
19.13	Procedure for triangle location and coupling makeup position	64
19.14	Procedure for evaluating straightness	64
19.15	Procedure for evaluating pipe diameter	65
20	Hydrostatic pressure testing	65
20.1	General	65
20.2	Application	66
20.3	Equipment, safety, and general procedures	66
20.4	Equipment calibration	67
20.5	Operating procedure	67
	SIST EN ISO 15463:2004 https://standards.iteh.ai/catalog/standards/sist/ab17dfd9-5d22-4fle-a0f1-1f0b548b08c3/sist-en-iso-15463-2004	
21	Marking	68
21.1	General	68
21.2	Authority	69
21.3	Guidelines	69
21.4	Marking of prime OCTG	70
21.5	Marking of no-drift OCTG	70
21.6	Marking of conditioned OCTG	70
21.7	Marking of conditionable OCTG (still to be conditioned)	71
21.8	Marking of non-conditionable OCTG (rejects)	71
21.9	Marking of OCTG not meeting ISO/API standards for hardness	71
21.10	Marking of prime couplings and connectors	72
21.11	Marking of conditioned couplings and connectors	72
21.12	Marking of conditionable couplings and connectors (still to be conditioned)	72
21.13	Marking of non-conditionable couplings and connectors (rejects)	72
Annex A (normative)	Tables in SI units	74
Annex B (normative)	Figures	91
Annex C (normative)	Tables in USC units	96
Bibliography	112	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15463 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 5, *Casing, tubing and drill pipe*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 15463:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

Introduction

This International Standard is provided for field inspection and testing of OCTG; it is not intended to restrict the agency or owner from using personal judgement and supplementing the specified inspections with other techniques, extending existing techniques, or re-inspecting certain lengths of OCTG.

Users of this International Standard should be aware that further or differing requirements might be needed for individual applications. This International Standard is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology. Where an alternative is offered, the vendor should identify any variations from this International Standard and provide details.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 15463:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 15463:2004

<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4f1e-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

Petroleum and natural gas industries — Field inspection of new casing, tubing and plain-end drill pipe

1 Scope

This International Standard specifies requirements and gives recommendations for field inspection and testing of oil country tubular goods (OCTG). This International Standard covers the practices and technology commonly used in field inspection; however, certain practices may also be suitable for mill inspections.

This International Standard covers the qualification of inspection personnel, a description of inspection methods and apparatus calibration and standardization procedures for various inspection methods. The evaluation of imperfections and marking of inspected OCTG are included.

This International Standard is applicable to field inspection of OCTG and is not applicable for use as a basis for acceptance or rejection (for which the relevant purchasing specification is applicable, see 5.4.2).

2 Conformance

2.1 Normative references

In the interests of worldwide application of this International Standard, ISO/TC 67 has decided, after detailed technical analysis, that certain of the normative documents listed in Clause 3 and prepared by ISO/TC 67 or other ISO Technical Committee are interchangeable in the context of the relevant requirement with the relevant document prepared by the American Petroleum Institute (API), the American Society for Testing and Materials (ASTM) or the American National Standards Institute (ANSI). These latter documents are cited in the running text following the ISO reference and preceded by "or", for example "ISO XXXX or API YYYY". Application of an alternative normative document cited in this manner may lead to technical results different from the use of the preceding ISO reference. However, both results are acceptable and these documents are thus considered interchangeable in practice.

NOTE ISO 11960 has been back-adopted by API as API Spec 5CT. Therefore, for the purposes of the provisions in this International Standard which cite ISO 11960, API Spec 5CT is equivalent to ISO 11960.

2.2 Units of measurement

In this International Standard, data are expressed in both the International system (SI) of units and the United States Customary (USC) system of units. For specific field inspection and testing, it is intended that only one unit system be used, without combining data expressed in the other system.

Inspection and testing performed using either of these unit systems shall be considered equivalent and totally interchangeable. Consequently, compliance with the requirements of the relevant Product Standard expressed in one of the unit systems provides compliance with the requirements expressed in the other system.

For data expressed in the SI, a comma is used as the decimal separator and a space as the thousands separator. For data expressed in the USC system, a dot (on the line) is used as the decimal separator and a space as the thousands separator.

In the text, data in SI units are followed by data in USC units in brackets.

2.3 Tables and figures

Separate tables for data expressed in SI units and USC units are given in Annex A and Annex C, respectively. For a specific order item, only one unit system shall be used.

In this International Standard, cross-references are made only to the tables in Annex A; if the USC units apply on an order, then any cross-references to tables in Annex A shall be taken to mean the equivalent table in Annex C.

Figures (data expressed in both SI and USC units) are contained in Annex B.

3 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10405:2000, *Petroleum and natural gas industries — Care and use of casing and tubing*

ISO 11960:2001 (including Technical Corrigendum 1:2002), *Petroleum and natural gas industries — Steel pipes for use as casing or tubing for wells*

ISO 11961:1996, *Petroleum and natural gas industries — Steel pipes for use as drill pipe — Specification*

ISO 13678, *Petroleum and natural gas industries — Evaluation and testing of thread compounds for use with casing, tubing and line pipe*

API RP 5A3¹⁾, *Thread compounds for casing, tubing and line pipe*

API Spec 5B, *Threading, gauging and thread inspection of casing, tubing and line pipe threads*
<https://standards.iteh.ai/catalog/standards/sist/ab17dfd9-5d22-4fle-a0f1-0051802310-00000000000000000000000000000000>

API RP 5B1, *Threading, gauging and inspection of casing, tubing, and line pipe threads*

API RP 5C1:1999, *Care and use of casing and tubing*

API Spec 5D:2001, *Specification for drill pipe*

API Std 5T1, *Imperfection terminology*

4 Terms, definitions, symbols and abbreviated terms

4.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

4.1.1

A-scan

data presentation utilizing a horizontal base line that indicates distance, or time, and a vertical deflection from the base line that indicates amplitude

4.1.2

AC-field

magnetic field induced by alternating current

1) American Petroleum Institute; 1220 L Street NW, Washington DC, 20005, USA

4.1.3**agency**

entity contracted to inspect new OCTG using the methods and criteria specified

4.1.4**ampere-turn**

unit of magnetomotive force which is the product of the number of turns in a coil and the quantity of amperes of current flowing through it, representing the magnetizing strength of the coil

EXAMPLE 800 A in a 6-turn coil gives 4 800 ampere-turns.

4.1.5**arc, verb**

create intense heat and light by passing an electric current across a gap

4.1.6**back-wall reflection**

ultrasonic signal received from the back surface of the pipe wall

4.1.7**black-crested thread**

non-full-crested thread whose original (black) mill surface has not been completely removed

4.1.8**black light**

long-wave ultraviolet light (UV-A) with a wavelength between 320 nm and 400 nm

4.1.9**borescope**

optical instrument with an illuminating lamp, used for inspecting the inside surface of OCTG

SIST EN ISO 15463:2004

<https://standards.iteh.ai/catalog/standards/sist/ab17df9-5d22-4fle-a0f1-f10b548b08c3/sist-en-iso-15463-2004>

4.1.10**box**

internally-threaded end of integral-joint OCTG, or the coupling end of threaded-and-coupled OCTG

4.1.11**calibration**

comparison of an instrument with, or the adjustment of an instrument to, a known reference(s) standard that is often traceable to a national institute such as the National Institute of Standards and Technology

4.1.12**casing**

steel pipe used in oil wells to seal off fluids from the bore hole and to prevent the walls of the hole from sloughing off or caving in

4.1.13**central conductor**

conductor that is passed through the bore of OCTG in order to create a circular or circumferential magnetic field in the OCTG

NOTE

This does not imply that the current rod is necessarily centred in the bore of the OCTG.

4.1.14**chamfer**

conical surface at the end of pipe having round or buttress threads

4.1.15**chatter**

wavy surface of the thread flank, root, crest, or chamfer, caused by a vibrating cutter insert