



Designation: ~~D6659~~—~~10~~ D6659 – 10 (Reapproved 2015)

## Standard Practice for Sampling and Preparation of Wet Blue for Physical and Chemical Tests<sup>1</sup>

This standard is issued under the fixed designation D6659; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice covers the sampling and preparation of wet blue for physical and chemical tests. The product is grouped into lots that are randomly sampled in such a manner as to produce a representative sample of the lot. This sample may be used to determine compliance of the lot with applicable specification requirements, and on the basis of results, the lot may be accepted or rejected in its entirety.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**D6658** Test Method for Volatile Matter (Moisture) of Wet Blue by Oven Drying

### 3. Terminology

3.1 *Definitions:*

3.1.1 *lot (or batch), n*—units of products from a single type, grade, class, size, and composition, manufactured under essentially the same conditions and time.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.02 on Wet Blue.

Current edition approved Oct. 1, 2010/Dec. 1, 2015. Published October 2010/December 2015. Originally approved in 2001. Last previous edition approved in 2008/2010 as D6659-08. DOI: 10.1520/D6659-10; — 10. DOI: 10.1520/D6659-10R15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

#### 3.1.1.1 Discussion—

Wet blue in formed lots should be produced from: (1) Units of product of similar size and type. (2) Chromium tanning material obtained from the same producer (or functionally equivalent). (3) A single product method. (4) Sequential production batches.

3.1.2 *unit, n*—a piece of wet blue in the form in which it is purchased, such as a single hide, skin, or any part thereof.

### 4. Significance and Use

4.1 The sampling procedures described in this practice have been designed to ensure random sampling of wet blue for physical and chemical tests. Wet blue is a natural product and as such is subject to extensive variability. The physical and chemical properties vary considerably depending on location on the hide, side, or skin from which the test sample is taken. Random sampling of specimens from a predefined location and orientation minimizes test bias and variability. This practice defines these parameters.

### 5. Conditioning

5.1 Unless otherwise specified in the applicable test method, specification, or procurement document, samples shall be tempered to the ambient laboratory conditions prior to preparation of testing.