



Designation: F2215 – 15

Standard Specification for Balls, Bearings, Ferrous and Nonferrous for Use in Bearings, Valves, and Bearing Applications¹

This standard is issued under the fixed designation F2215; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers requirements for ferrous and nonferrous inch balls. The balls covered in this specification are intended for use in bearings, bearing applications, check valves, and other components using balls.

1.2 This is a general specification. The individual item requirements shall be as specified herein in accordance with the MS sheet standards. In the event of any conflict between requirements of this specification and the MS sheet standards, the latter shall govern.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 This specification contains many of the requirements of MIL-B-1083, which was originally developed by the Department of Defense and maintained by the Defense Supply Center Richmond.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A108 Specification for Steel Bar, Carbon and Alloy, Cold-Finished](#)

[A276 Specification for Stainless Steel Bars and Shapes](#)

[A295 Specification for High-Carbon Anti-Friction Bearing Steel](#)

[B21/B21M Specification for Naval Brass Rod, Bar, and Shapes](#)

[B124/B124M Specification for Copper and Copper Alloy Forging Rod, Bar, and Shapes](#)

[B276 Test Method for Apparent Porosity in Cemented Carbides](#)

[B283 Specification for Copper and Copper-Alloy Die Forgings \(Hot-Pressed\)](#)

[D3951 Practice for Commercial Packaging](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E112 Test Methods for Determining Average Grain Size](#)

[E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings](#)

[E384 Test Method for Knoop and Vickers Hardness of Materials](#)

2.2 *ASTM Adjunct:*³

[ADJE0381 ASTM Adjuncts: Photographs for Rating Macroetched Steels \(3 Plates\) Plate I, Plate II, and Plate III](#)

2.3 *ABMA Standard:*⁴

[ABMA-STD-10 Metal Balls \(Inactive Specification\)](#)

2.4 *ANSI Standards:*⁵

[ANSI B46.1 Surface Texture \(Surface Roughness, Waviness and Lay\)](#)

[ANSI B89.3.1 Sampling Procedures and Tables for Inspection by Attributes](#)

[ANSI/ASQC Z1.4 Sampling Procedures and Tables for Inspection by Attributes](#)

2.5 *Federal Standards:*⁶

[FED-STD-151 Metals, Test Methods](#)

[QQ-N-286 Specification for Nickel-Copper Aluminum Alloy, Wrought](#)

¹ This specification is under the jurisdiction of ASTM Committee F34 on Rolling Element Bearings and is the direct responsibility of Subcommittee F34.01 on Rolling Element.

Current edition approved June 1, 2015. Published December 2015. Originally approved in 2002. Last previous edition approved in 2005 as F2215 – 05^{ε2}. DOI: 10.1520/F2215-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from ASTM International Headquarters. Order Adjunct No. ADJE0381

⁴ Available from the Anti-Friction Bearing Manufacturers' Association, Inc., 1101 Connecticut Ave., N.W., Suite 700, Washington, DC 20036.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁶ DLA Document Services Building 4/D 700 Robbins Avenue Philadelphia, PA 19111-5094 <http://quicksearch.dla.mil/>

2.6 ISO Standard:⁵

ISO 3290 Rolling Bearings, Bearing Parts, Balls for Rolling Bearings

2.7 Military Standards:⁶

MIL-B-1083 Military Specification: Balls, Bearing, Ferrous and Non-Ferrous (for Use in Bearings, Valves And Bearing Applications) General Specification for

MIL-DTL-197 Packaging of Bearings, Associated Parts and Subassemblies

MIL-STD-129 Marking for Shipment and Storage

2.8 NAS Standard⁷:

NAS 410 Certification and Qualification of Nondestructive Test Personnel

2.9 SAE Standards:⁸

AMS 5618 Steel, Corrosion Resistant Bars, Wire and Forgings

AMS 5630 Steel, Corrosion Resistant Bars, Wire and Forgings

AMS 5749 Steel, Corrosion Resistant Bars, Wire and Forging and Tubing Premium Aircraft Quality for Bearing Applications

AMS 5880 Steel, Corrosion Resistant Bars, Wire and Forging for Bearing Applications

AMS 6440 Specification for Steel Bars, Forgings and Tubing 1.45Cr (0.98-1.10C) (SAE 52100) for Bearing Applications

AMS 6444 Specification for Steel Bars, Forgings and Tubing Premium Aircraft Quality for Bearing Applications

AMS 6490 Specification for Steel Bars, Forgings and Tubing

AMS 6491 Specification for Steel Bars, Forgings and Tubing 4.1Cr-4.2Mo-1.0V (0.80-0.85C) Premium Aircraft-Quality for Bearing Applications, Double Vacuum Melted

3.1.7 *lot*—balls from a single production run of balls that are offered for delivery at one time that are of the same dimensions, made from metal material of the same type and composition, formed and fabricated under the same manufacturing processes.

3.1.8 *marking increments*—standard unit steps to express the specific diameter.

3.1.9 *nominal size (D_w)*—basic diameter, in inches, that is used for the purpose of general identification (for example, 1/16, 1/8, and so forth).

3.1.10 *out-of-roundness*—difference between the largest diameter and the smallest diameter measured on the same ball.

3.1.11 *passivation*—treatment for corrosion-resistant steel to eliminate corrodible surface impurities and provide a protective film.

3.1.12 *specific diameter*—diameter marked on the unit container and expressed in the grade standard marking increment nearest to the average diameter of the balls in that container.

3.1.13 *unit container*—container identified as containing balls from the same manufacturing lot of the same composition, grade, and basic diameter, and within the allowable diameter variation per unit container for the specified grade.

3.2 Acronyms:

3.2.1 *CEVM*—consumable electrode vacuum melted.

3.2.2 *VIMVAR*—vacuum induction melt-vacuum arc remelt.

4. Classification

4.1 This specification covers balls of Compositions 1 through 16 (see **Table 1**), and Grades 3, 5, 10, 16, 24, 48, 100, 200, 500 and 1000 (see **3.1.6**).

5. Ordering Information

5.1 When ordering balls in accordance with this specification, specify the following:

5.1.1 ASTM designation number, including year of issue,

5.1.2 Applicable MS sheet standard number,

5.1.3 Diameter of balls, whether standard or nonstandard,

5.1.4 Composition number required (see **Table 1**),

5.1.5 Grade required (see ISO 3290),

5.1.6 Whether a first article sample is required, and arrangements for testing and approval thereof,

5.1.7 Tests, test conditions, and sampling plans, if other than specified herein,

5.1.8 Quantity required,

5.1.9 Applicable levels of preservation and packing,

5.1.10 Special marking, if required, and

5.1.11 For Composition 13 balls, traceability records for each ball when required, including its corresponding heat treat lot, forging lot, consumable electrode remelt number, process lot number, and VIMVAR heat of steel,

5.1.11.1 Material identification records, when required,

5.1.11.2 Eddy current inspection records, when required, and

5.1.11.3 Ultrasonic inspection record for bar stock material, when required.

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *ball gage deviation (ΔS)*—difference between the lot mean diameter and the sum of the nominal diameter and the ball gage.

3.1.2 *basic diameter*—diameter size of the balls, in inches.

3.1.3 *basic diameter tolerance*—maximum allowable deviation from the specified basic diameter for the indicated grade.

3.1.4 *case depth*—thickness, measured radially from the surface of the hardened case to a point where carbon content or hardness becomes the same as the ball core.

3.1.5 *deviation from spherical form (ΔR_w)*—greatest radial distance in any radial plane between a sphere circumscribed around the ball surface and any point on the ball surface.

3.1.6 *grade designation (G)*—indicates the allowable out-of-roundness expressed in millionths of an inch.

⁷ Available from Global Engineering Documents, 15 Inverness Way, East Englewood, CO 80112-5704, <http://www.global.ihs.com>.

⁸ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

TABLE 1 Classification of Balls

Composition Number	Composition
1	chrome alloy steel (52100)
2	corrosion-resistant hardenable steel (400 series)
3	carbon steel
4	silicon molybdenum steel
5	Brass
6	Bronze
7	aluminum bronze
8	beryllium copper alloy
9	nickel-copper alloy (Monel)
10	nickel-copper-aluminum alloy (K-Monel)
11	aluminum alloy
12	tungsten carbide
13	premium quality bearing steel (double vacuum melted M-50)
14	corrosion resistant austenitic steel (300 series)
15	premium aircraft quality chrome alloy steel (52100 CEVM)
16	premium aircraft quality corrosion resistant alloy steel (440C VIMVAR)

6. Materials and Manufacture

6.1 *Composition 1*—Composition 1 balls shall be manufactured from chrome alloy steel conforming to the chemical composition of UNS G52986 in accordance with AMS 6440. Chemical composition shall be tested in accordance with 11.2.

6.2 *Composition 2*—Composition 2 balls shall be manufactured from corrosion-resistant steel conforming to the chemical composition of UNS S44003, UNS S32900, UNS S42000, UNS S41000, UNS S42700, or UNS S44004 in accordance with Specification A276 and AMS 5618, 5630, 5749 and 5880. Chemical composition shall be tested in accordance with 11.2.

6.3 *Composition 3*—Composition 3 balls shall be manufactured from carbon steel conforming to the chemical composition of UNS G10080 through UNS G10220 in accordance with Specification A108. Chemical composition shall be tested in accordance with 11.2.

6.3.1 The quality of the material used in the manufacture of Composition 3 balls shall have macrograph inspection in accordance with Test Methods E381 and ASTM Adjunct ADJE0381 Adjuncts. Tests shall be in accordance with 11.14.2.

6.4 *Composition 4*—Composition 4 balls shall be manufactured from selected silicon molybdenum steel UNS T41902 of

TABLE 2 Chemical Compositions for Materials Not Assigned UNS Numbers

Element	Chemical Compositions, weight %						
	Silicon Molybdenum Steel ^A	Brass ^B	Aluminum Bronze ^C	Beryllium Copper Alloy ^D	Nickel-Copper Alloy ^E	Aluminum Alloy ^F	Tungsten Carbide ^G
Carbon	0.45-0.55						
Copper		60-70	remainder	remainder	25-30	3.5-4.5	
Zinc		30-40				0.25 max	
Aluminum			9-14			remainder	
Manganese	0.30-0.60		1.5 max			0.40-1.0	
Nickel			5.5 max	0.20 min, ^H 0.60 max ^I	65-70		
Iron			2.10-4.00		5.0 max ^J	1.0 max	
Beryllium				1.80-2.05			
Silicon	0.90-1.15					0.8 max	
Magnesium						0.20-0.8	
Chromium	0.25 max					0.10 max	
Other elements		0.5 max total			5.0 max total	0.15 max total, 0.05 max each	0.5 max total
Tungsten carbide (WC)							93.5-94.5
Cobalt							5.5-6.5
Phosphorus	0.030 max						
Sulphur	0.030 max						
Molybdenum	0.30-0.50						

^A Composition 4.
^B Composition 5.
^C Composition 7.
^D Composition 8.
^E Composition 9.
^F Composition 11.
^G Composition 12.
^H Nickel or cobalt, or both.
^I Nickel plus cobalt plus iron.
^J Iron plus zinc.

the through-hardened type as specified in **Table 2**. Chemical composition shall be tested in accordance with **11.2**.

6.5 *Composition 5*—Composition 5 balls shall be manufactured from brass UNS C26000 as specified in **Table 2**. Chemical composition shall be tested in accordance with **11.2**.

6.6 *Composition 6*—Composition 6 balls shall be manufactured from bronze conforming to the chemical composition of UNS C46400 (SAE CDA464) in accordance with Specifications **B283**, **B124/B124M**, and **B21/B21M**. Chemical composition shall be tested in accordance with **11.2**.

6.7 *Composition 7*—Composition 7 balls shall be manufactured from aluminum bronze UNS C62400 and UNS C6300 as specified in **Table 2**. Chemical composition shall be tested in accordance with **11.2**.

6.8 *Composition 8*—Composition 8 balls shall be manufactured from beryllium copper as specified in **Table 2**. Chemical composition shall be tested in accordance with **11.2**.

6.9 *Composition 9*—Composition 9 balls shall be manufactured from nickel copper alloy (Monel) UNS N04400 as specified in **Table 2**. Chemical composition shall be tested in accordance with **11.2**.

6.10 *Composition 10*—Composition 10 balls shall be manufactured from nickel-copper-aluminum alloy conforming to the chemical composition of UNS N05500 (K-Monel) in accordance with QQ-N-286. Chemical composition shall be tested in accordance with **11.2**.

6.11 *Composition 11*—Composition 11 balls shall be manufactured from aluminum alloy UNS A92017 as specified in **Table 2**. Chemical composition shall be tested in accordance with **11.2**.

6.12 *Composition 12*—Composition 12 balls shall be manufactured from tungsten carbide material as specified in **Table 2**. Chemical composition shall be tested in accordance with **11.2**.

6.13 *Composition 13*—Composition 13 balls shall be manufactured from aircraft-quality steel conforming to the chemical composition of UNS T11350 or UNS T12001 in accordance with AMS 6490 or AMS 6491. Chemical composition shall be tested in accordance with **11.2**.

6.13.1 *Ultrasonic Inspection of Bar Stock*—Bar and wire stock selected for the manufacture of Composition 13 balls shall be inspected using the ultrasonic inspection test method in **Annex A1**. Composition 13 bar and wire stock shall be tested 100 %.

6.13.2 Material used in manufacture of Composition 13 balls shall conform to the inclusion rating specifications given in **7.6**.

6.13.3 When a first article sample of Composition 13 ball material is required, chemical testing, fracture grain size, and inclusion rating are required in addition to other tests.

6.13.4 Material used in the manufacture of Composition 13 balls shall be macro-examined in accordance with **11.14.2**.

6.14 *Composition 14*—Composition 14 balls shall be manufactured from corrosion-resistant unhardened steel conforming

to the chemical composition of UNS S30200, UNS S30400, UNS S30500, UNS S31600, or UNS S43000 in accordance with Specification **A276**. Chemical composition shall be tested in accordance with **11.2**.

6.15 *Composition 15*—Composition 15 balls shall be manufactured from premium quality chrome alloy steel conforming to the chemical composition of UNS G52986 in accordance with AMS 6444. Chemical composition shall be tested in accordance with **11.2**.

6.16 *Composition 16*—Composition 2 balls shall be manufactured from corrosion-resistant steel conforming to the chemical composition of UNS S44004 in accordance with Specification **A276** and AMS 5618 VIMVAR. Chemical composition shall be tested in accordance with **11.2**.

7. Other Requirements

7.1 *Density*—Density shall be as specified in **Table 3**. Select samples of each composition in accordance with Section **10**. Weigh the balls in air and divide the weight of each sample ball by the computed volume of the ball (cm³). The diameter used in computing the volume of the ball shall be determined in accordance with **11.12.1**. Determine the weight of each sample ball to an accuracy of 2.205×10^{-6} lbm (0.001 g) or 0.10 % of the weight, whichever is greater.

7.2 Hardness:

7.2.1 Hardness shall be as specified in **Table 3** when tested in accordance with **11.4**.

7.2.2 *Composition 3 Hardness*—Composition 3 balls shall have a minimum surface hardness of 60 HRC or equivalent when tested in accordance with **11.4**. Composition 3 balls shall be case hardened to the depth specified in **Table 4** when tested in accordance with **11.9**.

7.3 *Fracture Grain Size*—Unless otherwise specified, fracture grain size shall be in accordance with the material specification, when tested in accordance with **11.5**. Fracture grain size shall not exceed the fracture grain size specified in **Table 3**, when tested in accordance with **11.5**.

7.4 *Porosity*—Composition 12 balls shall not exceed the conditions for A02, B02, and C02 apparent porosity as given in Test Method **B276** when tested in accordance with **11.6**.

7.5 *Decarburization*—Compositions 1, 2, 3, 4, 13, 15 and 16 balls shall not exhibit decarburization when tested in accordance with **11.8**.

7.6 *Inclusion Rating*—Unless otherwise specified, inclusion rating requirements shall be in accordance with the material specification.

7.6.1 *Composition 13 Material Samples and Finished Balls*—Inclusion rating for Composition 13 material samples shall not exceed the inclusion rating specified for billets to be used for wire and rods in the manufacture of balls and rollers as specified in Specification UNS T11350 or UNS T12001. Inclusion rating for finished Composition 13 balls shall be as specified in AMS 6490 or AMS 6491.

TABLE 3 Other Requirements

Composition Number	Hardness ^A	Density, lbm/in. ³ (reference)	Fracture Grain Size, max, see 7.3
1	58-67 HRC ^B	0.283	8
2	58-65 HRC	0.277	7½
3	min 60 HRC ^C	0.284	...
4	52-60 HRC	0.278	...
5	75-87 HRB	0.306	...
6	75-98 HRB or 15-20 HRC ^D	0.304	...
7	15-20 HRC	0.273	...
8	min 38 HRC	0.300	...
9	85-95 HRB	0.318	...
10	min 27 HRC	0.306	...
11	54-72 HRB	0.101	...
12	87.5-90.4 HRA	0.539	...
13	61-64 HRC	0.279	8
14	25-39 HRC		
14 S43000	48-63 HRA		
15	58-67 HRC ^B	0.283	8
16	58-67 HRC ^B	0.277	7½

^A Hardness equivalent to those shown are also acceptable. See Standard Hardness Conversion Tables E140.

^B The balls within any unit container shall have a uniform hardness from ball to ball within three points HRC or equivalent.

^C See 7.2.2.

^D See 11.4.

TABLE 4 Case Depth Requirements for Composition 3 Balls

Nominal Size, in.		Minimum Case Depth, in.
At Least	But Not	
1/64 (SI)	1/16	0.005
1/16 (SI)	3/32	0.015
3/32 (SI)	1/8	0.020
1/8 (SI)	3/16	0.025
3/16 (SI)	7/32	0.030
7/32 (SI)	1/4	0.035
1/4 (SI)	3/8	0.045
3/8 (SI)	7/16	0.055
7/16 (SI)	1/2	0.065
1/2 (SI)	9/16	0.070
9/16 (SI)	3/4	0.075
3/4 (SI)	1½	0.080

See Test Method E384.

7.7 Retained Austenite—The retained austenite content of Composition 13 balls shall not exceed 3 % by volume, as determined using X-ray diffraction techniques, or other techniques as specified. The retained austenite content of Composition 1, 2, 15 and 16 balls shall not exceed 7 % by volume, as determined using X-ray diffraction techniques, or other techniques as specified.

7.8 Passivation—Composition 2 and 16 balls. The surface of the finished balls shall be chemically cleaned or otherwise treated to be passive and free from all non stainless contamination per AMS 2700 or A976M. Test for acceptance in accordance with the appropriate test method in the passivation specification. Samples exhibiting visible corrosion shall be cause for lot rejection.

7.9 Eddy Current—Composition 13 balls shall be tested in accordance with 11.10.

7.9.1 Processing After Eddy Current Testing—Re-inspect any balls that are processed in any way following eddy current testing.

8. Dimensions, Mass, and Permissible Variations

8.1 The basic diameter of the balls, whether standard or nonstandard, shall be as specified in the purchase order or contract. Tolerance limits for size (diameter) variations and spherical form variations shall be in accordance with Table 5 and Table 6. Dimensions not within the tolerances specified in Table 5 and Table 6 shall be classified as a defect. Balls shall meet the acceptance quality limits (AQL) of Table 8 when tested for dimensional requirements in accordance with 11.12.

9. Workmanship, Finish, and Appearance

9.1 **Visual Inspection**—Balls shall meet the acceptance quality limits (AQL) of Table 8 when visually tested in accordance with 11.11 for compliance with the requirements of 9.1.1 and 9.1.2.

9.1.1 Balls shall be free from decarburization, over tempering, and indications of soft spots.

9.1.2 Except as specified for Composition 13 ball surfaces, ball surfaces shall be free from scratches, nicks, pits, dents,

TABLE 5 Tolerances by Grade for Individual Balls

Grade	Allowable Ball Diameter Variation, millionths of an inch,	Allowable Deviation from Spherical Form, millionths of an inch,
	V_{DWS}	ΔRW
3	3	3
5	5	5
10	10	10
16	16	16
24	24	24
48	48	48
100	100	100
200	200	200
500	500	500
1000	1000	1000

TABLE 6 Tolerances by Grade for Lots of Balls

Grade	Allowable Lot Diameter Variation, millionths of an inch, V_{DWL}	Basic Diameter Tolerance, millionths of an inch	Allowable Ball Gage Deviation, millionths of an inch, Δs		Container Marking Increment, millionths of an inch
			High	Low	
3	5	±30	+30	-30	10
5	10	±50	+50	-40	10
10	20	±100	+50	-40	10
16	32	±100	+50	-40	10
24	48	±100	+100	-100	10
48	96	±200			50
100	200	±500			
200	400	±1000			
500	1000	±2000			
1000	2000	±5000			

TABLE 7 Visual Inspection Limits

Type of Defect	Acceptable Limits	Acceptable Limits Composition 15, 16
Pits	0.0008 in maximum dimension for single pit; maximum of 3 permitted in any ¼ in. diameter circle	Allowed if not felt with a 0.005 in. radius probe
Scratches, surface non-metallic inclusions	0.001 in. wide by 0.010 in. long any number allowed as long as they do not cross.	Allowed if not felt with a 0.005 in. radius probe
Nicks, dents and indentations on ball of less than ½ in. diameter	0.015 in. maximum dimension	Allowed if not felt with a 0.005 in. radius probe
Nicks, dents and indentations on balls of ½ in. diameter or larger	0.024 in. maximum dimension	Allowed if not felt with a 0.010 in. radius probe
Seams, laps, tears, cracks, indications of corrosion, raised metal, scants, orange peel	None allowed	None allowed
Stains	0.005 in. major dimension not to exceed.	None allowed

TABLE 8 Quality Conformance Inspection

Test	Inspection Level	AQL (Defects Per 100 Units)
Visual	II	1.0
Dimensional Examination: (see Tables 5 and 6)	II	1.0
Diameter tolerance per ball	S-1	2.5
Ball diameter variation	S-1	2.5
Measurement of deviation from spherical form	S-1	2.5
Tolerances by grade for lots of balls	S-1	2.5
Specific diameter marking	S-1	2.5

seams, laps, tears, cracks, and corrosion when examined in accordance with 11.11. Composition 13 ball surfaces shall not exceed the tolerance limits specified in Table 7 for scratches, nicks, pits, dents, and indentation when examined in accordance with 11.11.1.

9.2 *Surface Roughness*—The surface roughness of the balls shall not exceed the value specified in the applicable MS sheet

standard (see 2.7) or Table 9 for the specified grade, when tested in accordance with 11.7.

9.3 *Carbides*—Carbides on the surfaces of finished Composition 13 balls shall not protrude more than 11 µin. above the surface of the ball, when tested in accordance with 11.13.

TABLE 9 Surface Roughness by Grade for Individual Balls

Grade	Maximum Surface Roughness Arithmetical Average, × 10 ⁻⁶ in.
3	0.5
5	0.8
10	1.0
16	1.0
24	2.0
48	3.0
100	5.0
200	8.0
500	
1000	