



Designation: ~~C903~~—~~10~~ C903 – 15

## Standard Practice for Preparing Refractory Castable Specimens by Cold Gunning<sup>1</sup>

This standard is issued under the fixed designation C903; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice covers a procedure for preparing refractory ~~castable~~ specimens usually containing calcium aluminate cement with or without metal fibers by cold nozzle-mix gunning. Specimens prepared in accordance with this practice are intended for use in standard ASTM test methods required for evaluating gunned materials.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C401 [Classification of Alumina and Alumina-Silicate Castable Refractories](#)

C865 [Practice for Firing Refractory Concrete Specimens](#)

### 3. Significance and Use

3.1 The properties of ~~refractory castables~~ ~~refractories~~ can be affected by their method of installation. This practice attempts to minimize the variables encountered during installation by pneumatic gunning.

3.2 This practice provides parameters to produce gunned specimens for use in other ASTM test methods.

3.3 This practice may be used to produce specimens for acceptance testing, service evaluation, manufacturing control, and research and development.

3.4 Differences between various kinds of equipment and the differences in procedures and operator techniques may result in significant variations in the physical properties of the gunned specimens. It is recommended that the same operator use the same equipment to produce specimens for referee testing agreed to by the involved testing parties. The specific operating parameters should be shown in the report.

3.5 Although this practice is specifically designed for ~~refractory castables~~ ~~refractories~~ containing calcium aluminate cement, it may be used with minor modifications for gun mixes containing other bond systems.

### 4. Apparatus

4.1 *Gun*, pneumatic nozzle-mix. At least 50 ft (15.2 m) of hose should be available. Acceptable nozzle diameters range from 1 to 2 in. (25 to 51 mm).

4.2 *Air Compressor*, capable of delivering sufficient pressure and volume to adequately move castable to the gun. The compressor should be able to supply at least 250 ft<sup>3</sup> (7 m<sup>3</sup>)/min.

4.3 *Forms*, suitable nonabsorbent type, which will vary in size in accordance with the number and size of samples being prepared, but are at minimum 12 by 12 by 4 in. (305 by 305 by 100 mm). Forms should be sized to prevent rebound entrapment. The use of 1/2 inch hardware cloth as sidewalls of the form allows most of the rebound to pass through.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.09 on Monolithics. Current edition approved Jan. 1, 2010/Oct. 1, 2015. Published February 2010/December 2015. Originally approved in 1979. Last previous edition approved in 2008/2010 as ~~C903—08~~ C903 – 10. DOI: ~~10.1520/C0903-10~~ 10.1520/C0903-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.