



Designation: **C266 – 13 C266 – 15**

Standard Test Method for Time of Setting of Hydraulic-Cement Paste by Gillmore Needles¹

This standard is issued under the fixed designation C266; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of the time of setting of hydraulic-cement paste by means of the Gillmore needles.

1.2 The values stated in ~~inch-pound~~SI units are to be regarded as standard. ~~The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered~~ No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

Warning: Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²

1.4 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 *ASTM Standards:*³

C151 Test Method for Autoclave Expansion of Hydraulic Cement

C183 Practice for Sampling and the Amount of Testing of Hydraulic Cement

C187 Test Method for Amount of Water Required for Normal Consistency of Hydraulic Cement Paste

C219 Terminology Relating to Hydraulic Cement

C305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes [ai/catalog/standards/sist/45d49aa3-357f-4065-aa30-c209609397c8/astm-c266-15](https://standards.iteh.ai/catalog/standards/sist/45d49aa3-357f-4065-aa30-c209609397c8/astm-c266-15)

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C1005 Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements

D1193 Specification for Reagent Water

3. Terminology

3.1 Refer to Terminology C219 for definitions of terms.

4. Summary of Test Method

4.1 Sufficient water is added to the cement that is being tested to produce a paste of normal consistency. A specimen is molded from this paste and is tested for time of setting by means of the Gillmore initial and final needles. The initial time of setting is the time elapsed between initial contact of cement and water and the time when the Gillmore Initial needle does not leave a complete circular impression in the paste surface. The final time of setting is the time elapsed between initial contact of cement and water and the time when the Gillmore Final needle does not leave a complete circular impression in the paste surface.

¹ This test method is under the jurisdiction of ASTM Committee C01 on Cement and is the direct responsibility of Subcommittee C01.30 on Time of Set Current edition approved Dec. 1, 2013/Dec. 1, 2015. Published January 2014/December 2015. Originally approved in 1951. Last previous edition approved in 2008/2013 as C266 – 08/C266 – 13, ¹; DOI: 10.1520/C0266-13.10.1520/C0266-15.

² Section on Safety, Manual of Cement Testing, *Annual Book of ASTM Standards*, Vol 04.01.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

5. Significance and Use

5.1 The purpose of this test method is to establish whether a cement complies with a specification limit on Gillmore time of setting.

6. Apparatus

6.1 *Flat Trowel*, having a sharpened straight-edged steel blade 100 to 150 mm in length. The edges when placed on a plane surface shall not depart from straightness by more than 1 mm.

6.2 *Mixer, Bowl, Paddle, and Scraper*, conforming to the requirements of Practice **C305**.

6.3 *Glass Graduates*, 200 or 250 mL capacity, conforming to the requirements of Specification **C1005**.

6.4 *Mass Determining Devices*, conforming to the requirements of Specification **C1005**. The devices for determining mass shall be evaluated for precision and accuracy at a total load of 1000 g.

6.5 *Plane Non-absorptive Plates*, 100 mm \pm 5 mm square, of similar planeness, corrosivity, and absorptivity to that of glass (see Test Method **C187** Fig. 1, item H).

6.6 *Gillmore Needles*, conforming to the following requirements:

6.6.1 The initial time of setting needle shall have a mass of 0.250 ± 0.001 lb (113.4 ± 0.5 g) 113.4 \pm 0.5 g and a tip diameter of 0.084 ± 0.002 in. (2.12 ± 0.05 mm); 2.12 \pm 0.05 mm.

6.6.2 The final time of setting needle shall have a mass of 1.000 ± 0.001 lb (453.6 ± 0.5 g) 453.6 \pm 0.5 g and a tip diameter of 0.042 ± 0.002 in. (1.06 ± 0.05 mm); 1.06 \pm 0.05 mm.

6.6.3 The needle tips shall be cylindrical for a distance of 0.189 ± 0.020 in. (4.8 ± 0.5 mm); 4.8 \pm 0.5 mm. The needle ends shall be plane and at right angles to the axis of the rod and shall be maintained in a clean condition (See **Note 1**).

6.7 Inspect and document Section 6 apparatus for conformance to the requirements of this test method at least every 2 ½ years.

NOTE 1—The Gillmore needles should preferably be mounted as shown in Fig. 1 (b).

7. Reagents

7.1 *Mixing Water*—Potable water is satisfactory for routine tests. For all referee and cooperative tests, reagent water conforming to the requirements of Specification **D1193** for Type III or Type IV grade of reagent water shall be used.

8. Sampling

8.1 When the test is part of acceptance testing, sample the cement in accordance with Practice **C183**.

9. Conditioning

9.1 Maintain the temperature of the room, dry materials, paddle, bowl, and plane non-absorptive plates at 23.0 ± 3.0 °C. Maintain the temperature of the mixing water at 23.0 ± 2.0 °C.

9.2 Maintain the relative humidity of the mixing room at not less than 50%.

9.3 The moist cabinet or moist room shall conform to the requirements of Specification **C511**.

10. Procedure

10.1 *Preparation of Cement Paste*: Obtain the cement paste used for determination of the time of setting from one of the following methods:

10.1.1 Prepare a new batch of paste by mixing 650 g of cement with the percentage of mixing water required for normal consistency (Test Method **C187**), following the procedure described in Practice **C305**.

10.1.2 At the option of the tester, use the paste remaining from the batch used for the autoclave expansion specimen (Test Method **C151**) or from the normal consistency determination (Test Method **C187**).

10.2 *Molding Test Specimen*—From the cement paste prepared as described in 10.1, make a pat with a flat top and the sides tapering to a thin edge on a plane non-absorptive plate, conforming to the dimensions and tolerances in Fig. 1 (a). In molding the pat, flatten the cement paste first on the plate and then form the pat by drawing the trowel from the outer edge toward the center, then flattening the top. After making, place the pat in the moist cabinet or moist room and allow it to remain there except when the determinations of time of setting are being made.

10.3 *Time of Setting Determination*—Determine the time of setting by holding the needle in a vertical position and lightly applying it to the surface of the pat.

10.3.1 Using the Initial Gillmore needle, determine the Gillmore Initial time of setting end point to be the first penetration measurement that does not mark the specimen surface with a complete circular impression. Verify Initial set by obtaining two additional penetration measurements on different areas of the specimen surface. Verification measurements must be obtained within 90 s of the first “initial set” measurement. The elapsed time, in minutes, between the time of contact of cement and mixing water and the end point determined above is the Gillmore initial time of setting.