



Designation: F970 – 15

## Standard Test Method for Static Load Limit<sup>1</sup>

This standard is issued under the fixed designation F970; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope

1.1 This test method is intended for use in determining the recovery properties of resilient floor covering after long-term indentation test, 24 h under the load specified in the detail specification. The reported value, residual indentation, is the depth of the depression remaining 24 h after removal of the specified load.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**E691** Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

**F386** Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces

**F387** Test Method for Measuring Thickness of Resilient Floor Covering With Foam Layer

**F1914** Test Methods for Short-Term Indentation and Residual Indentation of Resilient Floor Covering

### 3. Significance and Use

3.1 This test method is a meaningful test for determining the indentation recovery properties of resilient floor covering.<sup>3</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.30 on Test Methods - Performance.

Current edition approved Dec. 1, 2015. Published January 2016. Originally approved in 1987. Last previous edition approved in 2011 as F970–07 (2011). DOI: 10.1520/F0970–15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> For additional information, see Resilient Floor Covering Institute (RFCI) document, Static Limit Testing of Resilient Flooring Products, available from RFCI, 115 Broad Street, Suite 201, La Grange, GA 30240, www.rfci.com.

3.2 As testing is conducted on uninstalled flooring, results are not necessarily an indicator of the floor covering's installed performance.<sup>3</sup>

### 4. Apparatus

4.1 The following apparatus shall be used:

4.2 *Conditioning Room*, providing the standard laboratory atmosphere of  $50 \pm 5$  % relative humidity at a temperature of  $73.4 \pm 3.6^\circ\text{F}$  ( $23 \pm 2.0^\circ\text{C}$ ).

4.3 *Indentation Machine*, as described in Section 12 and pictured in Fig. 2 of Test Method F1914.

4.4 *Indentor Plates*, each constructed of a piece of 2-in. (50.8 mm) square stainless steel,  $0.240 \pm 0.005$  in. ( $6.1 \pm 0.1$  mm) thick, with one side turned to 1.125 in. (28.6 mm) in diameter (one square inch area) to depth of 0.150 in. (3.8 mm) (see Fig. 1).

4.5 *Dial Micrometer*, as described in Test Method F386 when measuring resilient floor coverings containing a foam layer as part of the construction or as described in Test Method F387 when measuring all other resilient floor coverings.

4.6 *Template of Poly(methyl Methacrylate) (PMMA)*, or of other transparent material, 2 by 2 in. (50.8 by 50.8 mm) with round scratch line centered on the template that is 1.125 in. (28.58 mm) in diameter, defining the test area, and with a  $\frac{1}{2}$  in. (12.7 mm) diameter hole at the center of the template to draw a circle on the specimen where thickness will be measured.

4.7 *Die*, 2 by 2 in. (50.8 by 50.8 mm) and press, papercutter, or equivalent to cut specimens to 2 by 2 in. size (50.8 by 50.8 mm).

4.8 *Optional*—Open box without spring clips for 2 by 2 in. (50.8 by 50.8 mm) photographic slides, or equivalent, to separate specimens during conditioning and recovery periods.

### 5. Sampling, Test Specimens and Test Units

5.1 The specimens shall be 2 by 2 in. (50.8 by 50.8 mm). The test unit shall consist of three specimens.

5.2 The central one square inch test area of each specimen should be free of mortar lines or other embossing lines, if possible. If not possible, the largest flat, raised area should be centered on the specimen.