



Designation: **D946/D946M – 09a** D946/D946M – 15

Standard Specification for Penetration-Graded Asphalt Cement Binder for Use in Pavement Construction¹

This standard is issued under the fixed designation D946/D946M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers asphalt cement binder for use in the construction of pavements.

NOTE 1—For asphalt binders graded by viscosity at 60°C, see Specification [D3381](#). For performance-graded asphalt binder, see Specification [D6373](#).

1.2 This specification covers the following penetration grades:

40–50,	120–150, and
60–70,	200–300.
85–100,	

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

[D5](#) Test Method for Penetration of Bituminous Materials

[D36](#) Test Method for Softening Point of Bitumen (Ring-and-Ball Apparatus)

[D92](#) Test Method for Flash and Fire Points by Cleveland Open Cup Tester

[D113](#) Test Method for Ductility of Bituminous Materials

[D140](#) Practice for Sampling Bituminous Materials

[D1754](#) Test Method for Effects of Heat and Air on Asphaltic Materials (Thin-Film Oven Test)

[D2042](#) Test Method for Solubility of Asphalt Materials in Trichloroethylene

[D3381](#) Specification for Viscosity-Graded Asphalt Cement for Use in Pavement Construction

[D6373](#) Specification for Performance Graded Asphalt Binder

[D7553](#) Test Method for Solubility of Asphalt Materials in N-Propyl Bromide

3. Manufacture

3.1 Asphalt cement binder shall be prepared by the refining of crude petroleum by suitable methods.

4. Properties

4.1 The asphalt cement binder shall be homogeneous and shall not foam when heated to 175°C [350°F].

4.2 The asphalt cement binder shall conform to the requirements given in [Table 1](#) or [Table 2](#), as specified by the purchaser. If no table is specified, the default shall be [Table 1](#). [Table 2](#) requirements limit the temperature susceptibility of asphalt over [Table 1](#) requirements. Asphalts-Asphalt binders that meet [Table 2](#) requirements will also meet [Table 1](#) requirements of the same grade.

5. Methods of Sampling and Testing

5.1 The material shall be sampled and the properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

¹ This specification is under the jurisdiction of ASTM Committee [D04](#) on Road and Paving Materials and is the direct responsibility of Subcommittee [D04.40](#) on Asphalt Specifications.

Current edition approved Dec. 1, 2009/Dec. 1, 2015. Published January 2010/January 2016. Originally approved in 1947. Last previous edition approved in 2009 as [D946 – 09](#); [D946/D946M – 09a](#). DOI: 10.1520/D0946 – D0946M-09A; 10.1520/D0946_D0946M-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.