

Designation: F1141/F1141M - 15

Standard Specification for Wall Coverings¹

This standard is issued under the fixed designation F1141/F1141M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This specification covers the performance, quality, packaging, and marking characteristics of flexible wall coverings as finished products.
- 1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems has the potential to result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:²

F793 Classification of Wall Covering by Use Characteristics

3. Terminology

- 3.1 Definitions:
- 3.1.1 *wall covering*—a flexible product designed to cover walls and ceilings for decorative or functional purposes, or both.
 - 3.2 Definitions of Terms Specific to This Standard:
- 3.2.1 *backing (substrate)*—material upon which facing (or an intermediate layer) is applied. Backing is that material which is adhered to the wall.
- 3.2.2 *bias*—pattern running off true horizontal or vertical plane.
- 3.2.3 *bolt*—a continuous amount of packaged material containing the amount specified on the label.
- 3.2.4 *facing*—decorative material which is applied to an intermediate layer or backing.
- 3.2.5 *finished product*—wall covering offered to a consumer for installation.
- ¹ This specification is under the jurisdiction of ASTM Committee F15 on Consumer Products and is the direct responsibility of Subcommittee F15.15 on Wallcoverings.
- Current edition approved Dec. 1, 2015. Published January 2016. Originally approved in 1988. Last previous edition approved in 2010 as F1141 10. DOI: $10.1520/F1141_F1141M-15$.
- ² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- 3.2.6 *intermediate layer*—material, if any, between the facing and the backing.
- 3.2.7 *lot (batch)*—the product from a continuous manufacturing run having the same appearance and characteristic from beginning to end.
- 3.2.8 *pattern match*—the meeting of all parts and colors of a pattern at the seams of adjacent strips.
- 3.2.9 *pattern repeat*—the vertical distance between adjacent match points of a pattern.
- 3.2.10 *protective layer*—any material applied to the facing to enhance performance.
- 3.2.11 *register*—the designed meeting of all parts and colors of a pattern.
- 3.2.12 *run*—a unit of production which may include more than one lot.
- 3.2.13 *seconds*—finished material not meeting the required quality criteria.
- 3.2.14 *selvage*—an undecorated edge which must be trimmed away to allow for correct pattern match or uniform continuity of color.
- 3.2.15 *waste edge*—a decorated edge that must be trimmed away to allow for correct pattern match or uniformity of color.
 - 3.2.16 *Shading:*
- 3.2.16.1 *color variation* difference within the same lot of wall covering.
- 3.2.16.2 *luster variation* difference in gloss level within the same lot of wall covering.
- 3.2.16.3 *texture variation*—difference in embossing within the same lot of wall covering.
- 3.2.17 *split bolt*—a bolt consisting of two or three separate lengths of material.

4. Appearance

4.1 There shall be no appreciable difference in shading except on those finished products in which natural decorative characteristics are being simulated. These variances must be clearly stated in writing at the point of purchase. To determine whether there is an appreciable difference, suspend three sequential 8-ft [2.4-m] strips at eye level in a vertical position, as on the wall, under illumination between 100 to 150 fc [1000 to 1500 lx], and view the strips from a distance between 4 and