



Designation: C629/C629M – 15

Standard Specification for Slate Dimension Stone¹

This standard is issued under the fixed designation C629/C629M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of slate for general building and structural purposes. Refer to Guides [C1242](#) and [C1528](#) for the appropriate selection and use of slate dimension stone.

1.2 Dimension slate shall include stone that is sawed, cut, split, or otherwise finished or shaped, and shall specifically exclude molded, cast, or otherwise artificially aggregated units composed of fragments, and also crushed and broken stone.

1.3 It specifically excludes roofing slate (see Specification [C406/C406M](#)) and slate for industrial uses.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

- [C119 Terminology Relating to Dimension Stone](#)
- [C120/C120M Test Methods for Flexure Testing of Structural and Roofing Slate](#)
- [C121/C121M Test Method for Water Absorption of Slate](#)
- [C217/C217M Test Method for Weather Resistance of Slate](#)
- [C241/C241M Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic](#)
- [C406/C406M Specification for Roofing Slate](#)
- [C1242 Guide for Selection, Design, and Installation of](#)

¹This specification is under the jurisdiction of ASTM Committee [C18](#) on Dimension Stone and is the direct responsibility of Subcommittee [C18.03](#) on Material Specifications.

Current edition approved Dec. 1, 2015. Published December 2015. Originally approved in 1968. Last previous edition approved in 2010 as C629/C629M – 10. DOI: 10.1520/C0629_C0629M-15.

²For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Dimension Stone Attachment Systems](#)

[C1353 Test Method for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic Using a Rotary Platform Abraser](#)

[C1528 Guide for Selection of Dimension Stone](#)

3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology [C119](#).

4. Classification

4.1 Dimension slate shall be selected for the following uses:

4.1.1 *I Exterior*:

4.1.2 *II Interior*.

5. Physical Requirements

5.1 Slate supplied under this specification shall conform to the requirements listed in [Table 1](#).

5.2 Slate used for exterior applications in ambient acidic atmospheres or in industrial areas where heavy air pollution occurs shall be free of carbonaceous ribbons. Slate shall be sound, durable, and free of spalls, cracks, open seams, pits, or other defects that are likely to impair its structural integrity in its intended use.

5.3 Slate shall be selected for overall satisfactory and natural appearance.

5.4 The desired color and texture, with their permissible natural variations in material characteristics for all material to be produced for the project, shall be established by control samples. Select representative samples by viewing a sufficient number of physical samples prior to production that show the complete range of variations in color and texture of the slate specified.

6. Sampling

6.1 Samples, if required, for testing to determine the characteristics and physical properties shall be representative of the slate to be used.

7. Keywords

7.1 acid resistance; carbonaceous ribbons; slate