



Designation: ~~D849~~—~~11~~ D849 – 15

Standard Test Method for Copper Strip Corrosion by Industrial Aromatic Hydrocarbons¹

This standard is issued under the fixed designation D849; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the corrosiveness of industrial aromatic hydrocarbons to a copper strip.

NOTE 1—For a similar copper strip test applicable to other petroleum products, see Test Method [D130](#) and Test Method [D1838](#).

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 8.

2. Referenced Documents

2.1 *ASTM Standards:*²

[B152/B152M](#) Specification for Copper Sheet, Strip, Plate, and Rolled Bar

[D130](#) Test Method for Corrosiveness to Copper from Petroleum Products by Copper Strip Test

[D1838](#) Test Method for Copper Strip Corrosion by Liquefied Petroleum (LP) Gases

[D4790](#) Terminology of Aromatic Hydrocarbons and Related Chemicals

[D6809](#) Guide for Quality Control and Quality Assurance Procedures for Aromatic Hydrocarbons and Related Materials

2.2 *Other Documents:*³

[OSHA Regulations, 29 CFR](#) paragraphs 1910.1000 and 1910.1200

2.3 *ASTM Adjuncts:*

ASTM Copper Strip Corrosion Standards (13 photo lithographed aluminum strips; includes Test Method [D130](#))⁴

3. Terminology

3.1 See Terminology [D4790](#) for definition of terms used in this test method.

4. Summary of Test Method

4.1 A polished copper strip is immersed in 200 mL of specimen in a flask with a condenser and placed in boiling water for 30 min. At the end of this period, the copper strip is removed and compared with the ASTM Copper Strip Corrosion Standards.

5. Significance and Use

5.1 This test method is suitable for setting specifications, for use as an internal quality control tool, and for use in development or research work on industrial aromatic hydrocarbons and related materials. It also gives an indication of the presence of certain corrosive substances which may corrode equipment, such as acidic compounds or sulfur compounds.

¹ This test method is under the jurisdiction of ASTM Committee [D16](#) on Aromatic Hydrocarbons and Related Chemicals and is the direct responsibility of Subcommittee [D16.01](#) on Benzene, Toluene, Xylenes, Cyclohexane and Their Derivatives.

Current edition approved Feb. 1, 2011; Oct. 1, 2015. Published February 2011; January 2016. Originally approved in 1945. Last previous edition approved in 2009 as [D849 – 09](#); [D849 – 11](#). DOI: [10.1520/D0849-11](#); [10.1520/D0849-15](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, [http://www.access.gpo.gov](#).

⁴ Available from ASTM International Headquarters. Request Adjunct No. [ADJD0130](#). Names of suppliers in the United Kingdom can be obtained from the Institute of Petroleum—Energy Institute, 61 New Cavendish St., London, W1G 7AR, U.K. Two master standards are held by the HPEI for reference.

*A Summary of Changes section appears at the end of this standard

6. Apparatus

6.1 *Flask*, of sufficient size to allow for refluxing 200 mL specimen, of chemically resistant glass with flat bottom and vial mouth.

6.2 *Glass Condenser*, length may vary, with the inside diameter of the condenser tube not less than 10 mm. A cork is used to connect the flask with the condenser. A condenser and flask with ground-glass joints may also be used.

6.3 *Strip Polishing Vise*, (optional), to hold the copper strip firmly without marring the edges. For convenient vises see Test Method **D130**.

6.4 *Water Bath*, of convenient design, able to maintain boiling water such that the contents of the flask are submerged during the test.

7. Reagents and Materials

7.1 *Wash Solvent*—Any volatile, sulfur-free hydrocarbon solvent may be used provided that it shows no tarnish at all when tested at 100°C for 1 h. *Iso* octane (**Warning**—See 8.2) is a suitable solvent.

7.2 *Surface Preparation/Polishing Materials*, 00 grade or finer steel wool or silicon carbide grit paper or cloth of varying degrees of fineness including 65- μm (240-grit) grade; also a supply of 105- μm (150-mesh) size silicon carbide grain or powder and absorbent cotton (cotton wool). A commercial grade is suitable, but pharmaceutical grade is most commonly available and is acceptable.

7.3 *Copper Strips*—Use strips ~~12.5 mm \pm 0.2 mm (1/2 in. \pm 1/16 in.)~~ that are 12.5 ± 2 mm ($1/2 \pm 1/8$ in.) wide, 1.5 to 3.2 mm ($1/16$ to $1/8$ in.) thick, and cut ~~75 mm \pm 3 mm (3 in. \pm 1/4 in.)~~ long from smooth-surfaced, ~~hard-tempered,~~ **hard**, cold-finished copper of 99.9 + % purity. Electrical bus-bar stock is generally suitable (hard-temper, cold-finished type-electrolytic tough pitch (ETP) copper conforming to UNS C11000 in Specification **B152/B152M**. Drill a 3.2 mm \pm 0.5 mm hole approximately 3.2 mm from one end in the center of the strip. The strips may be used repeatedly but should be discarded when surfaces become deformed on handling.

7.4 *Copper wire*, Wire, soft, about 150 mm in length.

7.5 *ASTM Copper Strip Corrosion Standards*, consisting of reproductions in color of typical test strips representing increasing degrees of tarnish and corrosion. The reproductions are encased in plastic in the form of a plaque. Instructions for care and use are given on the reverse side of each plaque and in Test Method **D130**.

7.6 *Ashless Filter Paper or Disposable Gloves*, for use in protecting the copper strip from coming in contact with the individual during final polishing.

8. Hazards

8.1 Consult current OSHA regulations, ~~supplier's Material~~ **supplier's Safety Data Sheets**, and local regulations for all materials used in this test method.

8.2 *Isooctane* is Extremely Flammable. Harmful if inhaled. Vapors may cause flash fire. Keep away from heat, sparks, and open flame. Keep container closed. Use with adequate ventilation. Avoid buildup of vapors and eliminate all sources of ignition, especially non-explosion-proof electrical apparatus and heaters. Avoid prolonged breathing of vapor or spray mist. Avoid prolonged or repeated skin contact.

9. Preparation of Strips

9.1 *Surface Preparation*—Remove all surface blemishes from all six sides of the strip obtained from a previous analysis (see **Note 2**). One way to accomplish this is to use 00 grade or finer steel wool or silicon carbide grit paper or cloth of such degrees of fineness as are needed to accomplish the desired results efficiently. Finish with 65- μm (240-grit) silicon-carbide paper or cloth, removing all marks that may have been made by other grades of paper used previously. Ensure the prepared copper strip is protected from oxidation prior to final preparation, such as by immersing the strip in wash solvent from which it can be withdrawn immediately for final preparation (polishing) or in which it can be stored for future use.

NOTE 2—Only final polishing (see 9.2) is necessary for commercially purchased pre-polished strips.

NOTE 3—As a practical manual polishing procedure, place a sheet of the paper on a flat surface, moisten it with wash solvent, and rub the strip against the paper with a circular motion, protecting the strip from contact with the fingers by using an ashless filter paper, other suitable material, or wearing disposable gloves. Alternatively, the strip may be prepared by use of motor-driven machines using appropriate grades of dry paper or cloth.

9.2 *Final Polishing*—For strips prepared in 9.1 or new strips being used for the first time, remove a strip from its protected location, such as by removing it from the wash solvent. To prevent possible surface contamination during final preparation, do not allow fingers to come in direct contact with the copper strips, such as by wearing disposable gloves or holding the strips in the fingers protected with ashless filter paper. Polish first the ends and then the sides with the 105- μm (150-mesh) silicon-carbide grains picked up from a suitable container with a pad of absorbent cotton or cloth moistened with a drop of wash solvent. Wipe vigorously with fresh pads of absorbent cotton or cloth and subsequently handle only with stainless-steel forceps, tongs, or other suitable devices to avoid touching with the fingers. Polish the main surfaces with silicon carbide grains on absorbent cotton or cloth. Rub