



Designation: **C1645/C1645M – 11** **C1645/C1645M – 15**

## Standard Test Method for Freeze-thaw and De-icing Salt Durability of Solid Concrete Interlocking Paving Units<sup>1</sup>

This standard is issued under the fixed designation C1645/C1645M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This test method evaluates the resistance to freezing and thawing of solid interlocking concrete paving units conforming to the dimensional requirements of Specification **C936/C936M**. Units are tested in a test solution that is either tap water or 3 % saline solution, depending on the intended use of the units in actual service.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, in any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitation prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**C936/C936M** Specification for Solid Concrete Interlocking Paving Units

### 3. Significance and Use

3.1 This test method is intended to determine the effects of freezing and thawing on units conforming to the dimensional requirements of Specification **C936/C936M** while immersed in a test solution. Other types of segmental concrete paving units that do not conform to the dimensional requirements of Specification **C936/C936M** may be tested using this test method.

3.2 The results from this test method are not intended to provide a quantitative measure of the length of service from concrete paving units conforming to the dimensional requirements of Specification **C936/C936M**.

### 4. Apparatus

4.1 *Freezing-and-Thawing Apparatus*—The freezing apparatus shall consist of suitable cabinet or cold room with controls to reach and maintain within 1 h of introduction of specimens an air temperature of  $-5 \pm 3^{\circ}\text{C}$  [ $23 \pm 5^{\circ}\text{F}$ ] at all locations within the chamber regardless of the number of specimens in the chamber. The thawing chamber shall maintain a controlled air temperature. This temperature shall never be greater than  $+30^{\circ}\text{C}$  [ $+86^{\circ}\text{F}$ ].

4.2 *Balance*—A balance capable of weighing 500 g with an accuracy of  $\pm 0.1 \pm 0.1$  g shall be used for measuring the mass of the fine spalled material.

4.3 *Drying Oven*—The drying oven shall be vented and capable of being maintained at 100 to 115°C [212 to 239°F].

4.4 *Specimen Container*—The specimen container shall be made of non-corroding flexible material and have dimensions that allow complete submersion of the specimen in the test solution. The size of the container shall be less than or equal to three times the volume of the unit that is being tested. The container shall prevent evaporation of the test solution.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **C15** on Manufactured Masonry Units and is the direct responsibility of Subcommittee **C15.03** on Concrete Masonry Units and Related Units.

Current edition approved on Dec. 15, 2015. Published January 2016. Originally approved in 2006. Last previous edition approved in 2009 as **C1645/C1645M – 09**. **C1645/C1645M – 11**. DOI: 10.1520/C1645-C1645M-11. 10.1520/C1645-C1645M-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

## 5. Sampling

5.1 *Selection of Test Specimens—Specimens*—Select whole units representative of the lot from which they are selected. The units shall be free from visible cracks, chipped edges, and structural defects.

5.2 *Number of Test Specimens*—Sample according to the requirements of Specification **C936/C936M**.

5.3 *Identification*—Mark each test specimen so that it is identifiable at any time.

## 6. Preparation of Test Specimens

6.1 *Curing and Conditioning*—When possible, specimens shall be full-sized units. When the units cannot be tested full-size due to specimen configuration or lack of suitable specimen containers, obtain a specimen by saw-cutting a full-height coupon with a surface area of at least 190 cm<sup>2</sup> [29.5 in.<sup>2</sup>]. Test specimens shall be a minimum of 28 days old before freeze-thaw cycling begins. After sampling, all test specimens shall be cured for 14 days in a moist chamber (cabinet or room) at an air temperature of 23 ± 2°C [73 ± 4°F] and a relative humidity of at least 90 % or submerged in a saturated lime solution maintained at 23 ± 2°C [73 ± 4°F]. Moist curing shall be followed by air curing for a minimum of 14 days at 24 ± 8°C [75 ± 15°F] at a maximum 80 % relative humidity. The curing and conditioning of the test specimens shall be waived at the option of the manufacturer of the pavers. When curing is waived, allow the specimens to air cure for a minimum of 48 h at 24 ± 8°C [75 ± 15°F] at a maximum 80 % relative humidity.

6.1.1 Before testing begins, the specimens shall be brushed clean with a stiff bristled brush and all loose burrs and edge shards shall be removed with a carborundum stone.

## 7. Procedure

7.1 *Freezing and Thawing Cycles*—One freeze-thaw cycle shall be completed every 24 h. The cycle shall consist of 16 ± 1 h of freezing followed by 8 ± 1 h of thawing. The specimens shall be subjected to continuous cycles. If for reasons beyond the operator's control, a freezing period cannot commence at the specified time, the specimens shall remain in a thawed condition until conditions are suitable for resumption of the test but not longer than 96 h. The specimen temperature shall conform to -5 ± 3°C [23 ± 5°F] for the last 7 to 12 h of the freezing cycle and a minimum of +5° C [40°F] for the last 1 h of the thawing cycle. The temperature shall be recorded at least every 15 min in the smallest and largest specimen (by weight) within the apparatus with a temperature probe that is insulated from cabinet air and rests against, below, or inside a specimen.

7.2 *Specimen Containment*—Immediately following completion of the conditioning, each specimen shall be centered with the wearing surface facing upwards in individual containers. The supported bottom surface of the specimens shall rest on solid, noncorrosive, nonabsorptive (for example, glass, stainless steel, ceramic, plastic, etc.) spacers approximately 5 mm [0.2 in.] high to ensure exposure of at least 95 % of the bottom surface to the test solution. A minimum of 5 mm [0.2 in.] clearance shall be provided between the specimen and the container in all directions.

7.3 *Test Solution*—The test solution shall be tap water or saline as requested by the client. If the test solution is saline, containers shall be filled with 3 ± 0.1 % (by weight) NaCl solution. The test solution (tap water or saline) shall have a temperature of 24 ± 8°C [75 ± 15°F]. The level of the test solution shall be 5 ± 1 mm [0.2 ± 0.04 in.] above the top surface of the specimens (**Note 1**). After filling the containers, they shall be immediately closed to minimize evaporation and the closed containers left at a temperature of 24 ± 8°C [75 ± 15°F] for 24 ± 1 h. After the 24 h soak period, check the level of the test solution and add additional test solution as needed to maintain the required level of 5 ± 1 mm [0.2 ± 0.04 in.] above the surface of the specimens.

**NOTE 1**—Excess test solution volume should be avoided in order to ensure rapid freezing of the specimens. Likewise, choose a container with a plan area similar to the test specimen to minimize excess test solution.

7.4 *Temperature Monitoring*—Following the 24-h saturation period, the specimens shall be subjected to continuous freeze-thaw cycles. The ambient temperature in the freeze-thaw apparatus, as well as those of the specimen, shall be continuously measured at least every 15 min and recorded. If for any reason, except for residue collection, continuous 24-h cycles cannot be maintained, then this shall be noted in the report.

7.5 *Collection of Residue*—After 7, 28, and (if necessary) 49 cycles, the specimens shall be washed with test solution (tap water or saline, as appropriate) to remove all loose particles. These particles and spalled material collected at the bottom of the containers shall be filtered using a sieve or filter paver with a maximum opening of 80 µm and washed with tap water to remove any soluble salts (**Note 2**). Dry the residue—all the filter paper and residue (spall) collected from each specimen in the drying oven for not less than 4 h and until two successive weighings at intervals of 2 h ± 15 min show an increment of loss not greater than 0.2 %–0.2 % of the last previously determined weight. This residue shall be defined—Place the filter paper and residue in a draft-free location within the laboratory for a period of 2 h ± 15 min to allow the filter paper and residue to come to equilibrium temperature with the laboratory environment. Weigh the filter paper and residue to the nearest 0.2 g and record as mass  $W_{f+r}$ —loss expressed in grams. The residue shall. Calculate the residue weight,  $W_r$ —cumulatively weighed, as follows:

$$W_r = W_{f+r} - W_f \quad (1)$$

after 7, 28, and 49 (if necessary) cycles.