



Designation: C565 – 15

Standard Test Methods for Tension Testing of Carbon and Graphite Mechanical Materials¹

This standard is issued under the fixed designation C565; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 These test methods cover the apparatus, specimen, and procedures for the tension testing of carbon and graphite mechanical materials with a grain size smaller than 0.79 mm.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.2.1 *Exception*—All of the figures are dimensioned in inches in accordance with the original standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

[C749 Test Method for Tensile Stress-Strain of Carbon and Graphite](#)

[E4 Practices for Force Verification of Testing Machines](#)

[E6 Terminology Relating to Methods of Mechanical Testing](#)

3. Terminology

3.1 *Definitions*:

3.1.1 The definitions of terms relating to tension testing in Terminology [E6](#) shall be considered as applying to the terms used in these test methods.

3.1.2 *tensile strength, n*—property of solid material that indicates its ability to withstand a uniaxial tensile load, converted to unit stress based on the original cross-section area of the tensile test specimen.

¹ These test methods are under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and are the direct responsibility of Subcommittee D02.F0 on Manufactured Carbon and Graphite Products.

Current edition approved Dec. 1, 2015. Published January 2016. Originally approved in 1965. Last previous edition approved in 2010 as C565 – 93(2010)^{ε1}. DOI: 10.1520/C0565-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.3 *ultimate tensile strength, n*—the maximum tensile stress applied in stretching a specimen to rupture.

4. Significance and Use

4.1 These test methods may be used for quality control testing of established grades of carbon and graphite materials, in the development of new grades, and for other purposes where relative strength levels are the primary quantities of interest. This test method may be applicable only if the ratio of specimen diameter to grain size, or flaw size, is greater than 5.

4.2 These test methods do not substitute for that described in Test Method [C749](#), but are useful where less sophisticated data and less expensive techniques are sufficient.

4.3 Carbon and graphite materials exhibit significant physical property differences within parent materials. Exact sampling patterns and grain orientations must be specified in order to make meaningful tensile strength comparisons.

5. Apparatus

5.1 *Testing Machine*—The machine used for tension testing shall conform to the requirements of Practices [E4](#). The testing machine shall have a capacity that the breaking load of the test specimen falls between 10 % and 90 % of the scale capacity.

5.2 *Gripping Devices*—Gripping devices that conform to the principles of those illustrated in [Fig. 1](#) shall be used (dimensions that reflect the use of SI units are permissible). These gripping devices shall be attached to the heads of the testing machine through chain connectors. [Fig. 2](#) shows the gripping device connected to the heads. Extreme care shall be taken that the axis of the test specimen is located on the center line of the head of the testing machine.

6. Test Specimens

6.1 Test specimens shall be produced to the configuration shown in [Fig. 3](#).

6.2 Improperly prepared test specimens often cause unsatisfactory test results. It is important, therefore, that care be exercised in the preparation of specimens, particularly in the machining and polishing.

6.3 The specimen shall be hand polished with No. 000 dry paper until no circular grooves are visible to the naked eye.

*A Summary of Changes section appears at the end of this standard