



Designation: D3787 – 16

# Standard Test Method for Bursting Strength of Textiles—Constant-Rate-of-Traversal (CRT) Ball Burst Test<sup>1</sup>

This standard is issued under the fixed designation D3787; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This test method describes the measurement for bursting strength with a ball burst strength tester of textiles or garments that exhibit a high degree of ultimate elongation.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as the standard. Within the test, the inch-pound units are shown in parentheses. The values stated in each system are not exact equivalents; therefore, each system may be used independently of the other. Combining values from the two systems may result in nonconformance within the specification.

NOTE 1—For the measurement of bursting strength with a hydraulic testing machine, refer to Test Method [D3786](#).

NOTE 2—Constant Rate of Traverse (CRT) machines and Constant Rate of Extension (CRE) machines have been shown to provide different results. When using a CRE device, refer to Test Method [D6797](#).

1.3 *This standard may involve hazardous materials, operations and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D76](#) Specification for Tensile Testing Machines for Textiles

[D123](#) Terminology Relating to Textiles

[D1776](#) Practice for Conditioning and Testing Textiles

[D3786](#) Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method

[D4850](#) Terminology Relating to Fabrics and Fabric Test Methods

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [D13](#) on Textiles and is the direct responsibility of [D13.59](#) on Fabric Test Methods, General.

Current edition approved Jan. 1, 2016. Published February 2016. Originally approved in 2001. Last previous edition approved in 2015 as D3787–15. DOI: 10.1520/D3787-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D6797](#) Test Method for Bursting Strength of Fabrics  
Constant-Rate-of-Extension (CRE) Ball Burst Test

## 3. Terminology

3.1 For all terminology relating to [D13.59](#), Fabric Test Methods, General, refer to Terminology [D4850](#).

3.1.1 The following terms are relevant to this standard: bursting strength, constant-rate-of-traverse (CRT) tensile testing machine, fabric, knitted, fabric, nonwoven.

3.2 For all other terminology related to textiles, refer to Terminology [D123](#).

## 4. Summary of Test Method

4.1 A specimen is securely clamped without tension between grooved, circular plates of the ball burst attachment secured to the pulling (movable) jaw for the constant-rate-of-traverse (CRT) testing machine. A force is exerted against the specimen by a polished, hardened steel ball that is attached to the pendulum-actuating (fixed) clamp of the machine, until rupture occurs.

## 5. Significance and Use

5.1 This test method for the determination of ball bursting strength of textiles is being used by the textile industry for the evaluation of a wide variety of fabrics.

5.2 Test results obtained using the procedures in Test Method [D3787](#) have not been correlated with actual performance. Test Method [D3787](#) is considered satisfactory for acceptance testing of commercial shipments of textiles fabrics for bursting strength since the method has been used extensively in the trade for acceptance testing. In cases of disagreement arising from differences in values reported by the purchaser and the seller when using Test Method [D3787](#) for acceptance testing, the statistical bias, if any, between the laboratory of the purchaser and the laboratory of the seller should be determined with comparison based on testing specimens randomly drawn from one sample of material of the type being evaluated.

NOTE 3—The kind of force transfer and strength that occur when knitted goods are worn is prevented by clamping them as directed in this test method.

5.2.1 If there are differences of practical significance between reported test results for two (or more) laboratories, comparative tests should be performed to determine if there is a statistical bias between them. The test samples used should be as homogeneous as possible, drawn from the material from which the disparate test results were obtained, and randomly assigned in equal numbers to the laboratories for testing. Other materials with established test values may be used for this purpose. The test results from the two laboratories should be compared using a statistical test for unpaired data at a probability level chosen prior to the testing series. If a bias is found, either the cause must be determined and corrected or future test results must be adjusted in consideration of known bias.

**6. Apparatus**

6.1 *Constant-Rate-of-Traverse (CRT) Tensile Testing Machine (CRT)*, as specified in Specification **D76**, with a ball-burst attachment replacing the clamp assembly.

6.2 *Ball-Burst Attachment*,<sup>3</sup> consisting of an attachment having a polished steel ball that replaces the fixed clamp of the tensile tester and of a ring-clamp mechanism that replaces the pulling (moving) clamp of the tensile tester (see **Fig. 1** and **Fig. 2**). Movement of the ring clamp pushes the fabric in the ring clamp against the steel ball.

6.2.1 The polished steel ball shall have a diameter of 25.400 ± 0.005 mm (1.0000 ± 0.0002 in.) and shall be spherical within 0.005 mm (0.0002 in.). The ring clamp shall have an internal diameter of 44.450 ± 0.025 mm (1.750 ± 0.001 in.).

**7. Sampling**

7.1 *Lot Sample*—Take a lot sample as directed in the applicable material specification. In the absence of such a specification, randomly select the rolls or pieces of fabric that constitute the lot sample using the following schedule:

Number of Rolls or Pieces in Lot, Inclusive	Number of Rolls or Pieces in Lot Sample
1 to 3	all
4 to 24	4
25 to 50	5
Over 50	10 % or a maximum of 10 of the rolls or pieces

7.2 *Laboratory Samples*—From each roll or piece of fabric selected from the lot sample, cut at least one laboratory sample the full width of the fabric and at least 1 m (1 yd) along the selvage. From each roll or piece of circular knit fabric selected from the lot sample, cut a band at least 300 mm (1 ft) wide.

**8. Selection and Number of Specimens**

8.1 Unless otherwise agreed upon, as when specified in an applicable material specification, take five specimens of the laboratory sample(s) of fabric. Each specimen shall be at least 125 mm (5 in.) square, or a circle 125 mm (5 in.) in diameter. Specimens need not be cut for testing. No two specimens should contain the same warp and filling or wale and course yarns. Take no specimens nearer the selvage than one tenth the fabric width. This restriction does not apply to tubular knitted fabric.

**9. Conditioning**

9.1 Bring the specimens (or laboratory samples) from the prevailing atmosphere to moisture equilibrium for testing textiles in the standard atmosphere for testing as prescribed in Practice **D1776**.

<sup>3</sup> Apparatus and accessories are available commercially.



**FIG. 1 Ball Burst Attachment**