



Designation: **D4172 – 94 (Reapproved 2010) D4172 – 94 (Reapproved 2016)**

## Standard Test Method for Wear Preventive Characteristics of Lubricating Fluid (Four-Ball Method)<sup>1</sup>

This standard is issued under the fixed designation D4172; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope

1.1 This test method covers a procedure for making a preliminary evaluation of the anti-wear properties of fluid lubricants in sliding contact by means of the Four-Ball Wear Test Machine. Evaluation of lubricating grease using the same machine is detailed in Test Method [D2266](#).

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D2266 Test Method for Wear Preventive Characteristics of Lubricating Grease \(Four-Ball Method\)](#)

2.2 *ANSI Standard:*<sup>3</sup>

[B3.12 Specification for Metal Balls](#)

### 3. Terminology

3.1 *Definitions:*

3.1.1 *lubricant, n*—any material interposed between two surfaces that reduces the friction or wear between them.

3.1.2 *wear, n*—damage to a solid surface, generally involving progressive loss of material due to relative motion between that surface and a contacting substance or surface.

### 4. Summary of Test Method

4.1 Three ~~12.7-mm~~ 12.7 mm (1/2-in.) diameter steel balls are clamped together and covered with the lubricant to be evaluated. A fourth ~~12.7-mm~~ 12.7 mm diameter steel ball, referred to as the top ball, is pressed with a force of ~~147 or 392 N~~ 147 or 392 N (15 or 40 kgf) into the cavity formed by the three clamped balls for three-point contact. The temperature of the test lubricant is regulated at ~~75°C~~ 75°C (167°F) and then the top ball is rotated at ~~1200 rpm~~ 1200 rpm for ~~60 min.~~ 60 min. Lubricants are compared by using the average size of the scar diameters worn on the three lower clamped balls.

NOTE 1—Because of differences in the construction of the various machines on which the four-ball test can be made, the manufacturer's instructions should be consulted for proper machine set up and operation.

NOTE 2—Although the test can be run under other parameters, the precision noted in Section ~~4.10~~ 4.10 may vary. No aqueous fluid was included in the round-robin to establish the precision limits.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [D02](#) on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee [D02.L0.11](#) on Tribological Properties of Industrial Fluids and Lubricates.

Current edition approved ~~May 1, 2010~~ Jan. 1, 2016. Published ~~May 2010~~ February 2016. Originally approved in 1982. Last previous edition approved in ~~2004~~ 2010 as [D4172 – 94 \(2010\)](#). DOI: ~~10.1520/D4172-94R10.10.1520/D4172-94R16.~~

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

5. Significance and Use

5.1 This test method can be used to determine the relative wear preventive properties of lubricating fluids in sliding contact under the prescribed test conditions. No attempt has been made to correlate this test with balls in rolling contact. The user of this test method should determine to his own satisfaction whether results of this test procedure correlate with field performance or other bench test machines.

6. Apparatus

6.1 Four-Ball Wear Test Machine<sup>4</sup>—See Figs. 1-3.

NOTE 3—It is important to distinguish between the Four-Ball E.P. and the Four-Ball Wear Test Machines. The Four-Ball E.P. Test Machine is designed for testing under heavier loads and lacks the sensitivity necessary for wear tests.

6.2 Microscope,<sup>4</sup> capable of measuring the diameters of the scars produced on the three stationary balls to an accuracy of  $0.01 \pm 0.01$  mm. It is more efficient to measure the scars without removing the three balls from the holder.

7. Materials

7.1 Test Balls,<sup>5</sup> chrome alloy steel, made from AISI standard steel No. E-52100, with diameter of  $12.7 \pm 0.01$  mm (0.5 in.) Grade 25 EP (Extra Polish). Such balls are described in ANSI B3.12. The extra-polish finish is not described in that specification. The Rockwell C hardness shall be 64 to 66, a closer limit than is found in the ANSI requirement.

7.2 Cleaning Fluids for preparing balls and apparatus for the test should be those approved as nontoxic, capable of removing antirust coatings from the balls, eliminating test-oil carryover from one test to the next, and not contribute to wear or antiwear of the test lubricant. When the fluid(s) is flammable, appropriate precautions should be taken (see Note 1). In the round-robin tests to determine repeatability and reproducibility no specific directions were given for cleaning balls and machine parts. Operators reported using various solvents with and without a sonic cleaning bath. Cleaning techniques reported by some cooperators are included in Research Report RR:D02-1152, see Note 4.

8. Test Conditions

8.1 The test conditions used to develop the precision data as stated in Section 10 were:

	A	B
Temperature	$75 \pm 2^\circ\text{C}$ [ $167 \pm 4^\circ\text{C}$ ]	$75 \pm 2^\circ\text{C}$ [ $167 \pm 4^\circ\text{C}$ ]
Temperature	$75^\circ\text{C} \pm 2^\circ\text{C}$ ( $167^\circ\text{F} \pm 4^\circ\text{F}$ )	$75^\circ\text{C} \pm 2^\circ\text{C}$ ( $167^\circ\text{F} \pm 4^\circ\text{F}$ )
Speed	$1200 \pm 60$ rpm	$1200 \pm 60$ rpm
Speed	1200 r/min $\pm$ 60 r/min	1200 r/min $\pm$ 60 r/min
Duration	$60 \pm 1$ min	$60 \pm 1$ min
Duration	60 min $\pm$ 1 min	60 min $\pm$ 1 min
Load	$147 \pm 2$ N [ $15 \pm 0.2$ kgf]	$392 \pm 2$ N [ $40 \pm 0.2$ kgf]
Load	$147 \text{ N} \pm 2 \text{ N}$ (15 kgf $\pm$ 0.2 kgf)	$392 \text{ N} \pm 2 \text{ N}$ (40 kgf $\pm$ 0.2 kgf)

9. Preparation of Apparatus

9.1 Set up the drive of the machine to obtain a spindle speed of  $1200 \pm 60$  r/min.

9.2 Set temperature regulator to produce a test-oil temperature of  $75 \pm 2^\circ\text{C}$  ( $167 \pm 4^\circ\text{F}$ ).

<sup>4</sup> The Four-Ball Wear Test Machine and the Falex Model #6, Multi-Specimen Friction and Wear Test Machine, both made by Falex Corp., 1020 Airpark Drive, Sugar Grove, IL 60554, have been found satisfactory for this purpose. This company can also furnish a microscope with a special base to measure the wear scars without removing the balls from the test-oil cup. Discontinued models of the Four-Ball Wear Test Machine made by Precision Scientific Co. and Roxana Machine Works are also satisfactory.

<sup>5</sup> Steel balls meeting this description were used in developing the precision of the test. They are available from the manufacturer of the test machine and some ball manufacturers. Some operators prefer to check a new box of balls by running an oil with a known result.




FIG. 1 Schematic of a Four-Ball Wear Test Machine