



Designation: D4389/D4389M – 16

# Standard Specification for Finished Glass Fabrics Woven From Rovings<sup>1</sup>

This standard is issued under the fixed designation D4389/D4389M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification primarily covers glass fabrics woven from “E” electrical continuous glass fiber rovings that are intended primarily as a reinforcing material in laminated plastics for structural use.

1.2 This specification specifies the terminology, definitions, general requirements, and physical requirements for woven roving glass fiber fabrics. This specification permits the application of sizing materials to the glass fiber roving during manufacture that helps facilitate weaving. When used as permitted in this specification, such materials are compatible with the resin matrix as specified in the contracting instrument.

NOTE 1—Sizing materials on glass fiber yarns, in most cases, are removed by various cleaning procedures as a first stage in preparing a finished fabric. When these yarn sizing materials are removed during a cleaning procedure, they need not be compatible with the subsequent resin matrix.

1.3 *Units*—The values stated in either SI units or inch-pound units are to be regarded as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

NOTE 2—This specification is one of a series to provide a substitute for the following Military Specifications:

- MIL-Y-1140H Yarn, Cord, Sleaving, Cloth, and Tape-Glass
- MIL-C-9084C Cloth, Glass Finished for Resin Laminates
- MIL-C-19663C Cloth, Glass, Woven Roving for Plastic Laminates

## 2. Referenced Documents

### 2.1 *ASTM Standards*:<sup>2</sup>

- D123 Terminology Relating to Textiles
- D578 Specification for Glass Fiber Strands
- D1776 Practice for Conditioning and Testing Textiles

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.18 on Glass Fiber and its Products.

Current edition approved Jan. 1, 2016. Published February 2016. Originally approved in 1984. Last previous edition approved in 2010 as D4389 – 04 (2010<sup>ε1</sup>). DOI: 10.1520/D4389\_D4389M-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

- D2408 Test Method for Finish Content of Woven Glass Fabric, Cleaned and After-Finished With Amino-Silane-Type Finishes, for Plastic Laminates (Withdrawn 1988)<sup>3</sup>
  - D2409 Test Method for Finish Content of Woven Glass Fabric, Cleaned and After-Finished With Vinyl-Silane Type Finishes, for Plastic Laminates (Withdrawn 1988)<sup>3</sup>
  - D2410 Test Method for Finish Content of Woven Glass Fabric, Cleaned and After-Finished With Chrome Complexes, for Plastic Laminates (Withdrawn 1988)<sup>3</sup>
  - D2660 Test Method for Finish Content of Woven Glass Fabric, Cleaned and After-Finished with Acrylic-Silane-Type Finishes, for Plastic Laminates (Withdrawn 1988)<sup>3</sup>
  - D3098 Test Method for Finish Content of Woven Glass Fabrics, Cleaned and After-Finished with Epoxy-Functions Silane Type Finishes for Plastic Laminates (Withdrawn 1988)<sup>3</sup>
  - D3773 Test Methods for Length of Woven Fabric
  - D3774 Test Method for Width of Textile Fabric
  - D3775 Test Method for Warp (End) and Filling (Pick) Count of Woven Fabrics
  - D3776 Test Methods for Mass Per Unit Area (Weight) of Fabric
  - D4029 Specification for Finished Woven Glass Fabrics
  - D4963 Test Method for Ignition Loss of Glass Strands and Fabrics
  - D7018 Terminology Relating to Glass Fiber and Its Products
- ### 2.2 *ANSI Standard*:
- ANSI/ASQC Z1.4 Sampling Procedures for Inspection by Attributes<sup>4</sup>

## 3. Terminology

3.1 For definitions of glass fiber and product terms used in this specification refer to Terminology D7018.

3.1.1 The following terms are relevant to this standard: *continuous filament yarn, roving*.

3.2 For definitions of other textile terms used in this specification, refer to Terminology D123.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Available from American National Standards Institute 11 W. 42nd St., 13th Floor, New York, NY 10036.

## CLASSIFICATION

### 4. Classification

4.1 *Designation of Woven Roving Fabric*— The basic designations for glass woven roving fabric is by mass per unit area and is given in grams per square metre (ounces per square yard). Historically, an ASTM type number has been used by the industry. These numbers have been sequentially assigned as new woven roving constructions as they were added to this specification. Numbers 1 through 10 are shown in **Table 1** with the relationship to mass per unit area and fabric count.

## REQUIREMENTS

### 5. Material

5.1 The roving shall be continuous filament fiber, free of any free alkali, such as sodium or potassium metal salts and foreign particles, dirt, and other impurities. It shall be an E type glass as defined in Specification **D578**.

5.1.1 The fabric shall be uniformly woven, have uniform color, overall cleanness, and no objectionable odor.

### 6. Fabric Count

6.1 For woven roving fabrics listed in **Table 1**, the average fabric count shall conform to the requirements of **Table 1**. For woven roving fabrics not listed in **Table 1**, the average fabric count shall be agreed upon between the purchaser and the supplier.

### 7. Yarn Designations

7.1 For woven roving fabrics, the roving designations shall be as agreed upon between the purchaser and the supplier. The requirements of the individual elements of the designation are specified in Sections **8 – 10**.

### 8. Yarn Number

8.1 For woven roving fabrics listed in **Table 1**, the average size-free yarn numbers of the yarns designated shall conform to the requirements of **Table 1**. For woven roving fabrics not listed in **Table 1**, the average size-free yarn numbers shall be agreed upon between the purchaser and the supplier.

### 9. Filament Diameter

9.1 The range of values for the filament diameters are listed in **Table 2**. The average filament diameter for the rovings in the woven roving fabric shall be within the interval listed in **Table 2**.

### 10. Strand Construction

10.1 The construction of the component strands shall be agreed upon between the purchaser and the supplier.

### 11. Weave Type

11.1 For woven roving fabrics listed in **Table 1**, the weave type shall be plain weave. For woven roving fabrics not listed in **Table 1**, the weave type shall be agreed upon between the purchaser and the supplier.

### 12. Mass per Unit Area

12.1 For woven roving fabrics listed in **Table 1**, the average mass per unit area shall conform to the requirements of **Table 1**. For woven roving fabrics not listed in **Table 1**, the average mass per unit area shall be agreed upon between the purchaser and the supplier. The average mass per unit area for the lot shall be within the interval: specified mass per unit area  $\pm 10\%$  of the specified mass per unit area.

### 13. Width

13.1 Fabric width shall be agreed upon between the purchaser and the supplier. The fabric width, including both selvages but excluding any feathered edges, shall not be less than the specified width and no more than 13 mm [0.5 in.] wider than the specified width.

NOTE 3—During the processing of glass fabrics, the selvages may be slit to minimize tension influences. This slit distance is excluded when measuring the fabric width unless otherwise agreed upon between the purchaser and the supplier.

### 14. Length

14.1 For woven roving fabrics listed in **Table 1**, the fabric length on each roll shall not be less than 2 m [2 yd] below the requirements listed in **Table 1** unless otherwise agreed upon between the purchaser and the supplier. For woven roving

**TABLE 1 Physical Properties of Generally Available “E” Glass Finished Woven Roving Fabrics**

ASTM Type	Weave	Nominal Mass Per Unit Area		Roving Count 25.4 mm [1 in.] min		Construction <sup>A</sup> Nominal Roving Length Per Unit Mass				Standard Roll Length	
						Tex		yd/lb			
		g/m <sup>2</sup>	oz/yd <sup>2</sup>	Warp	Fill	Warp	Fill	Warp	Fill	m	yd
1	Plain	441	13.0	10	4	840 to 755	1065 to 925	590 to 655	465 to 535	91.5	100
2	Plain	542	16.0	10	4	840 to 755	1680 to 1505	590 to 655	295 to 330	91.5	100
3	Plain	831	24.5	5	4	2360 to 2065	2680 to 2255	210 to 240	185 to 220	68.5	75
4	Plain	831	24.5	5	3	2360 to 2065	3545 to 3105	210 to 240	140 to 160	68.5	75
5	Plain	915	27.0	5	2.5	2360 to 2065	4960 to 4725	210 to 240	100 to 105	59.5	65
6	Plain	610	18.0	7	6	1210 to 1835	1340 to 1155	410 to 270	370 to 430	68.5	75
7	Plain	745	22.0	5	4	2360 to 2065	2155 to 1910	210 to 240	230 to 260	68.5	75
8	Plain	610	18.0	4	4	2360 to 2065	1655 to 1505	210 to 240	300 to 330	68.5	75
9	Plain	559	16.5	5	4	1710 to 1525	1710 to 1525	290 to 325	290 to 325	91.5	100
10	Plain	711	21.0	4	4	2420 to 2155	2420 to 2155	205 to 230	205 to 230	82.5	90

<sup>A</sup> In some cases, the fill yarn may be woven as 2 picks per shed and as 1 fill yarn. The basic roving length per unit area used to produce the above fill yarns should be doubled.