



Designation: ~~D3307~~—~~10~~ D3307 – 16

Standard Specification for Perfluoroalkoxy (PFA)-Fluorocarbon(PFA) Resin Molding and Extrusion Materials¹

This standard is issued under the fixed designation D3307; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers melt processable molding and extrusion materials of ~~PFA-perfluoro(alkoxy-alkane) fluorocarbon~~ Perfluoroalkoxy (PFA) resin. The materials are copolymers of ~~TFE-fluorocarbon resins containing perfluoroalkoxy side chains~~. ~~These materials were formerly the subject of this specification and Specification tetrafluoroethylene and perfluoroalkoxy.~~~~D6314.~~

1.2 This specification is intended to provide a means for calling out plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection should be made by those having expertise in the plastics field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the costs involved, and the inherent properties of the material other than those covered by this specification.

1.3 This specification does not cover recycled plastics.

~~1.4 The tests involved are intended to provide information for identifying the materials covered. It is not the function of this specification to provide engineering data for design purposes. Specimens prepared by injection molding or extrusion could yield test results that may vary from the values in this specification.~~

1.4 The values stated in SI units² are to be regarded as standard. The values given in parentheses are for information only.

1.5 The following precautionary caveat pertains only to the test methods portions, Sections 8 and 9 of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—This specification, ISO 12086-1(2006), and ISO 12086-2(2006) differ in approach or detail. Data obtained using either may not be technically equivalent.

2. Referenced Documents

2.1 *ASTM Standards:*³

[D150 Test Methods for AC Loss Characteristics and Permittivity \(Dielectric Constant\) of Solid Electrical Insulation](#)

[D618 Practice for Conditioning Plastics for Testing](#)

[D638 Test Method for Tensile Properties of Plastics](#)

[D792 Test Methods for Density and Specific Gravity \(Relative Density\) of Plastics by Displacement](#)

[D883 Terminology Relating to Plastics](#)

[D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer](#)

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[D1708 Test Method for Tensile Properties of Plastics by Use of Microtensile Specimens](#)

~~[D2116 Specification for FEP-Fluorocarbon Molding and Extrusion Materials](#)~~

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials (Section D20.15.12).

Current edition approved July 1, 2010/April 1, 2016. Published July 2010/April 2016. Originally approved in 1974. Last previous edition approved in 2008/2010 as ~~D3307-08~~:D3307 - 10. DOI: ~~10.1520/D3307-10~~:10.1520/D3307-16.

² As defined in ~~Guide D5033~~.

² As defined in [IEEE/ASTM SI-10](#).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

D3892 Practice for Packaging/Packing of Plastics

D4591 Test Method for Determining Temperatures and Heats of Transitions of Fluoropolymers by Differential Scanning Calorimetry

~~D4895 Specification for Polytetrafluoroethylene (PTFE) Resin Produced From Dispersion~~

~~D5033 Guide for Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics (Withdrawn 2007)⁵~~

~~D6314 Specification for Fluorocarbon Perfluoromethoxy (MFA) Resin Molding and Extrusion Materials (Withdrawn 2002)⁵~~

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

IEEE/ASTM SI-10 Standard for Use of the International System of Units (SI): The Modern Metric System

2.2 ISO Standards:⁴

ISO 12086-1 Plastics—Fluoropolymer Dispersions and Moulding and Extrusion Materials—Part 1

ISO 12086-2 Plastics—Fluoropolymer Dispersions and Moulding and Extrusion Materials—Part 2

3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminologies D883 and D1600.

3.1.1 *lot, n*—one production run or a uniform blend of two or more productions runs.

4. Classification

4.1 This specification covers 1418 types of PFA-fluorocarbon resins supplied in pellet form for molding and extrusion, classified according to their melting points. The resins of each type are divided into two to four grades according to their melt flow rates.

4.2 A one-line system may be used to specify materials covered by this specification. The system uses predefined cells to refer to specific aspects of this specification, illustrated as follows:

Specification								
Standard Number	:	Type	:	Grade	:	Class	:	Special Notes
Block	:		:		:		:	
:	:	:	:	:	:	:	:	:
_____	:	_____	:	_____	:	_____	:	_____

Example: Specification D3307 – 06, I

In this standard, the only specifications are type; no grade or class is required. specifications are type and grade. A comma is used as the separator between the standard number and the type-type, and a separator is not needed between the type and grade.⁵

5. General Requirements

5.1 The materials shall be of uniform composition and so prepared as to conform to the requirements of this specification.

5.2 The materials described in this specification shall be free of foreign matter to such a contamination level as may be required in at the best commercially practical level.^{10.4.}

6. Detail Requirements

6.1 The materials covered by this specification shall conform to the requirements prescribed in Table 1 and Table 2 when tested by the procedures specified herein. Table 2 lists those tests requiring a specimen molded as described in 9.1.

7. Sampling

7.1 Sampling shall be statistically adequate to satisfy the requirements of 10.4.

8. Number of Tests

8.1 One set of test specimens as prescribed in Section 9 shall be considered sufficient for testing each sample. The average result of the specimens tested shall conform to the requirements of this specification.

9. Test Methods

9.1 *Test Specimens:*

9.1.1 Prepare a molded sheet 1.50 ± 0.25-mm (0.060 ± 0.010-in.) thick. Use a picture-frame-type chase having a suitable blanked-out section and thickness to produce the desired sheet. Use clean aluminum foil, 0.13 to 0.18 mm (0.005 to 0.007 in.) thick, in contact with the resin. A high temperature mold release agent may be sprayed on the aluminum foil helps to help prevent the foil from sticking to the sheet. Use steel molding plates at least 1.0 mm (0.040 in.) thick and of an area adequate to cover the chase.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ See *ASTM Form and Style Manual*.

TABLE 1 Detail Requirements for Test on Molding and Extrusion Materials

	Type I	Type II	Type III	Type IV	Type V	Type VI	Type VII	Type VIII	Type IX	Type X	Type XI	Type XII	Type XIII	Type XIV
Melt flow, ^A g/10min:														
min	>7	1	>3	>10	1	>3	10	2	>24	1	≥4	≥8	≥18	≥63
max	19	3	7	30	3	10	17	5	≤50	4	8	18	40	81
Melting endotherm peak temperature, ^B min, °C	300	300	300	285	285	285	280	280	300	265	265	265	265	290

TABLE 1 Detail Requirements for Test on Molding and Extrusion Materials

	Type I	Type II	Type III	Type IV	Type V	Type VI	Type VII	Type VIII	Type IX	Type X	Type XI	Type XII	Type XIII	Type XIV	Type XV	Type XVI	Type XVII	Type XVIII
Melt flow, ^A g/10min:																		
min	>7	1	>3	>10	1	>3	10	2	>24	1	≥4	≥8	≥18	≥63	<u>1</u>	<u>>2.5</u>	<u>>5</u>	<u>>9</u>
max	19	3	7	30	3	10	17	5	≤50	4	8	18	40	81	<u>2.5</u>	<u>5</u>	<u>9</u>	<u>13</u>
Melting endotherm peak temperature, ^B min, °C	300	300	300	285	285	285	280	280	300	265	265	265	265	290	<u>311</u>	<u>311</u>	<u>311</u>	<u>311</u>

^ASee 9.3 of this specification.

^BSee 9.4 of this specification.