



Designation: C757 – 16

# Standard Specification for Nuclear-Grade Plutonium Dioxide Powder for Light Water Reactors<sup>1</sup>

This standard is issued under the fixed designation C757; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## INTRODUCTION

This specification is intended to provide the nuclear industry with a general standard for plutonium dioxide ( $\text{PuO}_2$ ) powder. It recognizes the diversity of manufacturing methods by which  $\text{PuO}_2$  powders are produced and the many special requirements for chemical and physical characterization that may be applicable for a particular Mixed Oxide (MOX, that is  $(\text{U}, \text{Pu})\text{O}_2$ ) fuel pellet manufacturing process or imposed by the end user of the powder in different light water reactors. It is, therefore, anticipated that the buyer may supplement this specification with more stringent or additional requirements for specific applications.

## 1. Scope

1.1 This specification covers nuclear grade  $\text{PuO}_2$  powder. It applies to  $\text{PuO}_2$  of various isotopic compositions as normally prepared by in-reactor neutron irradiation of natural or slightly enriched uranium or by in-reactor neutron irradiation of recycled plutonium mixed with uranium.

1.2 There is no discussion of or provision for preventing criticality incidents, nor are health and safety requirements, the avoidance of hazards, or shipping precautions and controls discussed. Observance of this specification does not relieve the user of the obligation to be aware of and conform to all applicable international, national, or federal, state, and local regulations pertaining to possessing, shipping, processing, or using source or special nuclear material. For examples in the U.S. Government, relevant documents are Code of Federal Regulations, Title 10 Nuclear Safety Guide, U.S. Atomic Energy Commission Report TID-7016<sup>2</sup>, and “Handbook of Nuclear Safety”, H. K. Clark, U.S. Atomic Energy Commission Report, DP-532<sup>2</sup>.

1.3 The  $\text{PuO}_2$  shall be produced by a qualified process and in accordance with a quality assurance program approved by the user.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C26.02 on Fuel and Fertile Material Specifications.

Current edition approved April 1, 2016. Published April 2016. Originally approved in 1974. Last previous edition approved in 2011 as C757 – 06 (2011) <sup>$\epsilon$ 1</sup>. DOI: 10.1520/C0757-16.

<sup>2</sup> Available from Superintendent of Documents, U.S. Government Printing Office, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20402.

1.4 The values stated in SI units are to be regarded as the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

- B243 Terminology of Powder Metallurgy
- C697 Test Methods for Chemical, Mass Spectrometric, and Spectrochemical Analysis of Nuclear-Grade Plutonium Dioxide Powders and Pellets
- C859 Terminology Relating to Nuclear Materials
- C1233 Practice for Determining Equivalent Boron Contents of Nuclear Materials
- C1274 Test Method for Advanced Ceramic Specific Surface Area by Physical Adsorption
- C1295 Test Method for Gamma Energy Emission from Fission and Decay Products in Uranium Hexafluoride and Uranyl Nitrate Solution
- C1770 Test Method for Determination of Loose and Tapped Bulk Density of Plutonium Oxide
- E105 Practice for Probability Sampling of Materials

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 ASME Standard:

ASME NQA-1 Quality Assurance Requirements for Nuclear Facility Applications<sup>4</sup>

2.3 U.S. Government Documents:

Code of Federal Regulations, Title 10, Nuclear Safety Guide, U.S. Atomic Energy Commission Report TID-7016<sup>2</sup>

“Handbook of Nuclear Safety,” Clark, H. K., U.S. Atomic Energy Commission Report, DP-532<sup>2</sup>

2.4 ISO Standard:

ISO 8300 Determination of Pu Content in Plutonium Dioxide (PuO<sub>2</sub>) of Nuclear Grade Quality, Gravimetric Method<sup>4</sup>

ISO 9161 Uranium Dioxide Powder—Determination of Apparent Density and Tap Density

ISO 13463 Nuclear-grade Plutonium Dioxide Powder for Fabrication of Light Water Reactor MOX Fuel—Guidelines to Help in the Definition of a Product Specification

3. Terminology

3.1 Definitions—Definitions of terms are as given in Terminologies B243 and C859.

4. Isotopic Content

4.1 Concentrations and homogeneity ranges of the plutonium (Pu) shall be as specified by the buyer.

4.2 The isotopic composition of the final product shall be determined by a method to be agreed upon between the buyer and seller and shall be reported on a Pu basis including the associated measurement uncertainties. The date of the determination will be indicated.

5. Chemical Composition

5.1 Plutonium Content—The minimum Pu content shall be 86.0 weight % including measurement uncertainties as sampled on the date of sampling.

5.2 Uranium Content—The uranium content of the PuO<sub>2</sub> shall be measured and reported on a Pu basis.

5.3 Americium Content—The americium (Am) content shall be measured and reported on a Pu basis. The maximum acceptable Am content shall be agreed upon between the buyer and seller.

5.4 The dates of analyses of U, Th and Am shall be recorded.

5.5 Impurity Content—The impurity content shall not exceed the individual element limit specified in Table 1 on a Pu basis. Total non-volatile oxide impurity content excluding Am shall not exceed 6000 µg/g Pu. Some other elements such as those listed in Table 2 may also be of concern for the buyer and should be measured and reported if requested. If an element analysis is reported as “less than” a given concentration, this “less than” value shall be used in the determination of total

TABLE 1 Impurity Elements and Maximum Concentration Limits

Element <sup>C</sup>	Maximum Concentration Limit of Plutonium, µg/gPu
Aluminum (Al)	300
Boron (B)	3
Cadmium (Cd)	3
Carbon (C) <sup>A</sup>	500
Chlorine (Cl)	300
Chromium (Cr)	200
Dysprosium (Dy)	0.5
Europium (Eu)	0.5
Fluorine (F)	200
Iron (Fe)	500
Gadolinium (Gd)	3
Magnesium (Mg)	200
Molybdenum (Mo)	100
Nickel (Ni)	200
Nitrogen (N)	300
Samarium (Sm)	2
Silicon (Si)	200
Sodium (Na)	100
Titanium (Ti)	100
Thorium (Th) <sup>B</sup>	50
Tungsten (W)	100
Zinc (Zn)	100

<sup>A</sup> Sample may be heated prior to carbon analysis.

<sup>B</sup> Thorium is primarily of concern because of the reactor production of <sup>233</sup>U.

<sup>C</sup> Any additional potential impurities, added by the fabrication process for example, beyond those listed here shall be evaluated (for example, in terms of equivalent boron), and associated limits established and agreed upon between the buyer and seller.

TABLE 2 Additional Impurity Elements

Element	
Beryllium (Be)	Niobium (Nb)
Bismuth (Bi)	Phosphorous (P)
Calcium (Ca)	Potassium (K)
Cobalt (Co)	Silver (Ag)
Copper (Cu)	Sulfur (S)
Indium (In)	Tantalum (Ta)
Lead (Pb)	Tin (Sn)
Lithium (Li)	Vanadium (V)
Manganese (Mn)	Zirconium (Zr)
Neptunium (Np)	

impurities. Impurity elements measured and their associated limits may differ from what is listed in this specification as agreed upon between the buyer and seller.

5.6 Moisture Content—The moisture content shall be measured and reported on a Pu basis. The maximum acceptable moisture content shall be agreed upon between the buyer and the seller.

5.7 Equivalent Boron Content—For thermal reactor use, the total equivalent boron content (EBC) shall not exceed 20.0 µg/g on a Pu basis. The method of performing the calculation shall be as indicated in Practice C1233. For fast reactor use, the above limitation on EBC does not apply.

5.8 Gamma Activity—The gamma activity (Bq/g Pu) of the gamma emitting fission products whose isotopes have half lives of 30 days or greater shall be measured. The gamma radiation from fission products shall be less than 10<sup>5</sup> MeV·Bq/g Pu.

<sup>4</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, http://www.asme.org.