

Designation: F 1240 - 01

Standard Guide for Ranking Footwear Bottom Materials on Contaminated Walkway Surfaces According to Slip Resistance Test Results¹

This standard is issued under the fixed designation F 1240; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This guide describes a method for ranking slip resistance test results of footwear bottom materials on contaminated walkway surfaces.
- 1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Summary

- 2.1 Slip resistance test results of two or more footwear bottom materials are compared on a walkway surface after adding contaminants likely to be found on the walkway. For each contaminant, the footwear bottom material with the highest test result is ranked 1, the footwear bottom material with the next highest test result is ranked 2, and so forth. The rankings for each footwear bottom material are totaled.
- 2.2 The footwear bottom material with the lowest total ranking number can be regarded as the most slip-resistant under the conditions of the test.

3. Significance and Use

- 3.1 This guide provides a method for comparing footwear bottom materials based on their slip characteristics on contaminated surfaces.
- 3.2 In places where the presence of contamination is expected and in places where it is not feasible to keep walkway surfaces continually clean and dry, it may be appropriate to suggest footwear bottom materials with better slip resistance test results (that is, a lower total ranking number). Examples could include food preparation areas, rendering operations, places where machine oil is used, and cargo handling areas.
- ¹ This guide is under the jurisdiction of ASTM Committee F13 on Safety and Traction for Footwear and is the direct responsibility of Subcommittee F13.50 on Walkway Safety Practices.
- Current edition approved Oct. 10, 2001. Published December 2001. Originally published as F 1240 89. Last previous edition F 1240 89 $(1995)^{\epsilon 1}$.

3.3 This guide may be useful to safety professionals, union officials, and company management.

4. Procedure

- 4.1 Select two or more pieces of footwear bottom material for slip resistance testing. If testing the whole shoe bottom is not feasible, select a piece from the back of the heel bottom or from the center of the ball of the shoe bottom. Consideration should be given to both tread design and soling material. Footwear or soling suppliers, or both, can be a source of information for assisting with selection of appropriate bottom materials.
- 4.2 Select an appropriate method for slip resistance testing. Test methods under the jurisdiction of ASTM Committee F13 would be appropriate.
- 4.3 Select a walkway surface and contaminants based on the expected normal environmental exposure of the footwear.
- 4.4 Place an appropriate contaminant on the walkway surface and on the footwear bottom material. Describe the contaminant and the method for applying it, the walkway surface, and the test procedure in sufficient detail so others can reproduce the test procedure.
- 4.5 Test slip resistance of the bottom material on the walkway surface in accordance with the appropriate test method instructions.
- 4.6 Select another bottom material and place contaminant on it. Replenish the contaminant on the walkway surface. Continue as in 4.5.
- 4.7 Continue testing in this way until all the bottom materials have been tested.
- 4.8 Assign a rank of 1 to the bottom material that has the highest test result, 2 to the material with the next highest test result, and so on until all the materials have been ranked. When two or more slip resistance test results are equal, give each one the average of the rank values they otherwise would have had. For instance, if there is a tie for second and third, give each a value of 2.5. If there is a tie for second, third, and fourth, give each a value of 3.