



**Designation: B121/B121M – 16**

# Standard Specification for Leaded Brass Plate, Sheet, Strip, and Rolled Bar<sup>1</sup>

This standard is issued under the fixed designation B121/B121M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification establishes the requirements for leaded brass plate, sheet, strip, and rolled bar. The following alloys are covered:

Copper Alloy UNS No. <sup>2</sup>	Previously Used Designation	Nominal Composition, %			
		Copper	Zinc	Lead	Iron
C33500	2	63.5	36.0	0.5	...
C34000	3	63.5	35.5	1.0	...
C34200	5	63.5	34.5	2.0	...
C35000	...	61.5	37.4	1.1	...
C35300	4	61.5	36.7	1.8	...
C35600	6	61.5	36.0	2.5	...

1.2 *Units*—Values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

**B248** Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved April 1, 2016. Published April 2016. Originally approved in 1939. Last previous edition approved in 2011 as B121/B121M – 11. DOI: 10.1520/B0121\_B0121M-16.

<sup>2</sup> The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and suffix “00.” The suffix can be used to accommodate composition variations of the base alloy

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

**B248M** Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)

**B601** Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

**B846** Terminology for Copper and Copper Alloys

**E8/E8M** Test Methods for Tension Testing of Metallic Materials

**E112** Test Methods for Determining Average Grain Size

**E255** Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

**E478** Test Methods for Chemical Analysis of Copper Alloys

**E527** Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

## 3. General Requirements

3.1 The following sections of Specifications **B248** or **B248M** constitute a part of this specification:

3.1.1 Terminology

3.1.2 Materials and Manufacture

3.1.3 Workmanship, Finish, and Appearance

3.1.4 Sampling—except for chemical analysis

3.1.5 Number of Tests and Retests

3.1.6 Specimen Preparation

3.1.7 Test Methods—except for chemical analysis

3.1.8 Significance of Numerical Limits

3.1.9 Inspection

3.1.10 Rejection and Rehearing

3.1.11 Certification

3.1.12 Test Reports

3.1.13 Packaging and Package Marking

3.1.14 Supplementary Requirements

3.2 In addition, when a section with a title identical to that referenced in 3.1, above, appears in this specification, it contains additional requirements which supplement those appearing in Specifications **B248** or **B248M**.

\*A Summary of Changes section appears at the end of this standard



## 4. Terminology

4.1 For definitions of terms related to copper and copper alloys, refer to Terminology B846.

## 5. Ordering Information

5.1 Include the following specified choices when placing orders for product under this specification, as applicable:

- 5.1.1 ASTM designation and year of issue,
- 5.1.2 Copper [Alloy] UNS No. designation,
- 5.1.3 Temper (Section 8),
- 5.1.4 Dimensions: thickness and width (11.1.1 and 11.1.2),
- 5.1.5 How furnished: straight lengths or coils,
- 5.1.6 Quantity—total weight or total length or number of pieces of each size,
- 5.1.7 Type of edge, if required (slit, sheared, sawed, square corners, round corners, rounded edges, or full-rounded edges) (11.1.5),
- 5.1.8 Length (11.1.3), and
- 5.1.9 Intended application.

5.2 The following options are available but may not be included unless specified at the time of placing the order when required:

- 5.2.1 Heat identification or traceability details.
- 5.2.2 Certification,
- 5.2.3 Mill Test Report,
- 5.2.4 If product is purchased for agencies of the U. S. government (see the Supplementary Requirements section of Specifications B248 or B248M for additional requirements, if specified).

## 6. Materials and Manufacture

### 6.1 Materials:

6.1.1 The material of manufacture shall be a form (cast bar, cake, slab, et cetera) of Copper Alloy UNS No. C33500, C34000, C34200, C35000, C35300, or C35600 of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 When specified in the contract or purchase order that heat identification or traceability is required, the purchaser shall specify the details desired.

NOTE 1—Due to the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.

### 6.2 Manufacture:

6.2.1 The product shall be manufactured by such hot working, cold working, and annealing processes as to produce a uniform wrought structure in the finished product.

6.2.2 The product shall be hot or cold worked to the finished size and subsequently annealed when required, to meet the temper properties specified.

### 6.3 Edges:

6.3.1 Slit edges shall be furnished unless otherwise specified in the contract or purchase order.

## 7. Chemical Composition

7.1 The material shall conform to the composition requirements in Table 1 for the copper [alloy] UNS No. designation specified in the ordering information.

7.2 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and purchaser, limits may be established and analysis required for unnamed elements.

7.3 For alloys in which zinc is listed as “remainder,” either copper or zinc may be taken as the difference between the sum of results of all other elements determined and 100 %. When all elements in Table 1 are determined, the sum of the results shall be as shown in the following table:

Copper Alloy UNS No.	Copper Plus Named Elements, % min.
C33500	99.6
C34000	99.6
C34200	99.6
C35000	99.6
C35300	99.5
C35600	99.5

## 8. Temper

8.1 The standard tempers for products described in this specification are given in Tables 2 and 3.

- 8.1.1 Cold rolled tempers H01 and H10.
- 8.1.2 Annealed tempers OS025 to OS070.

## 9. Grain Size for Annealed Tempers

9.1 Grain size shall be the standard requirement for all product in the annealed tempers.

9.2 Acceptance or rejection based upon grain size shall depend only on the average grain size of a test specimen taken from each of two sample portions, and each specimen shall be within the limits prescribed in Table 3 when determined in accordance with Test Methods E112.

9.3 Grain size shall be determined on a plane parallel to the flat surfaces of the product.

## 10. Mechanical Property Requirements

### 10.1 Tensile Strength Requirements:

10.1.1 Product furnished under this specification shall conform to the tensile requirements prescribed in Table 2 when tested in accordance with Test Methods E8/E8M.

10.1.2 Acceptance or rejection based on mechanical properties shall depend only on tensile strength.

### 10.2 Rockwell Hardness:

TABLE 1 Chemical Requirements

Copper Alloy UNS No.	Composition			
	Copper	Lead	Iron	Zinc
C33500	62.0–65.0	0.25–0.7	0.10 max	remainder
C34000	62.0–65.0	0.8–1.5	0.10 max	remainder
C34200	62.0–65.0	1.5–2.5	0.10 max	remainder
C35000	60.0–63.0	0.8–2.0	0.10 max	remainder
C35300	60.0–63.0	1.5–2.5	0.10 max	remainder
C35600	60.0–63.0	2.0–3.0	0.10 max	remainder