



Designation: **B577–10 B577 – 16**

Standard Test Methods for Detection of Cuprous Oxide (Hydrogen Embrittlement Susceptibility) in Copper¹

This standard is issued under the fixed designation B577; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 These test methods describe procedures for determining the presence of cuprous oxide (Cu_2O) in products made from deoxidized and oxygen-free copper.

1.2 The test methods appear in the following order:

	Sections
Microscopical Examination without Thermal Treatment	9 – 11
Microscopical Examination after Thermal Treatment	13 – 15
Closed Bend Test after Thermal Treatment	17 – 19
Reverse Bend Test after Thermal Treatment	21 – 23

1.3 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

E3 Guide for Preparation of Metallographic Specimens

E883 Guide for Reflected-Light Photomicrography [ASTM B577-16](https://standards.iteh.ai/ASTM-B577-16)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:

3.1.1 *deoxidized copper*—material produced substantially free of cuprous oxide, by the use of metallic or metalloidal deoxidizers, as determined by metallographic examination at 75 \times under polarized light. Oxygen may be present as residual deoxidation products.

3.1.2 *oxygen-free copper*—electrolytic copper produced substantially free of cuprous oxide without the use of metallic or metalloidal deoxidizers as determined by metallographic examination at 75 \times under polarized light. Oxygen may be present up to a maximum of 5 ppm in Copper UNS No. C10100 and 10 ppm in Copper UNS No. C10200.

4. Summary of Test Methods

4.1 The presence of cuprous oxide is determined either by microscopical examination under polarized light or by methods that involve heating the test specimens in a hydrogen-rich atmosphere and rapidly cooling the specimens without undue exposure to air followed by a microscopical examination or a suitable bend test.

¹ These test methods are under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.06 on Methods of Test.

Current edition approved Oct. 1, 2010/April 1, 2016. Published November 2010/April 2016. Originally approved in 1973. Last previous edition approved in 2004/2010 as B577–93/B577–10. (2004). DOI: 10.1520/B0577-10.10.1520/B0577-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

5. Significance and Use

5.1 These test methods determine whether copper products will be resistant to embrittlement when exposed to elevated temperatures in a reducing atmosphere.

5.1.1 It is assumed that all who use these test methods will be trained personnel capable of performing these procedures skillfully and safely. It is expected that work will be performed in a properly equipped facility.

6. Apparatus

6.1 *Test Method A*—Metallographic equipment of the type described in Practice Guide E3 and Guide E883 suitably equipped with a polarized light illuminating device.

6.2 *Test Methods B, C, and D*:

6.2.1 Metallographic equipment of the type described in Practice Guide E3 and Guide E883 provided with normal illumination.

6.2.2 A furnace of sufficient capacity, capable of maintaining the required reducing atmosphere while the specimens are being heated. A rapid cooling device using either water or a reducing atmosphere is required.

6.2.3 A machinist vise with replaceable matching pairs of jaw mandrels of various radii contours.

7. Sampling

7.1 Sampling shall be in accordance with the requirements of the specification under which the material was ordered.

8. Test Specimens

8.1 Longitudinal specimens, that is, specimens whose axes are parallel to the direction of working are preferable. However, equally reliable results can be obtained with specimens in which the axis is perpendicular to the directions of working.

8.2 Specimens shall be of dimensions suitable for the performance of the required tests. Where necessary to cut a specimen from an oversize piece of material, at least one of the original surfaces of the material shall be retained in the test specimen. Suggested dimensions for test specimens for Procedures C or D are given in the following table:
(for Procedures C or D):

Wrought Products	Suggested Dimensions for Test Specimens
Flats (wire, strip, sheets, bar, and plate)	thickness—that of the product but should not exceed 1/2 in. (13 mm)
Flats (wire, strip, sheets, bar, and plate)	thickness—that of the product but should not exceed 1/2 in. (13 mm)
	width—approx. 1/2 in. (13 mm)
	width—approx. 1/2 in. (13 mm)
	length—approx. 6 in. (152 mm)
	length—approx. 6 in. (152 mm)
Shapes and forgings	To the extent that the dimensions of the material permit, the dimensions of the test specimens are those suggested for the flat products specimens.
	To the extent that the dimensions of the material permit, the dimensions of the test specimens are those suggested for the flat products specimens.
	(Where the product dimensions, particularly length, as in the case of forgings, do not permit taking a specimen, the total product may then become the test specimen for examination by Procedures A or B.)
	(Where the product dimensions, particularly length, as in the case of forgings, do not permit taking a specimen, the total product may then become the test specimen for examination by Procedures A or B.)
Wire or rod	diameter or distance between parallel surfaces—that of the product but not to exceed 1/2 in. (13 mm)
Wire or rod	diameter or distance between parallel surfaces—that of the product but not to exceed 1/2 in. (13 mm)