



Designation: **C522 – 03 (Reapproved 2009)^{ε1} C522 – 03 (Reapproved 2016)**

Standard Test Method for Airflow Resistance of Acoustical Materials¹

This standard is issued under the fixed designation C522; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Section 1.4.1 was editorially added in March 2010.

1. Scope

1.1 This test method covers the measurement of airflow resistance and the related measurements of specific airflow resistance and airflow resistivity of porous materials that can be used for the absorption and attenuation of sound. Materials cover a range from thick boards or blankets to thin mats, fabrics, papers, and screens. When the material is anisotropic, provision is made for measurements along different axes of the specimen.

1.2 This test method is designed for the measurement of values of specific airflow resistance ranging from 100 to 10 000 mks rayls (Pa·s/m) with linear airflow velocities ranging from 0.5 to 50 mm/s and pressure differences across the specimen ranging from 0.1 to 250 Pa. The upper limit of this range of linear airflow velocities is a point at which the airflow through most porous materials is in partial or complete transition from laminar to turbulent flow.

1.3 A procedure for accrediting a laboratory for the purposes of this test method is given in **Annex A1**.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4.1 **Table 1** is provided for user to convert into cgs units.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E384 Test Method for Microindentation Hardness of Materials

C634 Terminology Relating to Building and Environmental Acoustics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Terminology

3.1 *Definitions:* The definitions used in this test method are contained in Terminology **C634**.

3.2 *Definitions of Terms Specific to This Standard:* The following items have been modified to exclude alternating flow.

3.2.1 *airflow resistance, R;* mks acoustic ohm

(Pa·s/m³)—the quotient of the air pressure difference across a specimen divided by the volume velocity of airflow through the specimen.

3.2.2 *airflow resistivity, r_0 ;* mks rayl/m (Pa·s/m²)— *of a homogeneous material*, the quotient of its specific airflow resistance divided by its thickness.

3.2.3 *lateral airflow resistivity— of an anisotropic homogeneous material*, the airflow resistivity when the direction of airflow is parallel to the face of the material from which the test specimen is taken.

3.2.4 *specific airflow resistance, r;* mks rayl (Pa·s/m)—the product of the airflow resistance of a specimen and its area. This is equivalent to the air pressure difference across the specimen divided by the linear velocity of airflow measured outside the specimen.

¹ This test method is under the jurisdiction of ASTM Committee **E33** on Building and Environmental Acoustics and is the direct responsibility of Subcommittee **E33.01** on Sound Absorption.

Current edition approved Oct. 1, 2009 April 1, 2016. Published February 2010 April 2016. Originally approved in 1963. Last previous edition approved in 2003 2009 as **C522 – 03**; **C522 – 03 (2009)^{ε1}**. DOI: 10.1520/C0522-03R09E01.10.1520/C0522-03R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Conversion from cgs to mks and SI units

To convert from	to	Multiply by
cgs acoustic ohm	mks acoustic ohm (Pa·s/m ³)	10 ⁵
cgs rayl	mks rayl (Pa·s/m)	10
cgs rayl/cm	mks rayl/m (Pa·s/m ²)	10 ³
cgs rayl/in.	mks rayl/m (Pa·s/m ²)	394
mks rayl/in.	mks rayl/m (Pa·s/m ²)	39.4

3.2.5 *transverse airflow resistivity*— of an anisotropic homogeneous material, the airflow resistivity when the direction of airflow is perpendicular to the face of the material from which the test specimen is taken.

3.3 Application of Terms:

3.3.1 The term *airflow resistance* can be applied to specimens of any kind.

3.3.2 The term *specific airflow resistance* has meaning only when applied to a specimen of uniform thickness that is homogeneous in directions parallel to its surface but not necessarily homogeneous in the direction of airflow perpendicular to its surface.

3.3.3 The term *airflow resistivity* has meaning only when applied to a specimen that is homogeneous in directions parallel to a and perpendicular to its surface but not necessarily isotropic.

3.4 Symbols:

3.4.1 P = air pressure difference across test specimen, Pa.

3.4.2 U = volume velocity of airflow through the specimen, m³/s.

3.4.3 $u = U/S$ = linear velocity of airflow outside the specimen, m/s.

3.4.4 S = area of specimen, m².

3.4.5 T = thickness of specimen, m.

4. Summary of Test Method

4.1 This test method describes how to measure a steady flow of air through a test specimen, how to measure the air pressure difference across the specimen, and how to measure the volume velocity of airflow through the specimen. From the measurements may be calculated the airflow resistance, R , the specific airflow resistance, r , and the airflow resistivity, r_0 .

5. Significance and Use

5.1 The specific airflow resistance of an acoustical material is one of the properties that determine its sound-absorptive and sound-transmitting properties. Measurement of specific airflow resistance is useful during product development, for quality control during manufacture, and for specification purposes.

5.2 Valid measurements are made only in the region of laminar airflow where, aside from random measurement errors, the airflow resistance ($R = P/U$) is constant. When the airflow is turbulent, the apparent airflow resistance increases with an increase of volume velocity and the term “airflow resistance” does not apply.

5.3 The specific airflow resistance measured by this test method may differ from the specific resistance measured by the impedance tube method in Test Method E384 for two reasons. In the presence of sound, the particle velocity inside a porous material is alternating while in this test method, the velocity is constant and in one direction only. Also, the particle velocity inside a porous material is not the same as the linear velocity measured outside the specimen.

6. Apparatus

6.1 The apparatus, assembled as shown schematically in Fig. 1, consists of the following components:

6.1.1 *Air Supply*, a suction generator or positive air supply arranged to draw or force air at a uniform rate through the test specimen.

NOTE 1—It may be necessary to use a large surge tank or other means to reduce pressure fluctuations.

6.1.2 *Flowmeter*, to measure the volume velocity of airflow through the specimen. It is preferable to have two or more flowmeters with overlapping ranges to enable different airflow velocities to be measured to the same precision.

6.1.3 *Differential Pressure Measuring Device*, for measuring the static pressure difference between the faces of the specimen with respect to atmosphere.

NOTE 2—A slant manometer or pressure transducer system with a range from 0 to 250 Pa is usually satisfactory, but a second instrument with a smaller range, for example, 0 to 25 Pa, may be necessary for measuring small pressures to the desired precision.

6.1.4 *Specimen-Mounting Assembly*, consists essentially of a mounting plate and a specimen holder as shown in Fig. 2. The mounting plate has two holes for tube connections to the pressure measuring device and to the airflow supply. The specimen holder, which is sealed to the mounting plate, is preferably a transparent plastic tube at least 150 mm long with a diameter not less than 50 mm. For testing materials that will support themselves, such as disks cut from boards, a slight taper at the top of holder will