

Designation: $D4391 - 16D4391 - 16^{\epsilon 1}$

Standard Terminology Relating to The Burning Behavior of Textiles¹

This standard is issued under the fixed designation D4391; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

The definitions in this standard have been approved by the Society and are included in D123 "Terminology Relating to Textiles". They are published as a separate collection for the convenience of persons interested in the burning behavior of textiles. A bibliography of related literature is given in Appendix X1.

ε¹ NOTE—Terms from Test Method D1230 were added in April 2016.

afterflame, *n*—persistent flaming of a material after the ignition source has been removed.

[D13.92] D4391

after-flame time, n—the length of time for which a material continues to flame after the ignition source has been removed. [D13.92] D4391

afterglow, *n*—glow in material after the removal of an external ignition source or after the cessation (natural or induced) of flaming of the material. (See also **flame, glow**, and **smoldering**.)

afterglow time, *n*—the time afterglow continues after the cessation of flaming or after removal of the ignition source. **[D13.92] D4391**

base burn, *n*—the point at which the flame burns the ground (base) fabric of a raised surface textile fabric and provides a self-sustaining flame.

Discussion—

ASTM D//301 16e1

Base burn is also known as base fabric ignition or fusing. The base burns used to establish a Class 3 fabric are those burns resulting from surface flash that occur on specimens in places other than the point of impingement when the warp and fill yarns of a raised surface textile fabric undergo combustion. Base burns can be identified by an opacity change, scorching on the reverse side of the fabric, or when a physical hole is evident.

burn time, *n*—the time elapsed from ignition until the stop thread is severed as measured by the timing mechnsim of the test apparatus.

burning behavior, n—all the changes that take place when materials or products are exposed to a specified ignition source.

charring, *n*—the formation of carbonaceous residue as the result of pyrolysis or incomplete combustion.

combustible textile, *n*—a textile that will ignite and burn or that will give off vapors that will ignite and burn when subjected to external sources of ignition. (Compare **flammable textile, noncombustible textile.**)

combustion, *n*—a chemical process of oxidation that occurs at a rate fast enough to produce heat and usually light either as glow or flames.

DISCUSSION—

Some oxidation such as that of hydrogen emits radiation outside the visible spectrum.

critical sewn seams, *n*—*in assembly of flame resistant textiles*, those sewn junctions where failure would result in immediate danger or injury.

¹ This terminology is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.92 on Terminology. Current edition approved Feb. 15, 2016. Published March 2016. Originally approved in 1984. Last previous edition approved in 2013 as D4391 – 93a(2013)⁶¹. DOI: 10.1520/D4391-16.10.1520/D4391-16E01.

dangerously flammable textile, *n*— not defined. This term is implied in the Standard for the Flammability of Clothing Textiles (16 CFR Part 1610) under the Flammable Fabrics Act (15 USC 1191, et seq.) from which a meaning can be inferred. (See also **flammable textile**.)

embrittlement, n—the formation of a brittle residue as the result of pyrolysis or incomplete combustion.

exposure energy to thermal end point, n—the thermal energy transferred through a specimen that is sufficient to cause ignition of contiguous materials. [D13.92] D7140

fire, *n*—as related to textile flammability, an uncontrolled conflagration in which materials are destroyed by burning as evidenced by flames of varying size and shape, and a high intensity heat source of 5 kw or greater, such as a burning waste basket, grease-fire on a stove, burning building or forest fire.

flame, *n*—as related to textile flammability, a hot luminous zone of gas or matter in gaseous suspension, or both, that is undergoing combustion, that is relatively constant in size and shape, and that produces a relatively low heat flux. (Compare **fire**.)

DISCUSSION-

Examples are a match flame, candle flame, or a Bunsen burner gas flame.

flame application time, n—the time for which the ignition flame is applied to a material.

flame resistance, *n*—the property of a material whereby flaming combustion is prevented, terminated, or inhibited following application of a flaming or nonflaming source of ignition, with or without subsequent removal of the ignition source.

DISCUSSION-

Flame resistance can be an inherent property of the basic material or product, or it may be imparted by specific treatment. The degree of flame resistance exhibited by a specific material during testing may vary with different test conditions.

flame resistant, adj—indicating characteristics that can enhance inhibition of a textile to flaming.

DISCUSSION-

Document Preview

"Flame resistant" is the government mandated description for certain products that meet established governmental conformance standards or specifications when the product is tested by a specific method. Where no conformance standards exist, "flame resistant" is a relative term and is used to compare one material to another.

flame retardant, *adj*—not defined. This term should not be used as an adjective except in the terms "flame-retardant-treated" and "flame-retardant treatment".

flame retardant, *n*—a chemical used to impart flame resistance.

flame-retardant-treated, *adj*—having received a flame-retardant treatment.

DISCUSSION-

The term "flame-retardant-treated" does not apply to textiles that are inherently-flame-resistant due to the intrinsic properties of the material or the fiber-forming polymer.

flame-retardant treatment, n—a process for incorporating or adding flame retardant(s) to a material or product.

DISCUSSION-

The term "flame-retardant treatment" does not apply to textiles that are inherently flame resistant due to the intrinsic properties of the material or the fiber-forming polymer.

flame spread, *n*—the propagation of a flame away from the source of ignition.

[D13.92] D4391

flame spread time, *n*—the time taken by a flame on a burning material to travel a specified distance under specified conditions. [D13.92] D4391

flammability, *n*—those characteristics of a material that pertain to its relative ease of ignition and relative ability to sustain combustion.