This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: A290/A290M - 05 (Reapproved 2015) A290/A290M - 16

# Standard Specification for Carbon and Alloy Steel Forgings for Rings for Reduction Gears<sup>1</sup>

This standard is issued under the fixed designation A290/A290M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

# 1. Scope-Scope\*

1.1 This specification covers normalized and tempered, and quenched and tempered, carbon and alloy steel forged or rolled rings for reduction gears.

1.2 Several grades and classes of steel are covered as follows:

1.2.1 Grade 1, Classes A and B, and Grade 2, Classes C and D, are carbon steel.

1.2.2 Grade 3, Classes E and F, Grade 4, Classes G, H, I, J, K and L, Grade 5, Classes M and P, and Grade 6, Class T, are alloy steel.

1.2.3 All grades and classes are considered weldable under proper conditions. Welding techniques are of fundamental importance and it is pre-supposed that welding procedure and inspection will be in accordance with proper methods for the class of material used.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

## 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

A275/A275M Practice for Magnetic Particle Examination of Steel Forgings A370 Test Methods and Definitions for Mechanical Testing of Steel Products A388/A388M Practice for Ultrasonic Examination of Steel Forgings -ebd54a9d78fc/astm-a290-a290m-16 A788/A788M Specification for Steel Forgings, General Requirements

## 3. Terminology

3.1 Definitions of the terms used may be found in Specification A788/A788M.

## 4. Ordering Information and General Requirements

4.1 In addition to the ordering information required by Specification A788/A788M, the purchaser shall specify in the inquiry, contract, and order the grade and class desired and the supplementary requirements, if any, which should apply.

4.2 Material supplied to this specification shall conform to the requirements of Specification A788/A788M, which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

## 5. Materials and Manufacture

5.1 Melting Process:

#### \*A Summary of Changes section appears at the end of this standard

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved June 1, 2015 May 1, 2016. Published June 2015 May 2016. Originally approved in 1946. Last previous edition approved in 2010/2015 as A290/A290M – 05(2010). DOI: 10.1520/A0290\_A0290M-05R15.10.1520/A0290\_A0290M-16.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.



5.1.1 The steel shall be produced by any of the melting requirements in Specification A788/A788M, which may be supplemented by Supplementary Requirement S6, Vacuum Degassing.

5.2 Discard—Sufficient discard shall be taken from each ingot to secure freedom from piping and undue segregation.

5.3 *Forging Process*—The forgings shall receive their hot mechanical work in accordance with the requirements of Specification A788/A788M.

5.4 Heat Treatment:

5.4.1 *Cooling Prior to Heat Treatment*—After forging and before reheating for heat treatment, the forgings shall be allowed to cool in a manner to prevent injury, to accomplish transformation, and prevent flakes.

5.4.2 Heat treatment shall consist of normalizing and tempering for Grade 1 classes A and B and quenching and tempering for all other grades and classes.

5.4.2.1 Normalizing—A furnace charge thus treated is termed a normalizing charge.

5.4.2.2 *Quenching*—The forgings shall be completely austenitized and then quenched in a suitable medium. A group thus treated is termed a quenching charge.

5.4.2.3 *Tempering*—A furnace charge thus treated is termed a tempering charge. Minimum tempering temperatures shall be as follows:

	Minimum Tempering Temperature		
Grade and Class °F	[°C]		
Grade 1 Classes A and B 1200	[650]		
Grade 2 Classes C & D, E, F, G, H, M, P 1100	[595]		
Grade 3 Classes E & F 1100	[595]		
Grade 4 Classes G & H 1100	[595]		
Grade 5 Classes M & P 1100	[595]		
Grade 4 Classes I, J, K & L 1050	[565]		
Grade 6 Class T 1000	[540]		

#### 5.5 Machining:

5.5.1 Rough machining before heat treatment for mechanical properties may be performed at the option of the producer.

5.5.2 The forgings shall conform to the sizes and shapes specified by the purchaser.

#### 6. Chemical Composition

6.1 *Composition*—The steel shall conform to the requirements for chemical composition prescribed in Table 1. Alternative compositions may be agreed upon in accordance with Supplementary Requirement S1.1.

6.1.1 *Heat Analysis*—The heat analysis obtained from sampling in accordance with Specification A788/A788M shall comply with Table 1.

6.1.2 *Product Analysis*—An analysis may be made by the purchaser from a forging representing each heat. Samples for analysis may be taken from the forging or from a full-size prolongation at any point midway between the inner and outer surfaces of the ring or samples may be taken from the test specimen. The chemical composition thus determined shall not vary from the requirements prescribed in Table 1 by more than the amounts prescribed in Specification A788/A788M.

## 7. Mechanical Properties

7.1 *Tension and Impact Test Requirements*—The requirements for tensile and impact properties shall be as prescribed in Table 2.

TABLE 1 Chemical Requirements								
Element	Composition, %							
	Grade 1 Classes A and B	Grade 2 Classes C and D	Grade 3 Classes E and F	Grade 4 Classes G, H, I, J, K, and L	Grade 5 Classes M and P	Grade 6 Class T		
Carbon	0.35-0.50	0.40-0.50	0.35-0.45	0.35-0.45	0.38-0.45	0.25-0.39		
Manganese	0.60-0.90	0.60-0.90	0.70-1.00	0.60-0.90	0.40-0.70	0.20-0.60		
Phosphorus, max	0.040	0.040	0.040	0.040	0.040	0.015		
Sulfur, max	0.040	0.040	0.040	0.040	0.040	0.015		
Silicon <sup>A</sup> , max	0.35	0.35	0.35	0.35	0.40	0.35		
Nickel	0.30 max	0.30 max	0.50 max	1.65-2.00	0.30 max	3.25-4.00		
Chromium	0.25 max	0.25 max	0.80-1.15	0.60-0.90	1.40-1.80	1.25-1.75		
Molybdenum	0.10 max	0.10 max	0.15-0.25	0.20-0.50	0.30-0.45	0.30-0.70		
Vanadium, max	0.06	0.06	0.06	0.10	0.03	0.05-0.15		
Copper, max Aluminum	0.35	0.35	0.35	0.35	0.35 0.85–1.30	0.35		

<sup>A</sup> When vacuum carbon deoxidation is used, silicon maximum shall be 0.10 %.